DYCONIL DYES

The economical package of standard acid dyes for leather

DYCONIL
DYES

The economical package of standard acid dyes for leather

	Solubility in g/l	Light fastness	Washing fastness	Perspiration fastness	Rubbing fastness		Penetration	Migration to PVC
	60 °C	1/1	ALT CO WO	ALT CO WO	Wet	Dry	IUF 421	IUF 442
0.5% 2.0% 4.0%	**DYCONIL** Yellow 5GN # C.I. Acid Yellow 110	50	3-4	3 4 3	3 3 4	3	4	3	2
0.5% 2.0% 4.0%	**DYCONIL** Yellow RS # C.I. Acid Yellow 42	40	3	1 3 4	3 4-5 2	3-4	4	3	3
0.5% 2.0% 4.0%	**DYCONIL** Yellow 3RL # C.I. Acid Yellow 194	60	5	4 4-5 5-6	3 2-3 3-4	3-4	4	4	4
0.5% 2.0% 4.0%	**DYCONIL** Fur Yellow EG # C.I. Acid Orange 3	50	3	3 4 3	4 4 3-4	3-4	4-5	4	3
0.5% 2.0% 4.0%	**DYCONIL** Orange RL # C.I. Acid Orange 142	60	3	2 4-5 4-5	4 2-3 2	3	4	4	2-3
0.5% 2.0% 4.0%	**DYCONIL** Brown RD # C.I. Acid Brown 14	50	2-3	2 2-3 4-5	2 2 2	3-4	4	3	3-4
0.5% 2.0% 4.0%	**DYCONIL** Brown DS # C.I. Acid Brown 58	60	4-5	5 4-5 4	2 1 2	3-4	4-5	3	3-4
0.5% 2.0% 4.0%	**DYCONIL** Brown CRN # C.I. Acid Brown 75	50	4	1-3 2 2-3	3 3 1	3	3-4	4	2-3

DYCONIL
DYES

The economical package of standard acid dyes for leather

	Solubility in g/l	Light fastness	Washing fastness	Perspiration fastness	Rubbing fastness		Penetration	Migration to PVC
	60 °C	1/1	ALT CO WO	ALT CO WO	Wet	Dry	IUF 421	IUF 442
0.5% 2.0% 4.0%	**DYCONIL** Brown CGG # C.I. Acid Brown 83	60	3-4	3 2-3 4-5	4 2-3 2	3	4	3	3
0.5% 2.0% 4.0%	**DYCONIL** Brown MTG # C.I. Acid Brown 97	60	3-4	4 3 3	2 2 2	3-4	4-5	3	3
0.5% 2.0% 4.0%	**DYCONIL** Brown 5GG # C.I. Acid Brown 98	50	3-4	3 3-4 3	1 2 2	3-4	4	4	3
0.5% 2.0% 4.0%	**DYCONIL** Brown ORG # C.I. Acid Brown 100	50	3-4	2-3 3-4 4	4-5 2-3 4	3-4	4-5	2	3-4
0.5% 2.0% 4.0%	**DYCONIL** Brown WR # C.I. Acid Brown 106	50	2-3	3 2 3	2 3 2	3-4	4	3-4	3
0.5% 2.0% 4.0%	**DYCONIL** Brown GBG # C.I. Acid Brown 161	60	5	5 4-5 4	2 1 2	3-4	4	3	3
0.5% 2.0% 4.0%	**DYCONIL** Brown NTG # C.I. Acid Brown 165	60	4-5	5 4 1-2	4 3 2-3	3-4	4	5	3-4
0.5% 2.0% 4.0%	**DYCONIL** Brown HHG # C.I. Acid Brown 188	60	4-5	5 4-5 4	3 3 3	3-4	3	3	2-3

DYCONIL
DYES

The economical package of standard acid dyes for leather

	Solubility in g/l	Light fastness	Washing fastness	Perspiration fastness	Rubbing fastness		Penetration	Migration to PVC
	60 °C	1/1	ALT CO WO	ALT CO WO	Wet	Dry	IUF 421	IUF 442
0.5% 2.0% 4.0%	**DYCONIL** Brown DR # C.I. Acid Brown 191	50	4	3 2-3 3	4 3 1	3-4	4	3	3-4
0.5% 2.0% 4.0%	**DYCONIL** Brown RT # C.I. Acid Brown 214	50	4	2 3 2	2 3 2-3	3-4	54	3-4	3
0.5% 2.0% 4.0%	**DYCONIL** Brown GRG # C.I. Acid Brown 282	50	4	1-2 4 3	2 2 2	3-4	4	3	3
0.5% 2.0% 4.0%	**DYCONIL** Brown DRT # C.I. Acid Brown 348	60	3-4	2 2 3	1 2-3 1	3-4	4	3	3
0.5% 2.0% 4.0%	**DYCONIL** Brown GSG # C.I. Acid Brown 349	60	3	2 2 3	1 2-3 1	2-3	3-4	3	2-3
0.5% 2.0% 4.0%	**DYCONIL** Brown S3RG # C.I. Acid Brown 354	50	3-4	1-2 4 3	3 2 2	3-4	4-5	3	3
0.5% 2.0% 4.0%	**DYCONIL** Brown BL # C.I. Acid Brown 355	60	4	3-4 4 5	4-5 3 2-3	3	4	5	3
0.5% 2.0% 4.0%	**DYCONIL** Brown 2RL # C.I. Acid Brown 365	50	4	3-4 3-4 4	3-4 3 4	3-4	4-5	4	3

DYCONIL
DYES

The economical package of standard acid dyes for leather

	Solubility in g/l	Light fastness	Washing fastness	Perspiration fastness	Rubbing fastness		Penetration	Migration to PVC
	60 °C	1/1	ALT CO WO	ALT CO WO	Wet	Dry	IUF 421	IUF 442
0.5% 2.0% 4.0%	**DYCONIL** Brown SGL # C.I. Acid Brown 402	50	2-3	4-5 4-5 4-5	4-5 4-5 4	3-4	4-5	4	3
0.5% 2.0% 4.0%	**DYCONIL** Havana Brown 2RLX # C.I. Acid Brown 425	50	4-5	2 2-3 3-4	4-5 2-3 4	4-5	3-4	3	4
0.5% 2.0% 4.0%	**DYCONIL** Brown WG # C.I. Acid Brown 432	50	4-5	2 2-3 3-4	4-5 2-3 5	3-4	4-5	4	4
0.5% 2.0% 4.0%	**DYCONIL** Brown PRG # C.I. Acid Brown 434	50	4-5	1-2 2 2-3	4-5 2-3 5	3-4	4-5	4	4
0.5% 2.0% 4.0%	**DYCONIL** Brown 5GG # C.I. Acid Brown 452	50	4	2-3 3-4 4	4-5 2-3 5	3-4	4	4	2-3
0.5% 2.0% 4.0%	**DYCONIL** Beige MLK # C.I. Acid Beige Mix	70	3	2-3 2 3	4-5 2-3 3	3-4	3	4-5	4
0.5% 2.0% 4.0%	**DYCONIL** Beige OT # C.I. Acid Beige Mix	55	4-5	4-5 3 2-3	4-5 3 2-3	3-4	3-4	4-5	4-5
0.5% 2.0% 4.0%	**DYCONIL** Fast Red A # C.I. Acid Red 88	50	3-4	2 3 2	3 2 3	3	4	2-3	2

DYCONIL
DYES

The economical package of standard acid dyes for leather

	Solubility in g/l	Light fastness	Washing fastness	Perspiration fastness	Rubbing fastness		Penetration	Migration to PVC
	60 °C	1/1	ALT CO WO	ALT CO WO	Wet	Dry	IUF 421	IUF 442
0.5% 2.0% 4.0%	**DYCONIL** Scarlet R # C.I. Acid Red 97	50	2	1 4 4	2 3 2	3	4	3	2-3
0.5% 2.0% 4.0%	**DYCONIL** Bordo V # C.I. Acid Red 119	50	2	1 4 4	4 4 2	3	3-4	3	3
0.5% 2.0% 4.0%	**DYCONIL** Red 3BN # C.I. Acid Red 131	50	3	1 2 1	2 2 2	3	3-4	2-3	2
0.5% 2.0% 4.0%	**DYCONIL** Scarlet L # C.I. Acid Red 357	60	4	2 4-5 4-5	2 2 3	4	3-4	3	2-3
0.5% 2.0% 4.0%	**DYCONIL** Red BRG # C.I. Acid Red 362	50	5-6	2 4-5 4-5	2 2 3	4-5	3-4	3	4
0.5% 2.0% 4.0%	**DYCONIL** Bordeaux B # C.I. Acid Violet 90	50	2-3	2-3 2-3 4	3-4 3-4 4-5	3	3-4	4	3
0.5% 2.0% 4.0% 	**DYCONIL** Violet RL # C.I. Acid Violet 92	40	2-3	2 1-2 2	2-3 2 2	2-3	3	5	2-3
0.5% 2.0% 4.0%	**DYCONIL** Navy Blue 5R # C.I. Acid Blue 113	40	5	3 3-4 3-4	3 2 3	3-4	3-4	4	3

DYCONIL
DYES

The economical package of standard acid dyes for leather

	Solubility in g/l	Light fastness	Washing fastness	Perspiration fastness	Rubbing fastness		Penetration	Migration to PVC
	60 °C	1/1	ALT CO WO	ALT CO WO	Wet	Dry	IUF 421	IUF 442
0.5% 2.0% 4.0%	**DYCONIL** Navy Blue RL # C.I. Acid Blue 193	40	4	3-4 3 4	2-3 3 3	3	3-4	4	3
0.5% 2.0% 4.0%	**DYCONIL** Green PGG # C.I. Acid Green 1	50	3-4	2 2 3	3 2 2	3	5	4	3
0.5% 2.0% 4.0%	**DYCONIL** Dark Green B # C.I. Acid Green 20	50	4	1 3 4	2 1 1	3-4	4	4	2-3
0.5% 2.0% 4.0%	**DYCONIL** Green NG # C.I. Acid Green 68	50	4	1 3 4	2 1-2 2	3	4	4	3
0.5% 2.0% 4.0% 	**DYCONIL** Olive SG # C.I. Acid Green 73	50	3-4	3-4 3 4	2 2 1	4	4-5	3-4	2
0.5% 2.0% 4.0%	**DYCONIL** Olive Green BGL # C.I. Acid Green 104	50	3-4	3-4 3 4	2 2 1	3	2	5	3
0.5% 2.0% 4.0%	**DYCONIL** Black 10BX # C.I. Acid Black 1	40	4	1 3 4	2 1 2-3	2-3	3	1	2
0.5% 2.0% 4.0%	**DYCONIL** Black GL # C.I. Acid Black 84	80	2-3	1 3 4	2 2 2	3-4	4-5	3	2

DYCONIL
DYES

The economical package of standard acid dyes for leather

	Solubility in g/l	Light fastness	Washing fastness	Perspiration fastness	Rubbing fastness		Penetration	Migration to PVC
	60 °C	1/1	ALT CO WO	ALT CO WO	Wet	Dry	IUF 421	IUF 442
0.5% 2.0% 4.0%	**DYCONIL** Black AX # C.I. Acid Black 107	40	5-6	4-5 4 4-5	4-5 4 4	3-4	4	3	4
0.5% 2.0% 4.0%	**DYCONIL** Black BL # C.I. Acid Black 172	80	4-5	4-5 2-3 1-2	2 1 3	3-4	4	4	4
0.5% 2.0% 4.0%	**DYCONIL** Black RL # C.I. Acid Black 194	80	4-5	4-5 2-3 1-2	2 1 3	3-4	4	4	4
0.5% 2.0% 4.0%	**DYCONIL** Black RD # C.I. Acid Black 210	80	4-5	4-5 4 4-5	4-5 4 4	3-4	4-5	4	4
0.5% 2.0% 4.0%	**DYCONIL** Black LM # C.I. Acid Black 234	80	4-5	3 2-3 2	3 3-4 2	3	4	4	4-5

DATA ABOUT FASTNESS PROPERTIES

Penetration

is based on comparison to dyeings on split-leather.
Classification with a scale 1-5

Lightfastness

The lightfastness was tested on 2.0% chromside leather.
Xenotest 40h according to I.U.F. 402.
Classification is according to the blue-scale.

Migration into plasticized PVC (I.U.F. 442/132)

The migration rate was tested on 2.0% chromside leather.
The rate is based on the staining of the PVC.
Classification is according to the grey-scale ISO 105 A03.

Perspiration fastness (I.U.F. 426/132-133)

the perspiration fastness was tested without cationic fixatives.

The results are given in following order:

- change in leather colour - grey-scale ISO 105 A02
- staining of wool - grey-scale ISO 105 A03
- staining of cotton - grey-scale ISO 105 A03

Dyeing methods – overview

Dyeing methods of the illustrated leathers:

Full chrome side leather "Wet-Blue"

% is referring to the shaved weight

Washing	Water 40°C	300%	30 Min.
Neutralising	Water 40°C	200%	
	Sodium-Formate	0.3%	10 Min.
	Sodium-Bicarbonate	0.4%	30 Min.
Dyeing	Water 60°C	300%	
	DYCONIL Dye	X%	30 Min.
	DYCO-Licker LF	5%	30 Min.
	Formic acid	1%	30 Min.
Washing	Water 20°C	300%	10 Min.

DYCO COLOUR CHEM INDUSTRIES LLP

Corporate Office :

2, Crystal, Opposite Lubi Electronics, S.P Ring Road, Naroda, Ahmedabad, Gujarat, India – 382330 | Tel : +91 99048 85859 | Web : www.dyco.co.in | E-mail : info@dyco.co.in | export@dyco.co.in |