



## TDS-Technical Data Sheet

### ----Polycarboxylate Superplasticizer

**Company Name** : JSB Technology Co.,Ltd

**Address** : No. 202 Angang West Road,  
Dadaowan Economic Development  
Zone,Anshan City Liaoning  
Province,China

**Contact person** : **Robin Yam**

**Tel** : +86 412-5998881

**Fax** : +86 412-5237888

**Email** : jsbtech@163.com

\*\*\*\*\*

**Product Name:** Polycarboxylate Superplasticizer

**Product Code:**

**Usage:** it is a new excogitated environmental superplasticizer. It is a concentrated product, best high water reduction, high slump retention ability, low alkali content for the product, and it having high strength gained rate. It can be widely used in premix of common concrete, gushing concrete, high strength and durability concrete. Especially! It can be used in high strength and durability concrete having excellent capability

**Material:**

| Chemical Name | CAS No.   | Composition (% by weight) |
|---------------|-----------|---------------------------|
| Water         | 7732-18-5 | 40%~70%                   |



## TDS-Technical Data Sheet

### ----Polycarboxylate Superplasticizer

|                                                     |   |         |
|-----------------------------------------------------|---|---------|
| Sodium acrylate copolymer<br>of polyethylene glycol | - | 30%~60% |
|-----------------------------------------------------|---|---------|

#### Physicochemical property:

| Items               | Specification                              |
|---------------------|--------------------------------------------|
| Form                | Viscous liquid                             |
| Color               | Semitransparent, colorless to light yellow |
| pH                  | 6.0~8.0                                    |
| Density             | 1.05~1.20g/cm <sup>3</sup>                 |
| Solubility in water | Soluble                                    |

#### Features:

- No.1** The dosage of it is suggested as follows (wt.% of cement): 0.25%-0.8%.
- No.2** It can be mixed in metric water or added in concrete mixer. The recommended stirring time is 150s at least. Concrete mixing test should be made before using in order to insure concrete quality.
- No.3** It can be compounded together retarder, defoamer, air-entertraing reagent, lignin sulfonic natrium and so on.
- No.4** product is sold as concentrated product. It is not suggested to



## TDS-Technical Data Sheet

### ---- Polycarboxylate Superplasticizer

use this products directly in concrete or other materials without formulation blending. The compatibility of products to particular cement, aggregate and the other raw materials in the application is not guaranteed. It should be obtained through trial mixes and formulation technologies by the users.

#### SHVC and ROHS test results:

| Test Items      | Test results          |
|-----------------|-----------------------|
| Lead            | < 0.1%                |
| Cadmium         | < 0.01%               |
| Mercury         | < 0.1%                |
| Chromium VI     | < 0.1%                |
| PBB             | < 0.1%                |
| PBDEs           | < 0.1%                |
| SVHCs 161 items | < 0.1% each substance |

#### Precautions for handling:

Ensure good ventilation/exhaustion at the workplace.

Wash thoroughly after handling.



## **TDS-Technical Data Sheet**

**----Polycarboxylate Superplasticizer**

Do not eat, drink or smoke when using this product.

Use respiratory protective device against the effects of dust/fume/aerosol.

**More safe handling please refer to SDS section 4, section 6, section 7 and section 8.**

### **Storage condition:**

Store the product in a cool, dry and well-ventilation condition.

Keep away from flammable substance and acid.

### **Disposal consideration:**

Small quantities can be disposed together with household garbage.

Dispose large quantity of contents/container in according to the local/regional/national/ international regulation.

### **Transport information:**

This product is not regulated as a hazardous material or dangerous goods for transportation.

**Use TDS with SDS, more information please read SDS of this product**