

RODAS MAGIC

Surface Preparation:

New Concrete:

1. Surface must be clean, structurally sound, and free from all contaminants including curing compounds, form release agent, dust, dirt, oil, old coatings and paint.
2. New concrete and masonry surfaces should be cured for at least 28 days. Provide an absorptive surface on all substrates including smooth precast or formed concrete.
3. The moisture content of the concrete should be below 4% by weight. • All laitance must be removed prior to the next step in surface preparation. • Remove form marks and other protrusions.
4. Ensure that the surface is fully dry prior to the application of corresponding primer and subsequent coating.

Old Concrete:

5. Old concrete should be clean and in good condition. Cracks, holes and other irregularities should be filled in.
6. All blistered, cracks and peeled-off paints should be removed either by grit blasting, mechanical sanding or paint stripper.
7. Penetrated paint must be cleaned and treated with ammonia solution.
8. Glossy finish coat must be sanded.
9. Oils and greases are best removed by steam cleaning in conjunction with a detergent solution. Thorough scrubbing with hot caustic solutions will also remove mineral oils and greases.

General Description:

MAGIC is a water based and transpiring decorative paint with particular and fascinating bicolour effect. Easy application and wide range of colours helps to redecorate internal walls of houses, villas, shops, flats into sophisticated and exceptional scenery of renaissance palaces. This product is created to give new decorative solutions for interiors in order to make your environment unique for their refine elegance. Major Uses:

Best applied for interior masonry walls, gypsum, concrete and mineral surfaces

General Characteristics and Physical Properties:

Appearance	As per catalogue
Specific Weight	1.00 kg. / lit.
Dilution	Ready to use (you can add 5% if needed)
Coverage	2 5-6 m ² /liter
Drying Time	0 3-4 hrs. at 20C
Application temperature	0 0 5c - 30c
Resistance	Good resistance for abrasion once hardened
Washability	Good after hardened using water and normal detergent
Stability	Approximately one (1) year min. into the packaging.
voc	40 g/L