

RODAS LINOLISA

General Description:

RODAS LINOLISA is a water based and transpiring decorative paint with particular and beautiful stained, antique and classic effect. Easy application and wide range of colors helps to redecorate houses, villas, shops, flats into sophisticated and exceptional scenery of renaissance palaces. This product is created to give new decorative solutions for interiors in order to make your environment unique for them refine elegance.

Major Uses:

Best applied for interior and exterior **RODAS LINOLISA** walls, gypsum, concrete and mineral surfaces

General Characteristics and Physical Properties:

Appearance	As per catalogue
Specific Weight	1.00 kg. / lit.
Dilution	Ready to use (you can add 5% if needed)
Coverage	5 - 6 m ² /liter
Drying Time	3 - 4 hrs. at 20 ⁰ C
Application Temperature	5 ⁰ C - 30 ⁰ C
Resistance	Good resistance for abrasion once hardened
Wash ability	Good after hardened using water and normal detergent
Stability	Approximately one (1) year min. into the packaging.
VOC	40 g/L

Surface Preparation:

New Concrete:

- Surface must be clean, structurally sound, and free from all contaminants including curing compounds, form release agent, dust, dirt, oil, old coatings and paint.
- New concrete and **RODAS LINOLISA** surfaces should be cured for at least 28 days. Provide an absorptive surface on all substrates including smooth precast or formed concrete.
- The moisture content of the concrete should be below 4% by weight.
- All laitance must be removed prior to the next step in surface preparation.
- Remove form marks and other protrusions.
- Ensure that the surface is fully dry prior to the application of corresponding primer and subsequent coating.

Old Concrete:

- Old concrete should be clean and in good condition. Cracks, holes and other irregularities should be filled in.
- All blistered, cracks and peeled-off paints should be removed either by grit blasting, mechanical sanding or paint stripper.
- Penetrated paint must be cleaned and treated with ammonia solution.
- Glossy finish coat must be sanded.
- Oils and greases are best removed by steam cleaning in conjunction with a detergent solution. Thorough scrubbing with hot caustic solutions will also remove mineral oils and greases.

Old Wood, Old Iron:

- Previously painted with alkyds and P.U. paints.
- Remove grease from the surface and sand well.
- Smoothen with 280 – 300 grit sand paper to facilitate the adhesion of subsequent primer.

New Iron:

- Smoothen the surface with sandpaper.
- Remove traces of oil, grease and other contaminants and apply one (1) coat of Standard Deruster.
- Apply one (1) coat of anti corrosive primer to protect the surface from rust.

Application Procedure:

Please ensure that the surface is properly prepared with the application of **RODAS LINOLISA** AR Primer as an impregnating sealer to protect the concrete from efflorescence, **RODAS** PVA Wall Filler (if necessary to even up surface irregularities.) and **RODAS LINOLISA** (as specified) as an intermediate coat prior to the application of **RODAS LINOLISA**. It is imperative to ensure that the surface to be coated should be free from other contaminants, oil, grease and concrete laitance.

Classic Effect:

Spatula

Ensure that the surface is fully dry, clean and free from any contaminants. Apply **RODAS LINOLISA** (specified color) using the special brush and keep it dry.

Apply **RODAS LINOLISA** with stainless steel trowel, using uneven stroke between 15 – 30 cm. long in all directions, leaving a thin and irregular layer of the product on the surface. After 5-6 hours, apply the second coat, using the same method as for the first coat. Wait for approximately 1 hour and smoothen the coated surface with the same trowel horizontally and vertically

for about 15-20 cm. long in all directions with small amount of pressure to achieve a crushed and small particle thus creating a classical chromatic effect.

Brush + Spatula

This classic effect can also be achieved by applying **RODAS LINOLISA** with a suitable brush in all directions for about 8-12 cm. long, moving from right to left and vice versa, and from bottom to top and vice versa, leaving a thin layer of the product, which is more or less uneven. Let it dry for 20 minutes, smoothen the coated surface with stainless steel trowel, moving in all directions. After 5-6 hours, apply the second coat of **RODAS LINOLISA** with the brush, with the same method as the first coat.

Note: When the product is applied for outdoors, please ensure that the coating is fully dry prior to the application **RODAS** Protect as a protective coating.

Packaging:

Normally 4 kg, and 20 kg in plastic bucket are available upon request.

Colors Availability:

- **RODAS LINOLISA**
- Toner Pearl
- **RODAS LINOLISA** (premix)

Physiological Hazards:

RODAS LINOLISA is water-based paint, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. **RODAS LINOLISA** is harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advice.