

RODAS

MICROCEM

General Description:

RODAS MICROCEM is a high quality two component multipurpose Decorative and resurfacing material based on a special binder and Natural limestone to decorate the floors and walls. It is recommended for Interior and exterior but it is most useful in redecorating interior floor/walls With a choice of different colors.

Major Uses:

RODAS MICROCEM can be applied on well prepared substrates such as wall and floors. It adheres firmly to concrete, overlays, tile, ceramics and other cementitious surface.

MIXING AND APPLICATION METHOD

BASECOAT

RODAS MICROCEM BASE should be mixed with a forced action mechanical mixer Or by heavy duty drill fitted purpose made paddle.

Mix **RODAS MICROCEM** Base B with desired color into the mixing vassal and slowly add **RODAS MICROCEM** Base A in accordance with the required mixing until a Smooth consistency is obtained.

Mix for a minimum of three minutes.

If the mixture is to dense, add water until you reach the Desired consistency



RODAS MICROCEM may be applied by stainless steel trowel at rate of approximately 1.5m/kg

Scrape over the layered material to remove any small lumps
Or trowel lines. pay attention at the corners to avoid uneven finish.

Leave the first layer until dry to touch for about an hour depending on the temperature on the working place.

Repeat the process progressively over the wall, occasionally passed the area already coated to achieve the required design and effect.

Keep on trowelling the surface with cleaned stainless steel trowel for about 15-20 minute until the surface is smooth
15-20 minute until the surface is smooth

TOPCOAT

Top well dry Basecoat, sand the surface with 220 grit sand paper. remove all laitance and dust by vacuum cleaner prior to the application of **RODAS MICRCCEM TOPCOAT**

Repeat the same procedure as the Basecoat.
Apply the topcoat at a rate of 4m² /kg

Leave the surface to dry for about 2days before application of subsequent coating

