

RODAS PALMYRA

General Description:

RODAS PALMYRA is a special coating for interiors with aesthetic effect of metal texture. It is realized with new technologies which creates a surfaces characterized by unique feel that gives a new decorative solution to make your environment an ambiance of sophistication and elegance.

Advantages:

- For interior use.
- Good adhesion properties.
- Ease of application.
- Environment friendly.

Characteristics and Physical Properties:

Color	As per catalogue
Specific Gravity	1.0 +/- 0.1 kg./ lit.
Viscosity	20 poise @ 25 ⁰ C
Coverage	13 m ² / lit.
Shelf Life	12 months
Flash Point	65 ⁰ C
Application	By brush or sponge
Dilution	5% water max. if required
VOC	75 g/L

Surface Preparation:

New Substrates:

- New concrete should be cured at least 28 days.
- Substrate must be free from any form of contaminants.
- Apply 1 coat of RODAS Masonry AR Primer as impregnating sealer.
- Level the surface with RODAS PVA Wall filler and sand until smooth.

Apply 1 – 2 coats of RODASCRYL as an intermediate coat (optional). Apply 1 coat of RODAS PALMYRA in non-uniform manner and rotational movements.

Old Concrete (previously painted)

- Remove all blistered, cracked and peeled off paint from the surface.
- Penetrated paint must be cleared and treated with 3% ammonia and water.
- Glossy finish coat must be sanded.
- Apply 1 coat of RODAS Masonry AR Primer as impregnating sealer; apply 1 – 2 coats of RODASCRYL (desired color)
- Apply 1 coat of RODAS PALMYRA in a specified application technique.

Typical Recommended System:

RODAS Masonry AR Primer	- 1 coat.
RODAS Masonry Primer (optional)	- 1 coat.
PVA Wall Filler (optional)	- 2 coats.
RODASCRYL (Intermediate coat)	- 1 coat.
RODAS PALMYRA	- 1 coat.

Storage:

The product must be stored in accordance with national regulations. The product should be kept in a cool and well ventilated place, protected from heat and direct sunlight. Containers must be kept tightly closed.

Cleaning of Tools:

All tools should be cleaned with water.

Packing:

Available in ½ kg., 1 kg. and 5kg.

Precautions:



See safety indication sh