

Summary report

Wellbore: 15/9-F-15 C

Period: 2013-11-01 00:00 - 2013-11-02 00:00

Status:	normal
Report creation time:	2018-05-03 13:52
Report number:	74
Days Ahead/Behind (+/-):	
Operator:	Statoil
Rig Name:	MÆRSK INSPIRER
Drilling contractor:	Maersk Drilling
Spud Date:	2009-01-19 00:00
Wellbore type:	
Elevation RKB-MSL (m):	54.9
Water depth MSL (m):	91
Tight well:	Y
HPHT:	Y
Temperature (I):	
Pressure (I):	
Date Well Complete:	2009-02-14

Dist Drilled (m):	-999.99
Penetration rate (m/h):	-999.99
Hole Dia (I):	
Pressure Test Type:	formation integrity test
Formation strength (I):	
Dia Last Casing (I):	

Depth at Kick Off mMD:	
Depth at Kick Off mTVD:	
Depth mMd:	2637
Depth mTVD:	
Plug Back Depth mMD:	
Depth at formation strength mMD:	
Depth At Formation Strength mTVD:	
Depth At Last Casing mMD:	2914.8
Depth At Last Casing mTVD:	

Summary of activities (24 Hours)

Waited on weather to run HPDR.

Summary of planned activities (24 Hours)

Wait on weather to run HPDR.
Run HPDR and land same.
Lock Tie Back Connector.
Install tensioner system.

Operations

Start time	End time	End Depth mMD	Main - Sub Activity	State	Remark
00:00	07:00	0	interruption -- waiting on weather	ok	Waited on weather to run HPDR. Meanwhile: Installed hatches on well head deck. Performed planned maintenance and general housekeeping.
07:00	19:00	0	interruption -- waiting on weather	ok	Waited on weather to run HPDR. Meanwhile: Performed planned maintenance and general housekeeping.
19:00	00:00	0	interruption -- waiting on weather	ok	Waited on weather to run HPDR. Meanwhile: Removed well head deck hatches from well F-10 and F-15. Performed planned maintenance and general housekeeping.

Drilling Fluid

Sample Time	10:00	22:00
Sample Point	Reserve pit	Active pit
Sample Depth mMD	0	0
Fluid Type	Enviromul Yellow	Enviromul Yellow
Fluid Density (g/cm3)	1.21	1.21
Funnel Visc (s)	-999.99	-999.99
Mf (I)		
Pm (I)		
Pm filtrate (I)		
Chloride (I)		
Calcium (I)		
Magnesium (I)		
Ph		
Excess Lime (I)		
Solids		
Sand (I)		
Water (I)		
Oil (I)		
Solids (I)		
Corrected solids (I)		
High gravity solids (I)		
Low gravity solids (I)		
Viscometer tests		
Plastic visc. (mPa.s)	30	33
Yield point (Pa)	8.5	8
Filtration tests		
Pm filtrate (I)		
Filtrate Lthp (I)		
Filtrate Hthp (I)		
Cake thickn API (I)		
Cake thickn HPHT (I)		
Test Temp HPHT (degC)	120	120

Comment		
---------	--	--