

# site-analysis: A Python package for site-projection analysis of molecular dynamics trajectories

Benjamin J. Morgan <sup>1,2</sup>

<sup>1</sup> Department of Chemistry, University of Bath, Claverton Down, Bath, BA2 7AY, United Kingdom  
<sup>2</sup> The Faraday Institution, Quad One, Harwell Science and Innovation Campus, Didcot, OX11 0RA, United Kingdom

DOI: [10.xxxxxx/draft](https://doi.org/10.xxxxxx/draft)

## Software

- [Review](#) 
- [Repository](#) 
- [Archive](#) 

Editor: [Open Journals](#) 

## Reviewers:

- [@openjournals](#)

Submitted: 01 January 1970

Published: unpublished

## License

Authors of papers retain copyright and release the work under a Creative Commons Attribution 4.0 International License ([CC BY 4.0](#)).

## Summary

Understanding ionic transport in crystalline solids is important for developing materials for batteries, fuel cells, and other electrochemical devices. Molecular dynamics (MD) simulations provide complete information about the microscopic dynamics of mobile ions, but extracting mechanistic insights from these complex data can be challenging. In crystalline solids, ionic diffusion can often be considered to be effected by discrete jumps between “sites”—persistent local minima on the potential energy surface. `site-analysis` is a Python package that processes MD trajectories to produce discrete time-resolved site-occupation data that provide a coarse-grained description of ion transport behaviour. The package implements four site-definition methods—spherical, polyhedral, Voronoi, and dynamic Voronoi—allowing users to choose the approach best suited to their requirements. For polyhedral and dynamic Voronoi sites `site-analysis` implements a reference-based workflow that automates site generation from coordination environment specifications, allowing users to analyse trajectories using these site types without manually defining site geometries. `site-analysis` integrates with existing computational materials science workflows through the `pymatgen` ecosystem and provides both atom-centric and site-centric representations of ion dynamics as simple Python data structures.

## Statement of need

Molecular dynamics simulations are widely used to study ionic transport in battery materials, solid electrolytes, and ceramic ion conductors ([Landgraf et al., 2024](#); [Mercadier et al., 2023](#); [Morgan, 2021](#); [Poletayev et al., 2022](#)). While these simulations, in principle, provide complete descriptions of atomic-scale dynamics, extracting mechanistic insights from these data often presents significant challenges. In crystalline solids, ionic transport is often well described as occurring through a series of discrete “jumps” between crystallographic sites—persistent local minima on the potential energy surface where mobile ions reside between diffusive events. This site-hopping model provides a framework for understanding and quantifying transport mechanisms by separating motion between sites from non-diffusive motion within sites. To extract a site-projected description of ion dynamics from MD data, we need methods that can transform continuous ion trajectories into discrete time-resolved sequences of site occupations. This coarse-graining process filters out vibrational motion and reveals the events that contribute to macroscopic transport, enabling identification of rate-limiting steps, preferred pathways, and correlated ion movements.

Implementing site-projection analysis requires defining spatial regions (sites) and assigning mobile ions to these sites at each timestep. Once site positions are known—whether from crystallographic knowledge or data-driven methods ([Chen et al., 2017](#); [Kahle et al., 2019](#); [López et al., 2024a](#))—various geometric definitions can be applied; for example, spherical regions with distance cutoffs ([Klerk et al., 2016](#); [Klerk & Wagemaker, 2016](#)), space-filling Voronoi

tessellations (Clarke et al., 2021; Krenzer et al., 2023; Richards et al., 2016; Sicolo et al., 2018), or coordination polyhedra (Burbano et al., 2016; Kozinsky et al., 2016; Morgan, 2021; Zhang et al., 2019; Zou et al., 2021). Each approach involves implementation challenges and parameter choices that can affect the resulting analysis. Without accessible tools, researchers must develop custom code for their specific systems—a significant barrier particularly when using complex site definitions that account for dynamical distortions of the host framework structure or non-spherical site geometries.

site-analysis provides a Python framework that implements multiple site-definition methods within a consistent interface. For each analysis timestep in an MD trajectory, the package determines which site (if any) each mobile ion occupies. This information can be accessed in two ways: atom trajectories, which record the sequence of sites visited by each ion (e.g., ion 1 visits sites [0, 0, 1, 1, 2, ...]), and site trajectories, which record which ions occupied each site over time. These outputs are represented using simple Python lists, which allows easy downstream analysis to compute, for example, site-occupation probabilities, site-site transition frequencies, and quantification of correlated ion movements.

The package provides four site-definition methods—spherical, polyhedral, Voronoi, and dynamic Voronoi:

- **Spherical sites** are conceptually simple and widely used in the literature.
- **Voronoi sites** partition space based on proximity to site centres, ensuring complete spatial coverage—every point in space belongs to exactly one site.
- **Dynamic Voronoi sites** use Voronoi partitioning to assign atoms to sites, but use Voronoi centres that are dynamically calculated each frame according to the instantaneous positions of coordinating host-framework atoms; this accounts for thermal distortions and host framework dynamics whilst maintaining spatial partitioning.
- **Polyhedral sites** define sites as coordination polyhedra formed by host-framework atoms, directly reflecting local coordination environments. Like dynamic Voronoi sites, polyhedral sites update their geometry based on the instantaneous positions of the vertex host-framework atoms.

To assist with analyses using dynamic Voronoi and polyhedral sites, the package provides a reference-based workflow that automates site generation: users provide an ideal reference structure and specify coordination criteria (e.g., “Li ions coordinated by 4 O atoms”), and the software identifies all matching environments and maps them to target structures. This automated approach allows analyses using these dynamic sites without requiring the user to pre-identify all relevant coordination environments.

The package uses a builder pattern interface that provides method chaining for configuration and ensures parameter validation. Analyses can be set up and executed with a few lines of code, with results returned as Python lists that integrate simply into downstream analysis workflows. The software natively supports VASP XDATCAR files and integrates with the pymatgen ecosystem.

The materials modelling community has developed various tools for site-based trajectory analysis, including pymatgen-analysis-diffusion (Deng et al., 2016; *Pymatgen-Analysis-Diffusion*, n.d.), SITATOR (Kahle et al., 2019; *Sitator*, n.d.), IonDiff (López et al., 2024b), and gemdat (Azizi et al., n.d.). These packages each implement specific schemes for defining sites and assigning occupations, and are often tightly integrated with downstream workflows for particular analysis tasks. site-analysis complements these tools by focusing on generality: it provides multiple site-definition methods within a consistent interface and produces output using simple data structures that can feed into any downstream analysis. To our knowledge, site-analysis is unique in implementing geometric sites that dynamically update during the simulation (polyhedral sites and dynamic Voronoi sites) in a publicly available package. We note that the use of dynamic polyhedral sites is particularly valuable for materials with close-packed host-framework structures, where mobile ion coordination environments provide a natural and intuitive basis for describing transport mechanisms (Burbano et al., 2016; Mercadier et al.,

95 2023; Morgan, 2021).

96 By transforming continuous MD trajectories into discrete site-occupation sequences, site-  
 97 analysis enables researchers to apply site-projection coarse-graining to characterise and  
 98 quantify mechanisms of ion transport in solid electrolytes. The software provides both atom-  
 99 centric views (tracking which sites each ion visits) and site-centric views (recording which ions  
 100 occupy each site over time), supporting different analytical perspectives on the same transport  
 101 processes. This dual representation, combined with multiple site-definition methods including  
 102 dynamically-updating geometric sites, provides a flexible toolkit for analysing ionic transport  
 103 mechanisms across diverse materials.

104 The software has been used to analyse ion-transport mechanisms in lithium-ion and fluoride-ion  
 105 solid electrolytes (Hu et al., 2025; Krenzer et al., 2023; Mercadier et al., 2023; Morgan, 2021).  
 106 The package reproduces functionality from an earlier Fortran code that used dynamically  
 107 defined coordination polyhedra to study ion-transport and defect distributions (Burbano et  
 108 al., 2016; Morgan & Madden, 2011, 2012, 2014b, 2014a), which was itself motivated by  
 109 earlier studies using projections onto tetrahedral sites (Castiglione et al., 1999; Castiglione  
 110 & Madden, 2001; Marrocchelli et al., 2009). Documentation and tutorials are available at  
 111 <https://site-analysis.readthedocs.io>.

## 112 Acknowledgements

113 B.J.M. acknowledges support from the Royal Society (UF130329 and URF/R/191006) and  
 114 the Faraday Institution (FIRG016).

115 Azizi, V., Smeets, S., Lavrinenko, A. K., Ciarella, S., Famprikis, T., Landgraf, V., & Vasileiadis,  
 116 A. (n.d.). GEMDAT (Version 1.6.2). <https://github.com/GEMDAT-repos/GEMDAT>

117 Burbano, M., Carlier, D., Boucher, F., Morgan, B. J., & Salanne, M. (2016). Sparse cyclic  
 118 excitations explain the low ionic conductivity of stoichiometric  $\text{Li}_7\text{La}_3\text{Zr}_2\text{O}_{12}$ . *Physical*  
 119 *Review Letters*, 116, 135901. <https://doi.org/10.1103/PhysRevLett.116.135901>

120 Castiglione, M. J., & Madden, P. A. (2001). Fluoride ion disorder and clustering in superi-  
 121 onic  $\text{PbF}_2$ . *Journal of Physics: Condensed Matter*, 13, 9963. <https://doi.org/10.1088/0953-8984/13/44/311>

123 Castiglione, M. J., Wilson, M., & Madden, P. A. (1999). Polarization effects in the simulation  
 124 of lead (ii) fluoride. *Journal of Physics: Condensed Matter*, 11, 9009–9024. <https://doi.org/10.1088/0953-8984/11/46/303>

126 Chen, C., Lu, Z., & Ciucci, F. (2017). Data mining of molecular dynamics data reveals Li  
 127 diffusion characteristics in garnet  $\text{Li}_7\text{La}_3\text{Zr}_2\text{O}_{12}$ . *Sci. Rep.*, 7(1). <https://doi.org/10.1038/srep40769>

129 Clarke, M. J., Dawson, J. A., Mays, T. J., & Islam, M. S. (2021). Atomistic insights  
 130 into the effects of doping and vacancy clustering on Li-ion conduction in the  $\text{Li}_3\text{OCl}$   
 131 antiperovskite solid electrolyte. *ACS Appl. Energy Mater.*, 4(5), 5094–5100. <https://doi.org/10.1021/acsaem.1c00656>

133 Deng, Z., Zhu, Z., Chu, I.-H., & Ong, S. P. (2016). Data-driven first-principles methods  
 134 for the study and design of alkali superionic conductors. *Chem. Mater.*, 29(1), 281–288.  
 135 <https://doi.org/10.1021/acs.chemmater.6b02648>

136 Hu, J., Squires, A. G., Kondek, J., Johnson, M. J., Youd, A. B., Vadhva, P., Paul, P. P.,  
 137 Withers, P. J., Di Michiel, M., Keeble, D. S., Hansen, M. R., Scanlon, D. O., & Rettie,  
 138 A. J. E. (2025). Enabling ionic transport in  $\text{Li}_3\text{AlP}_2$ : The roles of defects and disorder.  
 139 *Journal of Materials Chemistry A*, 13, 6427–6439. <https://doi.org/10.1039/D4TA04347B>

140 Kahle, L., Musaelian, A., Marzari, N., & Kozinsky, B. (2019). Unsupervised landmark  
 141 analysis for jump detection in molecular dynamics simulations. *Phys. Rev. Mater.*, 3(5).

- 142 <https://doi.org/10.1103/physrevmaterials.3.055404>
- 143 Klerk, N. J. J. de, Rosłoń, I., & Wagemaker, M. (2016). Diffusion mechanism of Li argyrodite  
144 solid electrolytes for Li-ion batteries and prediction of optimized halogen doping: The  
145 effect of Li vacancies, halogens, and halogen disorder. *Chem. Mater.*, 28(21), 7955–7963.  
146 <https://doi.org/10.1021/acs.chemmater.6b03630>
- 147 Klerk, N. J. J. de, & Wagemaker, M. (2016). Diffusion mechanism of the sodium-ion solid  
148 electrolyte Na<sub>3</sub>PS<sub>4</sub> and potential improvements of halogen doping. *Chem. Mater.*, 28(9),  
149 3122–3130. <https://doi.org/10.1021/acs.chemmater.6b00698>
- 150 Kozinsky, B., Akhade, S. A., Hirel, P., Hashibon, A., Elsässer, C., Mehta, P., Logeat, A., &  
151 Eisele, U. (2016). Effects of sublattice symmetry and frustration on ionic transport in  
152 garnet solid electrolytes. *Phys. Rev. Lett.*, 116(5), 055901. <https://doi.org/10.1103/physrevlett.116.055901>
- 154 Krenzer, G., Klarbring, J., Tolborg, K., Rossignol, H., McCluskey, A. R., Morgan, B. J., &  
155 Walsh, A. (2023). Nature of the superionic phase transition of lithium nitride from machine  
156 learning force fields. *Chemistry of Materials*, 35, 6133–6140. <https://doi.org/10.1021/acs.chemmater.3c00874>
- 158 Landgraf, V., Tu, M., Zhao, W., Lavrinenko, A., Cheng, Z., Canals, J., Leeuw, J. de,  
159 Ganapathy, S., Vasileiadis, A., Wagemaker, M., & Famprikis, T. (2024). Disorder-mediated  
160 ionic conductivity in irreducible solid electrolytes. *ChemRxiv*. <https://doi.org/10.26434/chemrxiv-2023-33r87-v2>
- 162 López, C., Rurali, R., & Cazorla, C. (2024a). How concerted are ionic hops in inorganic  
163 solid-state electrolytes? *J. Am. Chem. Soc.*, 146(12), 8269–8279. <https://doi.org/10.1021/jacs.3c13279>
- 165 López, C., Rurali, R., & Cazorla, C. (2024b). IonDiff: Command-Line tool to identify ionic  
166 diffusion events and hopping correlations in molecular dynamics simulations. *J. Open  
167 Source Softw.*, 9(99), 6616. <https://doi.org/10.21105/joss.06616>
- 168 Marrocchelli, D., Madden, P. A., Norberg, S. T., & Hull, S. (2009). Cation composition effects  
169 on oxide conductivity in the Zr<sub>2</sub>Y<sub>2</sub>O<sub>7</sub>–Y<sub>3</sub>NbO<sub>7</sub> system. *Journal of Physics: Condensed  
170 Matter*, 21, 405403. <https://doi.org/10.1088/0953-8984/21/40/405403>
- 171 Mercadier, B., Coles, S. W., Duttine, M., Legein, C., Body, M., Borkiewicz, O. J., Lebedev,  
172 O., Morgan, B. J., Masquelier, C., & Dambournet, D. (2023). Dynamic lone pairs and  
173 fluoride-ion disorder in cubic-BaSnF<sub>4</sub>. *Journal of the American Chemical Society*, 145,  
174 17700–17714. <https://doi.org/10.1021/jacs.3c08232>
- 175 Morgan, B. J. (2021). Mechanistic origin of superionic lithium diffusion in anion-disordered  
176 Li<sub>6</sub>PS<sub>5</sub>X argyrodites. *Chemistry of Materials*, 33, 2004–2018. <https://doi.org/10.1021/acs.chemmater.0c03738>
- 178 Morgan, B. J., & Madden, P. A. (2011). Effects of lattice polarity on interfacial space charges  
179 and defect disorder in ionically conducting AgI heterostructures. *Physical Review Letters*,  
180 107, 206102. <https://doi.org/10.1103/PhysRevLett.107.206102>
- 181 Morgan, B. J., & Madden, P. A. (2012). Absence of a space-charge-derived enhancement of  
182 ionic conductivity in β/γ-heterostructured 7H- and 9R-AgI. *Journal of Physics: Condensed  
183 Matter*, 24, 275303. <https://doi.org/10.1088/0953-8984/24/27/275303>
- 184 Morgan, B. J., & Madden, P. A. (2014a). Molecular dynamics simulation of ionic transport  
185 at coherent interfaces in fluorite heterostructures. *Physical Review B*, 89, 054304. <https://doi.org/10.1103/PhysRevB.89.054304>
- 187 Morgan, B. J., & Madden, P. A. (2014b). Relationships between atomic diffusion mechanisms  
188 and ensemble transport coefficients in crystalline polymorphs. *Physical Review Letters*,  
189 112, 145901. <https://doi.org/10.1103/PhysRevLett.112.145901>

- 190 Poletayev, A. D., Dawson, J. A., Islam, M. S., & Lindenberg, A. M. (2022). Defect-driven  
191 anomalous transport in fast-ion conducting solid electrolytes. *Nature Materials*, 21(9),  
192 1066–1073. <https://doi.org/10.1038/s41563-022-01316-z>
- 193 *Pymatgen-analysis-diffusion*. (n.d.). <https://github.com/materialsvirtuallab/pymatgen-analysis-diffusion>
- 194 Richards, W. D., Tsujimura, T., Miara, L. J., Wang, Y., Kim, J. C., Ong, S. P., Uechi,  
195 I., Suzuki, N., & Ceder, G. (2016). Design and synthesis of the superionic conductor  
196  $\text{Na}_{10}\text{SnP}_2\text{S}_{12}$ . *Nat. Commun.*, 7(1). <https://doi.org/10.1038/ncomms11009>
- 197 Sicolo, S., Kalcher, C., Sedlmaier, S. J., Janek, J., & Albe, K. (2018). Diffusion mechanism in  
198 the superionic conductor  $\text{Li}_4\text{PS}_4\text{I}$  studied by first-principles calculations. *Solid State Ionics*,  
199 319, 83–91. <https://doi.org/10.1016/j.ssi.2018.01.046>
- 200 *Sitator*. (n.d.). <https://github.com/Linux-cpp-lisp/sitator>
- 201 Zhang, Z., Zou, Z., Kaup, K., Xiao, R., Shi, S., Avdeev, M., Hu, Y., Wang, D., He, B., Li,  
202 H., Huang, X., Nazar, L. F., & Chen, L. (2019). Correlated migration invokes higher  
203  $\text{Na}^+$ -ion conductivity in NaSiCON-type solid electrolytes. *Adv. Energy Mater.*, 9(42).  
204 <https://doi.org/10.1002/aenm.201902373>
- 205 Zou, Z., Ma, N., Wang, A., Ran, Y., Song, T., He, B., Ye, A., Mi, P., Zhang, L., Zhou, H.,  
206 Jiao, Y., Liu, J., Wang, D., Li, Y., Avdeev, M., & Shi, S. (2021). Identifying migration  
207 channels and bottlenecks in monoclinic NASICON-type solid electrolytes with hierarchical  
208 ion-transport algorithms. *Adv. Funct. Mater.*, 31(49). <https://doi.org/10.1002/adfm.202107747>  
209