

CERALASTIC

2K, ELASTOMERIC CEMENTITIOUS WATERPROOF COATING

CERALASTIC is a 2k, cementitious, flexible waterproofing material based on special synthetic resin dispersion and a blend of selected cement mixed with well-graded aggregates and high performance acrylic co-polymers.

ADVANTAGES

- Excellent resistance to water
- Resistance to freezing and thawing
- Non-toxic, suitable for potable water tanks applications
- Protects the concrete from water, carbonation and deionizing salts
- Enhances bridging effect against post construction hairline cracks
- Excellent adhesion to porous and non-porous concrete surface/masonry etc.,
- Ideal waterproofing system for new buildings as well as repair of old structures
- Considerable flexibility and elongation help accommodate linear thermal expansion of surface

FUNCTIONS

CERALASTIC is a proven and fool-proof waterproofing system wherein the ingress of moisture into the structural member is prevented by a flexible membrane formed as a result of resin modified cement hydration and polymer film formation. The highly elastic nature of the membranes takes care of the stresses set up by temperature and resists crack formation. The high content of the dispersed synthetic resin particles results in unheard-of high flexibility for a cement based material and the ability to bridge hairline cracks up to 0.3 mm.

USAGES

- Can be used as waterproof coating and protection for balconies & terraces
- Can be used as waterproofing for new and old buildings (internal & external)
- Can be used for waterproofing tanks, containers, swimming pools, basements, bathrooms, roofs, etc.,

METHOD OF USE

Surface Preparation:

The surface must be clean, sound and free of dust, loose particles, cement laitance, grease, rust and

other contaminants. Insufficiently covered reinforcement has to be treated with a corrosion protectant **CERA ZINC-ZR**. Rough areas and honeycombs must be levelled with **CERA POLY MORTAR** or polymer-modified mortar mixed with **CERA LATEX SBR**. Absorbent surfaces (concrete, renderings, plaster) have to be pre-wetted with clean water. During application, the surface has to be moist but free of puddles. A minimum temperature of +5°C is essential.

Mixing:

The liquid component A and clean water in the proportion of 1 : 1 by volume are to be poured into the bucket. The powder component B is to be added to it slowly and stirred well to obtain a smooth, lump-free, consistent slurry. For ready to use packings, the addition of water is not required. For better dispersion of polymers and large applications, mechanical stirrers may be used. Mix only in small batches of one unit at a time, which can be used within the pot life. Mixing of the two components results in a plastic, thixotropic and easily applicable compound, even to vertical surfaces.

Application:

Apply the well-mixed **CERALASTIC** slurry with a brush or broom onto the prepared surface in minimum of two layers. If used on smooth screed floors, the application can also be done by notched trowel. Do not apply more than 1.5 mm per coat. The second coat can be applied as soon as the preceding coat is dry after approx. 8- 10 hours, but it is recommended to wait overnight. Ceralastic can be sprayed also by using a suitable nozzle. The total thickness of 2 coats of **CERALASTIC** would be 800 microns-1 mm.

The tools should be cleaned with water before **CERALASTIC** hardens because the cured material is very hard to remove even by machine.

Curing:

High water resistance is assured if **CERALASTIC** does not dry too quickly, therefore it should be protected after application against heavy wind and intense sunshine.

Hardening Time:

Curing and hardening depend on the temperature. **CERALASTIC** coated surface becomes dry in

3 – 4 hrs. The area can be recoated after 8 hours.

PROPERTIES

Component A	Milky White liquid
Component B	White/Grey powder
Mixing proportion by weight	1 part of Component A : 1 part water : 5 part powder component B
Toxicity	Non-Toxic
Resistance to Ultra violet rays	Good
Chloride content	Nil
Bond strength (ASTM D 4541/95)	1.2 N/mm ²
Tensile strength (ASTM D 638)	0.4 N/mm ² / @ 1day
Elongation % ASTM D 412	40
Dry material solids % mass	55 ± 5
pH	7.5
Abrasion resistant's (ASTM D 4060, CS17 wheel)	22 mg/ 1000 cycles
Relative density	1.086
Water permeability Control DIN 1048	14.7 Avg
Concrete with ceralastic DIN 1048	4.6 Avg
Water absorption % Control	4
Concrete with ceralastic	1.4
Pot life	30 minutes @ 30°C

COVERAGE

Approx. 1.25 Sqm/kg/coat.

Approx. 0.625 Sqm/kg / 2 coats.

Coverage may vary depending on surface conditions.

PACKING

CERALASTIC NORMAL:

24 Kg unit – 4 Kg Component A & 20 kg Component B.

6 Kg unit – 1 Kg Component A & 5 kg Component B.

CERALASTIC RTU (Ready to use, No mixing of water):

7 kg unit – 1 kg compound A (2 nos.), 2.5 kg Compound B (2 nos.)

3.5 kg unit – 1 kg compound A & 2.5 kg compound B.

SHELF LIFE

Keep frost-free, cool and dry. **CERALASTIC** can be

stored for 12 months in tightly closed original packing. Once frozen, compound A becomes unusable.

HEALTH & SAFETY

Avoid contact with the skin for prolonged periods. Any contact with the eye, wash immediately with plenty of water.

Please consult Cera-Chem technical cell for further details.

QUALITY CONTROL: Cera-Chem products are certified as per ISO 9001: 2015. The chemical composition and physical properties are tested as per appropriate standards.

Cera-Chem Private Limited also manufactures and markets a wide range of products including:

- Tile adhesives, Joint fillers & Dry mix mortars • Admixtures • Waterproofing solutions • Repair and Rehabilitation • Protective & Decorative Coating • Flooring Systems • Marble Renewal & Sealer Coats • Construction Aids

Whilst any information and/or specification contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendation or suggestions made by us, our Representatives, Agents or Distributors, as the conditions of use of any labour involved, site conditions are beyond our control.



CERA-CHEM PRIVATE LIMITED
SUPERIOR CONSTRUCTION CHEMICALS
AN ISO 9001 : 2015 COMPANY

No. 9, First Cross Street, Sterling Road, Nungambakkam,
Chennai-600 034
Tel: 044-48684523, 42652454, 42654525
Trade Enquiry: 98404 80307
Email: corporate@cerachemindia.com
www.cerachemindia.com

EDITION 2023