

RAPPORT DE RENFORCEMENT

CTTP Reinforcement Design Report

RN120 PK70-80 — Tiaret, Algeria — Direction des Études Techniques

Project Information

Route RN120 PK70-80
Date 27 May 2026

Input Parameters

Traffic Class

T3

Surface Type

BB

UNI

3200

Visual Status

Mauvais

Deflection Calculation

Measured deflection (d_c) 70 1/100mm
Seasonal coefficient (C_s) 1.25 (Dry)
Regional coefficient (C_r) 1.00 (North)
Temperature coefficient (C_t) 1.045 (20°C, ≥10cm bitumen)

Corrected deflection (d_corr) **91.44 1/100mm**

Deflection zone

T4 — Très Fort

Reinforcement Design

Renforcement en Béton Bitumineux (BB)

Structure: 6 cm BB (binder) + 4 cm BB (wearing course)

Base: 15 cm — Compacted to 98% MDA — Drainage layer required

Reinforcement type BS — Béton Bitumineux (épais)
Binder course 6 cm BB 0/14
Wearing course 4 cm BB 0/10
Compaction 98% MDA
Drainage Subsurface drainage required

Regulatory Traceability

Rule

CTTP Table 4 — p.28 (T3, T4)

Matrix row

T3 + T4 + BB + Mauvais → BS reinforcement