

PRODUS/ ARTICLE: SIDLUT

Textile neţesute din fibre tip poliester, impregnate PES impregnated needlepunched nonwovens

| CARACTERISTICI TEHNICE TECHNICAL CHARACTERISTICS | | UM UNITS | Valoare <i>Valu</i> e | | | Metodă de încercare | |
|--|------------------|-------------|--|------------|------------|---------------------|------------------------|
| 72071110712 07711071071271107700 | | o, ii 7 G | 200 | 300 | 500 | 750 | Test Method |
| MASA WEIGHT | | g/m² | 200+20 | 300±30 | 500+50 | 750+75 | (SR)EN 29073-1:1998 |
| LĂŢIME <i>WIDTH</i> | | cm | 150±1 | 150±1 | 150±1 | 150±1 | |
| FORȚA LA TRACȚIUNE, min TENSILE STRENGTH | long. transv. | N N | 150 200 | 200 250 | 300 400 | 400 650 | (SR)EN 20344:2004 |
| ALUNGIRE LA RUPERE, min ULTIMATE ELONGATION | long. transv. | % % | 20 35 | 18 35 | 14 22 | 25 40 | (SR)EN 29073:1998 |
| APLICATII APLICATIONS | | Indus | ustria de încălţăminte: branţ, acoperiș de branţ Footwear industry: midsole, insole | | | | |