



**DONG ER ROAD, BINHAI INDUSTRIAL ZONE, KEQIAO DISTRICT
SHAOXING CITY CHINA**

Email: sales@galaxy-film.cn

Skype: linda.bopp

TECHNICAL DATA SHEET

Standards		GB/T10003-08	Testing Environment	℃	23	Film Type	BOPP Film
				%	55	Thickness	25 MIC
N O	Inspection		Acceptance Standard			Test Standard	Test Result
			Top	First Class			
1	Width Deviation mm		0~+2.0	≤3.0		GB6673-86	0
2	Average Thickness Deviation %		±2.5	±3.5		GB6672-86	24.65
3	Tensile Strength MPa	MD	≥140	≥120		GB1040-91	156
		TD	≥260	≥200			299
4	Elongation At Break %	MD	≤180	≤180		GB1040-91	170
		TD	≤65	≤75			55
5	E Modulus（3 Day）MPa		≥1500	≥1500		GB1040-91	2900
6	Heat Shrinkage Rate %	MD	≤4	≤5		GB/T10003	2
		TD	≤2	≤4			0
7	Haze %		≤1.6	≤2.5		GB2410-08	1.04
8	Gloss %		≥90	≥85		GB8807-88	93.4
9	Electrostatic（%）	Yes	/	/		JISL1094	—
		Not	/	/			—
10	Coefficient Of Friction	Yes/Yes	≤0.8	≤0.8		GB10006-88	0.325
		Not/Not	≤0.8	≤0.8			0.306
11	Wetting Tension mN/m		≥38	≥38		GB/T 14216-08	39
12	Appearance		NO Defects	Light Defects		GB/T 10003-08	NO
Test Conclusion		Qualified					