



ZHEJIANG HAIBIN FILM TECHNOLOGY CO., LTD

DONG ER ROAD, BINHAI INDUSTRIAL ZONE, KEQIAO DISTRICT

SHAOXING CITY CHINA

Tel: 86-575-85584161

Email: sales@galaxy-film.cn

Mobile: 0086 13858466830

Skype: linda.bopp

TECHNICAL DATA SHEET

Type of Film	BOPP Film		Thickness		30 MIC	
Index	Thickness	Average (mic)	29.9		Max / Min	30.5/28.3
		Tolerance (%)	-0.3			
	Physical Properties	Tensile Strength (Mpa)	MD/TD		158/342	
		Elongation of Break (%)	MD/TD		259/57	
		Elastic Modulus (Mpa)	MD/TD			
		Thermal Shrinkage (%)	MD/TD		2.5/1.5	
		Friction Coefficient	Back	Static	0.22	
				Dynamic	0.15	
			Front	Static	0.19	
				Dynamic	0.16	
		Surface Tension (mN/m)	38			
		Heat Seal Strength (N/15mm)	inside/outside 3.3/2.7			
		Haze (%)	1.94			
		Gloss (%)	90.8			
	Appearance	No Defects				