



# ZHEJIANG HAIBIN FILM TECHNOLOGY CO., LTD

**DONG ER ROAD, BINHAI INDUSTRIAL ZONE, KEQIAO  
DISTRICT, SHAOXING CITY CHINA**

**Tel: 86-575-85584161**

**Email: sales@galaxy-film.cn**

**Mobile: 0086 13858466830**

**Skype: linda.bopp**

## TECHNICAL DATA SHEET

Description of Goods		CPP	Specification	30MIC	Testing Criteria	Q/NHBZ003-2013
Properties			Standard	Testing Result		Result of Single Item
Appearance			Regular	Meet with the standards of Q/HNDP49-2011		Qualified
1	Width tolerance		0 ~ +5	+3		Qualified
	Thickness Tolerance		±8	+3.2	-2.8	Qualified
	Thickness Tolerance on Average		±5	+1.1		Qualified
2	MPa Tensile Strength	TD	≥25	29		Qualified
		MD	≥35	48		Qualified
	Elongation at Break	TD	≥500	751		Qualified
		MD	≥400	598		Qualified
	Tearing Strength N/mm	TD	≥70	111		Qualified
		MD	≥80	192		Qualified
	Haze		≤3.5	3.0		Qualified
	Wetting Tension		≥38	38		Qualified
	Seal Initiation Temperature		≤115	113		Qualified
	Heat Seal Strength		≥10	12.1		Qualified
Coefficient of Friction			≤0.25	0.14		Qualified
Conclusion			First Class Product			