



ZHEJIANG HAIBIN FILM TECHNOLOGY CO., LTD

DONG ER ROAD, BINHAI INDUSTRIAL ZONE, KEQIAO DISTRICT

SHAOXING CITY CHINA

Tel: 86-575-85584161

Email: sales@galaxy-film.cn

Mobile: 0086 13858466830

Skype: linda.bopp

TECHNICAL DATA SHEET

Type of Film	BOPP Film		Thickness		35 MIC	
Index	Thickness	Average (mic)	34.81		Max / Min	35.5/34.3
		Tolerance (%)	-0.2			
	Physical Properties	Tensile Strength (Mpa)	MD/TD		153/335	
		Elongation of Break (%)	MD/TD		260/56	
		Elastic Modulus (Mpa)	MD/TD			
		Thermal Shrinkage (%)	MD/TD		2.5/1.0	
		Friction Coefficient	Back	Static	0.28	
				Dynamic	0.20	
			Front	Static	0.21	
				Dynamic	0.19	
		Surface Tension (mN/m)	38			
		Heat Seal Strength (N/15mm)	inside/outside 3.1/2.8			
		Haze (%)	1.86			
		Gloss (%)	93.4			
	Appearance	No Defects				