



# ZHEJIANG HAIBIN FILM TECHNOLOGY CO., LTD

**DONG ER ROAD, BINHAI INDUSTRIAL ZONE,  
KEQIAO DISTRICT, SHAOXING CITY CHINA**

**Tel: 86-575-85584161**

**Email: sales@galaxy-film.cn**

**Mobile: 0086 13858466830**

**Skype: linda.bopp**

## TECHNICAL DATA SHEET

Name		CPP	Specification	25 MIC	Test Criteria	Q/NHBZ003-2013
Testing Item			Criteria	Result		Result for Single Property
Appearance			Regular	Q/NHBZ003-2013 Standards		Eligible
Specification	Width Tolerance mm		0~+5	+3		Eligible
	Thickness Tolerance %		±8	-0.2	-2.8	Eligible
	Thickness Tolerance on Average %		±6	-1.0		Eligible
Physical Properties	Tensile Strength MPa	TD	≥25	26		Eligible
		MD	≥35	53		Eligible
	Elongation at Break %	TD	≥500	710		Eligible
		MD	≥400	541		Eligible
	Wetting Tensioning		≥38	38		Eligible
	N Heat Sealing Strength		≥8	9.2		Eligible
C.O.F			≤0.25	0.14		Eligible
Definition			First Class Product			