



ZHEJIANG HAIBIN FILM TECHNOLOGY CO., LTD

DONG ER ROAD, BINHAI INDUSTRIAL ZONE, KEQIAO DISTRICT

SHAOXING CITY CHINA

Tel: 86-575-85584161

Email: sales@galaxy-film.cn

Mobile: 0086 13858466830

Skype: linda.bopp

TECHNICAL DATA SHEET

Type of Film	BOPP FILM/25mic two sides heat sealable		Inspector		Ding	
Index	Thickness	Average (mic)	24.68		Max / Min	25.1/24.0
		Tolerance (%)	-1.30%			
	Physical Properties	Tensile Strength (Mpa)	MD/TD		145/329	
		Elongation of Break (%)	MD/TD		180/47	
		Elastic Modulus (Mpa)	MD/TD			
		Thermal Shrinkage (%)	MD/TD		3.2/1.3	
		Friction Coefficient	Back	Static	0.29	
				Dynamic	0.29	
			Front	Static	0.25	
				Dynamic	0.24	
		Surface Tension (mN/m)			38	
		Heat Seal Strength (N/15mm)			4.08	
		Haze (%)			1.46	
		Gloss (%)			92.7	