

ZHEJIANG HAIBIN FILM TECHNOLOGY CO., LTD

DONG ER ROAD, BINHAI INDUSTRIAL ZONE, KEQIAO DISTRICT SHAOXING CITY CHINA

Tel: 86-575-85584161 Email: sales@galaxy-film.cn Mobile: 0086 13858466830 Skype: linda.bopp

TECHNICAL DATA SHEET

Name	VM	ВОРР	Specifications	18MIC	Test Basis	BB/T0030-2004
Testing Result						
Test Propertiers			Units	Test Datas		Single Conclusion
Thickness			μm	18		Qualified
Thickness Deviation		%	±1.0		Qualified	
Tensile Strength		MD	Mara	144		Qualified
		TD	Mpa	236		Qualified
Elongation at Break		MD	%	150		Qualified
		TD	70	55		Qualified
Thermal Shrinkage			N	3.0		Qualified
W.W. Tanaian			mN/m	38		Qualified
Wetting Tension		Qualified				
Heat Shrinkage		MD	%	4		Qualified
		TD	/0	2.36		Qualified
Haze			%	1.32		Qualified
Thickness of Aluminum Layer			Å	380		Qualified
Firm of Aluminum Layer				3M Tape		No peal of aluminum
Uniformity of Aluminum Layer			%	±10		Qualified
Appearance		Qualified				
Testing Conclusion		Qualified				