

The Technical Specifications of Copy Paper

Super premium multi-purpose A4 papers no recycling.

- Basic weight: 80g/m²,
- Moisture 3.5%-4.5%,
- Whiteness: >98%
- Thickness: 103-110 µm
- Surface roughness TS ml/min: 75-175
- Surface roughness BS ml/min: 100-200
- Bending stiffness MD: >110 Mn
- Bending stiffness CD: >50 Mn
- Opacity: >94%
- Brightness: 101-104%
- CIE whiteness: 148-152
- Cobb Test: 27-33 g/m² 27-33
- We will also need the following specifications:
- Tensile strength MD
- Tensile strength CD
- Tear resistance MD
- Tear resistance CD
- Colour shade L
- Colour shade a
- ph

Key Performance

- No jam in photocopy machine
- No double feed
- Stay flat after copying
- Leave no dust in the copy-machine
- Nice appearance-white and clean
- Nice touch-smooth and bulky
- No see through-print both sides
- Been developed for : Photocopy Machines, Laser Printers, Ink-jet Printers, Fax Machines

Packaging

- 500 sheets/ream, 5 reams/carton
- All cartons must be packed on pallets
- 20ft containers required

Quantity Required

- 5 x 20ft containers

Destination

Class A ISO 9001

Basic Weight	g/m ²	ISO 536	80
Thickness	mm/1000	ISO 534	111
Bending stiffness CD	mN	ISO 2493	145 68
Surface roughness BS	ml/min	ISO 8791-2	
200			
CIE Whiteness		ISO 11475	166
UV Whiteness	%	ISO 2470	113
Opacity	%	ISO 2471	min 91,5
Moisture	%	ISO 287:1994	3,8-5,0

Class B ISO 9001

Basic Weight	g/m ²	ISO 536	80
Thickness	mm/1000	ISO 534	106
Bending stiffness CD	mN	ISO 2493	125 60
Surface roughness BS	ml/min	ISO 8791-2	
200			
CIE Whiteness		ISO 11475	161
UV Whiteness	%	ISO 2470	110
Opacity	%	ISO 2471	min 91
Moisture	%	ISO 287:1994	3,8-5,0

Class C ISO 9001

Basic Weight	g/m ²	ISO 536	80
Thickness	mm/1000	ISO 534	106
Bending stiffness CD	mN	ISO 2493	122,5
55			
Surface roughness BS	ml/min	ISO 8791-2	
200			
CIE Whiteness		ISO 11475	146
UV Whiteness	%	ISO 2470	103,5
Opacity	%	ISO 2471	min 90
Moisture	%	ISO 287:1994	3,8-5,0

100% wood pulp copy paper quality standards
The Technical Standard of Copy Paper

Property 指标名称		Unit 单位	Grade A 优等 (A)	
Grammage 定量		g/m ²	70.0±2.0	80.0±2.0
Thickness 厚度		μm	100-104	110-115
Brightness(ISO11475/1999 D65/10°) 白度(ISO11475/1999 D65/10°)		%	104 ±1.0	
Opacity 不透明度		%	≥85.0	
Smoothness 平滑度 Average of both sides 正/反面平均		S	20-30	
Stiffness(bend procedure) 挺度 (弯曲法)	MD 纵向	mN	≥80	≥105
	CD 横向		≥35	≥48
Dirt 尘埃度	In which 0.2-1.5mm ² 0.5-1.5 mm ² >1.5mm ²	p/m ²	≤30 ≤4 none	
Moisture 水份		%	5.0±1.0	
Shade 色调	L a* b*		≥92 3.0±0.3 -15.7±0.3	
Splice 卷筒接头		n/roll	≤1	