

Typical Values of Physical Properties *

Property		Unit	Testing Method	Thickness in microns				
				15	17.5	20	25	30
Optical Density		-	Macbeth	2.2				
Kinetic Coefficient of Friction (F/F)	NT/NT	--	ASTM D1894	0.3				
Tensile Strength	MD	N/mm ²	ASTM D882	125				
	TD			235				
Elongation at Break	MD	%		180				
	TD			50				
Secant Modulus @ 2%	MD	N/mm ²		1,700				
	TD			3,000				
Heat Seal Initiation Temperature (SIT)	NT	°C	ASTM F88 / F2029A	105				
Seal Strength @ 130° C	NT	N/25mm	40 psi, 0.5s	4.0			6.0	
Water Vapor Transmission Rate (WVTR) @ 38°C, 90% RH		g/m ² /day	ASTM F1249	0.2				
Oxygen Transmission Rate (OTR) @ 22°C, 0% RH		cm ³ /m ² /day	ASTM D3985	60				

Notes

MD Machine Direction
TD Transverse Direction
NT Non Treated Side
T Treated Side

* Information presented in this data sheet is intended to be used as general guidelines and not as technical specifications

Important Considerations

- It is recommended to store this material at conditions not exceeding 30°C in temperature, at shadow and with a relative humidity of 60%
- There might be a deterioration of certain physical properties by adverse storage conditions through time. It is therefore advisable to keep an adequate inventory turn-over of this material.