

100% wood pulp copy paper quality standards

The Technical Standard of Copy Paper

Property 指标名称		Unit 单位	Grade A 优等 (A)	
Grammage 定量		g/m ²	70.0±2.0	80.0±2.0
Thickness 厚度		μm	100-104	110-115
Brightness(ISO11475/1999 D65/10°) 白度(ISO11475/1999 D65/10°)		%	104 ±1.0	
Opacity 不透明度		%	≥85.0	
Smoothness 平滑度 Average of both sides 正/反面平均		S	20-30	
Stiffness(bend procedure) 挺度 (弯曲法)	MD 纵向	mN	≥80	≥105
	CD 横向		≥35	≥48
Dirt 尘埃度	In which 0.2-1.5mm ² 0.5-1.5 mm ² ≥ 1.5mm ²	p/m ²	≤30 ≤4 none	
Moisture 水份		%	5.0±1.0	
Shade 色温	L		≥92	
	a* b*		3.0±0.3 -15.7±0.3	
Splice 卷筒接头		n/roll	≤1	