

Technical Data Sheet

F4OP003

14/10/2022

Version 1

Name and Code

F4OP003 Technolux 2K matt g30 .

Description and performances

Matt acrylic topcoat Two-component

F4OP003 has the following features:

- Quick drying
- high flexibility
- high resilience
- suitable for the protection of iron, galvanized sheet, brass, silver, copper, aluminum, steel
- good anti-scratch properties
- excellent fullness and excellent retention in sunlight

Technical Data Sheet

F4OP003

14/10/2022

Version 1

Tests performed

Description	Method	Unit of measure	Value - Range
Adhesion	UNI EN ISO 2409	Test level	0
Pencil hardness	ASTM D 3363		HB
Resistance to temperature	Thermal differences: from -40°C to +120°C for 15 cycles		ok
Resistance to chemicals	Acetic acid 5%		ok
Resistance to chemicals	Sodium Chloride 20%		ok
Resistance to chemicals	Sodium hydroxide 10%		ok
Resistance to chemicals	Sodium sulphate 10%		ok
Resistance to chemicals	Sodium hypochlorite 10%		ok
Resistance to chemicals	Differential oil		ok
Resistance to chemicals	Hydraulic brake oil		ok
Resistance to chemicals	Diesel engine oil		ok
Resistance to chemicals	Synthetic Engine Oil		ok
Resistance to chemicals	Baked linen oil		ok
Resistance to chemicals	Vaseline		ok
Resistance to chemicals	Petrol 99 octane		ok
Resistance to chemicals	Lead-free petrol		ok
Resistance to chemicals	Diesel		ok
Resistance to chemicals	Glycerol		ok
Resistance to chemicals	Acetone		ok
Resistance to chemicals	Ethanol		ok
Resistance to chemicals	Saline solution 5%		ok
Resistance to chemicals	Distilled water		ok
Resistance to chemicals	Solvesso 100		ok

Technical Data Sheet

F4OP003

14/10/2022

Version 1

All tests must be carried out at least 15 days after application

Additional description of the product

Chemical - Technical Properties

Description	Method	Unit of measure	Value - Range
Solid content	I.O. 371	%	53±1
Viscosity DIN 8 @20°C	I.O. 301	seconds	15±5
Specific gravity	I.O. 309	g/cm3	0,9800±0,020
Gloss Level		gloss units	30±5
Solid Content A+B		%	45±1
VOC A+B		g/l	470-500

* Typical values

Usable surfaces

All surfaces to be coated must be clean and dry and free from dust and rust. Any traces of salt, grease and oil must be removed using a suitable detergent

For all light alloys, roughen the surface of the substrate mechanically or manually, then clean accurately

Suitable surface
Iron/Steel
Galvanised sheet metal
Aluminum
Cement
Brass
Copper
silver

Technical Data Sheet

F4OP003

14/10/2022

Version 1

Field of application

F4OP003: 100 parts by weight

F901CT: 20 parts by weight Catalyst ratio in volume: 4:1

F922CT: 20 parts by weight ; Catalyst ratio in volume: 4:1

Thinning: according application device used (see table below)

Pot-Life + 10 °C 8-10 hours

Pot-Life + 20 °C 6-8 hours

Pot-Life + 30 °C 4-6 hours

Application device:

- The product needs to be applied at temperatures ranging between +0°C and +35°C and with relative humidity no higher than 85%
- The surface temperature must be at least 3°C above dew point
- Temperatures of below +0°C inhibit drying

Drying (Thickness (DFT) 30μ dry)

Degree of drying	10°C	20°C	30°C	Unit of measure
Dust free	20-30	10-20	5-10	minuti
To touch	40-60	20-40	10-20	minuti
Tack free	12-16	6-8	4-6	ore
Stackable	16	12	8	ore
Complete cross-linking	10	7	5	giorni

Drying time may vary according to the thickness applied and humidity

Suitable air exchange on the surface of the item facilitates drying

Stacking times depend on the thickness, humidity and size of the items

Technical Data Sheet

F4OP003

14/10/2022

Version 1

Application methods

Application devices	Thinner	Thinning (%)	Pressure	Nozzle	Fan (in °)
gravity spray gun	DPN425	15-25	1,8-2,2 atm	1,4-1,6 mm	40
airless	DPN425	10-15	120 bar	0,11 mm/p	30
airmix	DPN425	5-15	90 bar	0,11 mm/p	40
Electrostatic	DPN425	15-25	120 bar	0,11 mm/p	40

For applications in airless.airmix and electrostatic the compression ratio is: 30:1

Subsequent layers

Time for applying further coats:

- minimum: wet on wet
- maximum: 5 days

Recommended primers: Product applicable directly on all the supports listed above
product applicable on metalized bases and pastel shades to obtain the double layer with wet-on-wet repainting

Thickness and yield

Thickness wet (μ)	Thickness dry (μ)	Theoretical yield (mq/L)	Theoretical yield (mq/Kg)	Theoretical consumption per 1mq(L)	Theoretical consumption per 1mq (KG)
minimum 50	minimum 20	19,80	19,40	0,050	0,055
maximum 90	maximum 40	11,20	11,00	0,090	0,095

Yield and consumption are theoretical only. Practical values vary according to the efficiency of transfer and the method used

Technical Data Sheet

F4OP003

14/10/2022

Version 1

Operative advice

Recipients used must be disposed of in compliance with regional regulations and/or legislation
Once coating is finished, we recommend cleaning all equipment used immediately with a good washing diluent

Storage instructions

Keep containers tightly closed, cool and in a ventilated area; protect from the frost
EXPIRATION DATE: 12 months
The data refers to the product stored in original sealed packaging

POLISTUC. - plant: Via Comunale del Rovere,4 85-SAN GIOVANNI AL NATISONE (UD) - Italy - Tel. +39 0432/747411 Fax +39 0432/747411 - Internet: www.polistuc.it
POLISTUC is a brand of SIRCA S.p.A. - Offices and plant: Viale Roma, 85-35010 Sandono di Massanzago (PD) - Italy - Tel. 049/9322311 ra - 049/5797262 Fax - Internet: www.sirca.it
S.p.A. has a quality system certified by DNV ISO 9001

The information supplied are correct to the best of our knowledge. However, as the coating process depends on many variables and the present application takes place without our supervision, we cannot assume any responsibility for the final result. Sirca guarantees that chemical and physical characteristics of the products are within the reported range. Due to the large variety of substrates and application devices, the purchaser/user should test our products in his own application conditions and safety and environment circumstances. Sirca's technical and sales departments are at customer's disposal for any further information regarding correct application of our products