

Technical Data Sheet

F4SP100

07/08/2019

Version 1

Name and Code

F4SP100 .

Description and performances

High gloss acrylic transparent topcoat Two-component

F4SP100 has the following features:

- Quick drying
- high flexibility
- high resilience
- suitable for the protection of iron, galvanized sheet, brass, silver, copper, aluminum, steel
- good anti-scratch properties
- excellent body and distinctness of the image; excellent light retention
- usable as a glossy finish on metallized bases or pastel shades to obtain a double layer with wet-on-wet repainting

Additional description of the product

Chemical - Technical Properties

Description	Method	Unit of measure	Value - Range
Solid content(*)	I.O. 371	%	47±1
Solid content by volume(*)		%	39±1
Viscosity DIN 4 @20°C	I.O. 301	seconds	30±3
Specific gravity(*)	I.O. 309	g/cm3	0,980±0,020
Gloss Level		gloss units	>95
Solid Content A+B(*)		%	43±1
VOC A+B		g/l	0,520

* Typical values

Technical Data Sheet

F4SP100

07/08/2019

Version 1

Usable surfaces

All surfaces to be coated must be clean and dry and free from dust and rust. Any traces of salt, grease and oil must be removed using a suitable detergent

For all light alloys, roughen the surface of the substrate mechanically or manually, then clean accurately

Suitable surface
Iron/Steel
Galvanised sheet metal
Aluminum
Brass
Copper
silver

Special supports: In the presence of special supports, shiny or smooth, where adhesion may not be sufficient, it is advisable to carry out preliminary tests by adding in the application phase the adhesion promoter CR 4110 to the extent of 3% on part A.

Technical Data Sheet

F4SP100

07/08/2019

Version 1

Field of application

F4SP100: 100 parts by weight

F921CT: 50 parts by weight ; Catalyst ratio in volume: 2:1

F922CT: 40 parts by weight

Thinning: according application device used DPN425 winter thinner DPN426 summer thinner

Application: gravity spray gun, airmix, Electrostatic

Pot-Life + 25 °C 4-5 hours

Application device:

- The product needs to be applied at temperatures ranging between +0°C and +35°C and with relative humidity no higher than 85%
- The surface temperature must be at least 3°C above dew point
- Temperatures of below +0°C inhibit drying

Drying (Thickness (DFT) 30µ dry)

Degree of drying	20 °C	30 °C	Unit of measure
Dust free	10-20	5-10	minuti
To touch	30-40	20-30	minuti
Tack free	8-12	4-8	ore
Stackable	16	12	ore
Complete cross-linking	7	5	giorni

Drying time may vary according to the thickness applied and humidity

Suitable air exchange on the surface of the item facilitates drying

Stacking times depend on the thickness, humidity and size of the items

Subsequent layers

Time for applying further coats:

- up to 1h: wet on wet
- after drying: after sanding

Recommended primers: Product applicable directly on all the supports listed above

product applicable on metalized bases and pastel shades to obtain the double layer with wet-on-wet repainting

Applicable as a glossy finish on all the solvent finishes, strictly respecting the overcoating times shown in the TDS of each product used

Technical Data Sheet

F4SP100

07/08/2019

Version 1

Operative advice

Recipients used must be disposed of in compliance with regional regulations and/or legislation
Once coating is finished, we recommend cleaning all equipment used immediately with a good washing diluent

Storage instructions

Keep containers tightly closed, cool and in a ventilated area.
EXPIRATION DATE: 12 months
The data refers to the product stored in original sealed packaging

POLISTUC. - plant: Via Comunale del Rovere,4 85-SAN GIOVANNI AL NATISONE (UD) - Italy - Tel. +39 0432/747411 Fax +39 0432/747411 - Internet: www.polistuc.it
POLISTUC is a brand of SIRCA S.p.A. - Offices and plant: Viale Roma, 85-35010 Sandone di Massanzago (PD) - Italy - Tel. 049/9322311 ra - 049/5797262 Fax - Internet: www.sirca.it
S.p.A. has a quality system certified by DNV GL ISO 9001

The information supplied are correct to the best of our knowledge. However, as the coating process depends on many variables and the present application takes place without our supervision, we cannot assume any responsibility for the final result. Sirca guarantees that chemical and physical characteristics of the products are within the reported range. Due to the large variety of substrates and application devices, the purchaser/user should test our products in his own application conditions and safety and environment circumstances. Sirca's technical and sales departments are at customer's disposal for any further information regarding correct application of our products