

Technical Data Sheet

FDL2500

31/05/2023

Version 2

SIRCA S.p.A. - Offices and plant: Viale Roma, 85-35010 Sandono di Massanzago (PD) - Italy - Tel. 049/9322311 ra - 049/5797262 Fax - Internet: www.sirca.it.

BRAND: Sirca.

S.p.A. has a quality system certified by DNV according to standard UNI EN ISO 9001.

Name and Code

FDL2500 ACR UV High gloss topcoat SP .

Chemical Nature

Acrylic paint.

Description and performances

Dual cure U.V. high gloss. The product is suitable for furniture, kitchen cabinets and flat items applications.

Additional description of the product

Chemical - Technical Properties

Description	Method	Unit of measure	Value - Range
Solid content	I.O. 371	%	70±1
Viscosity DIN 4 @20°C	I.O. 301	seconds	35±5
Specific gravity	I.O. 309	g/cm3	0,980±0,010

Technical Data Sheet

FDL2500

31/05/2023

Version 2

Field of application

FDL2500: 100 parts by weight

CTH46s05: 10 parts by weight

DPU809: 30-40 parts by weight

DPP2021: 20-30 parts by weight (alternatively) . Excellent wetting properties.

Drying conditions: 25-30 °C

Laminated air: 25-30 minutes

Drying conditions: Three U.V. lamps Hg, 80 W/cm, at 8 m/min speed

Application amount: 100-110 g/m²

Number of layers: 1

Application devices: spray and curtain coater

General properties

Acrylic high gloss topcoat with great levelling properties, great body and good distinctness of the image.

We recommend to apply the product by spray or curtain coater, on UV putty or polyester basecoat thoroughly sanded.

Storage instructions

Keep the product in a ventilated area; do not exceed 25-28°C. Polyisocyanic hardeners should be protected from frost and humidity. If they have been partially used please close the can tight and use the residual amount in a short time.

EXPIRATION DATE 6 months

The data refers to the product stored in original sealed packaging.

The information contained in this datasheet is based on laboratory data and our experience. Gel time and rheological properties may change because of reactive nature of material. We believe this information to be reliable, however we cannot guarantee its applicability in your process. We decline all responsibility for events that may arise as a consequence of improper use of the product.

By accepting the products described herein, the user accepts the responsibility to thoroughly test any application before commencing production. Our advice should not be taken as encouragement to breach any patent, law, safety code or insurance regulation.