

---

# Technical Data Sheet

**CIM0230**

**13/02/2018**

**Version 1**

---

SIRCA S.p.A. - Offices and plant: Viale Roma, 85-35010 San Dono di Massanzago (PD) - Italy - Tel. 049/9322311 ra - 049/5797262 Fax - Internet: [www.sirca.it](http://www.sirca.it).

S.p.A. has a quality system certified by DNV according to standard UNI EN ISO 9001.

---

## Name and Code

CIM0230 White SINT Paste .

---

## Chemical Nature

Pigment dispersed in binder.

---

## Description and performances

CIM.e is a series of coloring pastes based on transparent iron oxides, developed to color long oil air drying alkyds products such as the transparent impregnating agents of the IME2000 series.

In the colouring process of clear impregnating agents, the recommended dosage is 8% (max)

---

## Additional description of the product

### Chemical - Technical Properties

| Product Name | Colour | % Solid Content | Specifi Gravity (g/cm3) |
|--------------|--------|-----------------|-------------------------|
| CIM0102      | brown  | 67±1            | 0,970±0,010             |
| CIM0230      | white  | 87±1            | 1,950±0,010             |
| CIM0238      | Blue   | 56±1            | 1,000±0,010             |
| CIM0239      | Green  | 56±1            | 1,000±0,010             |
| CIM0243      | Red    | 46±1            | 0,900±0,010             |
| CIM0246      | Black  | 43±1            | 0,905±0,010             |
| CIM0255      | yellow | 43±1            | 0,905±0,010             |

---

# Technical Data Sheet

**CIM0230**

**13/02/2018**

**Version 1**

---

## Storage instructions

Keep the product in a ventilated area; do not exceed 25-28 °C. Polyisocyanic hardeners should be protected from frost and humidity. If they have been partially used please close the can tight and use the residual amount in a short time.

EXPIRATION DATE 12 months

The data refers to the product stored in original sealed packaging.

---

## Danger level for people and environment

Before use consult the safety data sheet

---

The information supplied are correct to the best of our knowledge. However, as the coating process depends on many variables and the present application takes place without our supervision, we cannot assume any responsibility for the final result. Sirca guarantees that chemical and physical characteristics of the products are within the reported range. Due to the large variety of substrates and application devices, the purchaser/user should test our products in his own application conditions and safety and environment circumstances. Sirca's technical and sales departments are at customer's disposal for any further information regarding correct application of our products