



Report on C3-76-018726-1-A21-0044

04/23/2021

Langdon Feltner

The plate was laid up and cured and post cured as per the manufacturer recommended procedure. It was then measured on a Hexagon coordinate measuring machine for the thickness measurements

Units in mm



Statistics

Average Thickness:	0.205
Thickness Standard Deviation:	0.005

11x11 Thickness Measurements for C3-76-018726-1-A21-0044

Units in mm

0.196	0.198	0.207	0.197	0.201	0.205	0.208	0.200	0.199	0.205	0.206
0.204	0.204	0.201	0.204	0.204	0.208	0.212	0.206	0.207	0.212	0.216
0.199	0.202	0.210	0.205	0.210	0.206	0.209	0.204	0.209	0.217	0.204
0.199	0.202	0.205	0.204	0.205	0.207	0.215	0.208	0.209	0.208	0.203
0.199	0.202	0.206	0.212	0.209	0.210	0.214	0.207	0.204	0.212	0.202
0.203	0.199	0.205	0.214	0.204	0.212	0.208	0.203	0.204	0.211	0.200
0.203	0.202	0.206	0.208	0.207	0.204	0.217	0.205	0.204	0.206	0.196
0.201	0.198	0.206	0.207	0.204	0.204	0.209	0.202	0.202	0.202	0.198
0.202	0.201	0.200	0.207	0.208	0.206	0.214	0.217	0.203	0.202	0.203
0.200	0.193	0.204	0.202	0.201	0.200	0.208	0.209	0.194	0.200	0.202
0.199	0.199	0.192	0.207	0.207	0.200	0.211	0.205	0.199	0.201	0.202