


Report on C3-76-018726-1-A21-0046

04/22/2021

Langdon Felter-CMSC

The plate was laid up and cured and post cured as per the manufacturer recommended procedure. It was then measured on a Hexagon coordinate measuring machine for the thickness measurements

Units in mm



Statistics

Average Thickness:	0.200
Thickness Standard Deviation:	0.006

11x11 Thickness Measurements for C3-76-018726-1-A21-0046

Units in mm

0.194	0.192	0.203	0.190	0.195	0.193	0.198	0.196	0.197	0.199	0.203
0.200	0.204	0.195	0.194	0.202	0.196	0.199	0.196	0.196	0.209	0.195
0.194	0.196	0.196	0.198	0.197	0.213	0.206	0.196	0.196	0.205	0.204
0.194	0.197	0.196	0.197	0.199	0.203	0.228	0.196	0.200	0.204	0.197
0.196	0.198	0.207	0.203	0.198	0.226	0.203	0.199	0.202	0.207	0.200
0.199	0.196	0.199	0.204	0.198	0.198	0.203	0.199	0.199	0.207	0.199
0.196	0.196	0.201	0.203	0.200	0.206	0.201	0.199	0.205	0.202	0.197
0.198	0.199	0.197	0.206	0.201	0.198	0.201	0.198	0.197	0.200	0.223
0.203	0.198	0.201	0.207	0.201	0.200	0.206	0.199	0.201	0.200	0.199
0.202	0.196	0.197	0.200	0.197	0.198	0.197	0.199	0.198	0.202	0.197
0.202	0.195	0.197	0.206	0.194	0.195	0.198	0.200	0.196	0.202	0.195