



Energrease FG 00-EP

Extreme pressure grease

Description

A semi-fluid extreme pressure grease based on mineral oil and polymer-thickened.

Application

Energrease FG 00-EP is for use in industrial spur, bevel and helical enclosed gears, particularly where the orientation of the gearbox is subject to change and where leakage can be troublesome. It has a working temperature range of -10°C to 100°C.

Advantages

- Sulphur-phosphorous EP additives cater for heavily loaded steel gears.
- Compatible with the ferrous and non-ferrous metals used in gear systems, and with conventional sealing materials.
- Excellent shear stability and load-carrying ability.
- Good "coating" characteristics eliminate the risks of dry start-up.
- Reduced noise levels and improved cleanliness from reduced leakage whatever the orientation of the gearbox.

Typical Characteristics

Name	Method	Units	FG 00-EP
Colour	Visual	-	Brown
Texture	Visual	-	Smooth
NLGI Class	ISO 2137		00/000
Thickener type	-	-	Polymer
Worked penetration at 25°C after 60 strokes	ISO 2137	0.1mm	430-460
Prolonged worked stability 60°C after 10,000 strokes	ISO 2137	0.1mm	+30
Drop Point	ASTM D566	°C	55
Timken OK-load	ASTM D2509	lb	40
Four ball extreme pressure test, welding load	DIN 51350:4	N	3000
FZG gear test : A/8.3/90°C	DIN 51502/51826	FLS	>12

The above figures are typical of those obtained with normal production tolerance and do not constitute a specification.

Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and the obliteration of drum markings.

Products should not be stored above 60°C, exposed to hot sun or freezing conditions.

Supplied in packs of approximately 15kg. Note that pack size may vary according to country of supply.

Energrease FG 00-EP

22 Feb 2012

BP, the BP logo and related marks are trademarks of BP p.l.c., used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Marine, Technology Centre, Whitchurch Hill, Pangbourne, Reading RG8 7QR, United Kingdom

www.bpmarine.com

