

Klüberlub BE 41- 542

Heavy-duty grease for high-load rolling bearings



Benefits for your application

- Good pressure absorption capacity
- Very good wear protection
- High corrosion protection
- Strong adhesiveness

Description

High loads and shocks can damage rolling bearings and lead to their premature failure.

To prevent this, we developed Klüberlub BE 41-542 on the basis of highly viscous mineral oil, lithium special soap, EP/AW and anticorrosive additives.

This selected combination makes Klüberlub BE 41-542 a preferred choice for numerous applications involving high loads.

- work rolls in hot strip mills
- cold pilger rolling mills
- rolling bearings subject to shock or pulsating stress
- shock absorbers in washing machines

Application notes

The ambient temperature should be $\geq 15\text{ °C}$ when applying the product with an automatic grease pump.

Application

Typical Klüberlub BE 41-542 applications are in high-load roller bearings operating at low to medium speeds such as for

- load rollers in rotary kilns for the cement industry
- crane wheels
- bucket wheel excavators
- hammer crushers, hammer mills

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klüberlub BE 41-542
Bucket 25 kg	+
Drum 180 kg	+

Product data	Klüberlub BE 41-542
Article number	020269
Colour space	brown
Texture	homogeneous
Chemical composition, type of oil	mineral oil
Chemical composition, thickener	special lithium soap
Lower service temperature	-20 °C / -4 °F
Upper service temperature	140 °C / 284 °F
NLGI grade, DIN 51818	2
Density at 20 °C	approx. 0.93 g/cm ³
Drop point, DIN ISO 2176, IP 396	$\geq 230\text{ °C}$



Klüberlub BE 41- 542

Heavy-duty grease for high-load rolling bearings

Product data	Klüberlub BE 41-542
Flow pressure of lubricating greases, DIN 51805, test temperature: -20 °C	<= 1 400 mbar
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	265 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	295 x 0.1 mm
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 540 mm²/s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 28 mm²/s
Speed factor (n x dm)	approx. 500 000 mm/min
Corrosion inhibiting properties of lubricating greases, DIN 51802, (SKF-EMCOR), test duration: 1 week, distilled water	<= 1 corrosion degree
Four-ball tester, welding load, DIN 51350 pt. 04	>= 3 000 N
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.