PRODUCT INFORMATION DATA SHEET

17451 Von Karman Avenue, Irvine, CA 92614
Tel (949) 474-0400 (800) 544-3338
Fax (949) 474-7269
www.deftfinishes.com

02GN070B (02-GN-70B) Low Density Quick Dry Epoxy Polyamide Primer

Product Information

Specifications **MIL-PRF-23377K Type II Class C2**

Description Chemically cured, strontium chromate, two-component epoxy polyamide primer

Features

- Corrosion inhibiting
- Chemical and Solvent Resistant
- Resistant to immersion in Hydraulic Fluids, Lubricating Oils, Phosphate Ester Based Hydraulic Fluids, Skydrol and Distilled water

Color **Dark Green Low IR Reflecting**

Reducer None required. May be reduced with IS-237*

Mix Ratio 3 parts 02GN070B base by volume to 1 part 02GN070BCAT catalyst by volume

Kit size	02GN070B base	02GN070BCAT
GK	1 can filled @ 96 oz / 2.84 L	1 can filled @ 32 oz / 946 mL

Pot Life 4 hours at 75° ± 10°F

Viscosity initial: 20 ± 2 seconds # 2 EZ Zahn Cup
40 seconds, max, # 4 Ford Cup
Pot life: 70 seconds, max, # 4 Ford Cup

Induction Time None required

Application Thickness 0.6 – 0.9 mils dry film thickness

Storage Stability 2 years from DOM when stored between 72 - 80°F

Recommended Storage Store indoors between 70 – 90°F in original unopened containers.

*Use only if needed and if local and state VOC limits allow.

U.S. STATE DEPARTMENT EXPORT LICENSE REQUIRED FOR DISTRIBUTION TO FOREIGN DESTINATIONS OR FOREIGN PERSONS, WHEREVER LOCATED. This document contains Technical Data controlled under the US International Traffic in Arms Regulations ("ITAR"), 22 CFR §§120-130, and may not be exported or transferred to any Foreign Person, foreign country or foreign entity, by any means, without prior written approval from the U.S. Department of State, Directorate of Defense Trade Controls ("DDTC") and PPG Industries, Inc.

Characteristics*

Characteristics	Base	Catalyst	Admixed
Weight per gallon (lbs)	10.2	8.9	9.9
% Solids by weight	46.0	82.2	55.3
% Solids by volume	36.3	76.5	47.9
Coatings VOC (g/L)	414	190	328
Coatings VOC (lbs/gal)	3.5	1.6	2.7
Material VOC (g/L)	303	190	275
Material VOC (lbs/gal)	2.5	1.6	2.3

Dry film density:** 1.39 g/cc
Theoretical Coverage per gallon as applied:** 743 sq. ft.
Theoretical Dry Film Weight per gallon kit as applied:
3.27 g/sq. ft (0.00721-lbs/sq. ft)

* Characteristics are calculated based on product formulas and ingredient characteristics as reported to Deft, Incorporated by raw material suppliers. Values reported are not specification values. They are presented for general information only.
** Dry film density and theoretical coverage based on proper application of coating at 1 mil dry film thickness and 100% transfer efficiency.
Note: Formulation contains VOC exempt solvents.

Dry Times

Dry to Topcoat: 3 - 4 hours, max **Tack Free:** 2 - 3 hours, max
Dry Hard: 8 hours, max **Full Cure:** 14 days, max

Note: Dry times above were established at room (ambient) temperatures, 75° ± 5°F and 50% ± 10% Relative Humidity. After 8 hours cure, it is recommended to solvent wipe the entire primed surface before top coating. After 24 hours of cure, it is recommended to scuff sand the entire primed surface for optimal inter-coat adhesion. Ref: T.O. 1-1-8 Section 6.12.6.5

Forced Dry Schedule

For dry to stack conditions only. Allow a minimum of 15 minutes flash off time at ambient temperatures* prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect these cure schedules.

Temperature	Time
120°F	45 minutes
140°F	30 minutes
160°F	20 minutes
180°F	15 minutes

* Ambient temperatures are defined as 70° ± 10°F and 50% ± 10% Relative Humidity.

Mixing and Thinning

Stir or shake the base component to ensure any pigment, which may have settled on the bottom of the can, has been fully incorporated into the base. **Do not stir or shake the base component longer than 5 minutes**. Slowly add one part by volume of catalyst to three parts by volume base component. Mix by hand stirring, paint shaker or mechanical mixing to ensure the base/catalyst mixture is homogeneous**. DO NOT SHAKE OR MECHANICALLY MIX MATERIAL FOR LONGER THAN 10 MINUTES.** Constant agitation of the material during spray application is recommended.

Application Equipment

Conventional, Air, Air Assisted Airless, HVLP, Electrostatic spray equipment may be used to apply this material. For your application, please contact the equipment manufacturer for more specific information on Conventional, HVLP or Electrostatic spray applications, and recommendations on hose diameter and lengths.

Packaging, Yields, Shipping Weight

This material is available in the follow kit sizes:

Kit size	Approx. Yield (Mixed)	Approx. Shipping Weight
GK	1 gallon (3.8 L)	13.0 lbs (5.9 kg)

Additional kit sizes are available upon request.

Equipment Cleanup

Use IS-237 Epoxy Reducer (MIL-T-81772B Type II) to remove any liquid or residual primer from equipment. Once material has cured, use an approved chemical paint removal system to strip primer from parts and equipment

Safety

Refer to the product label or Material Safety Data Sheet (MSDS) for each component for Personal Protective Equipment and Proper Handling.