

		RPCL-NORINCO INTL POWER LIMITED Daily as fired coal sampling report		Form No: RNPL-CHEM- 表格编号: RNPL-CHEM-	
				Effective Date(生效日期): 2026.01.03 Revision No(修订编号):B	
Patuakhali 1320 MW Coal Fired Thermal Power Plant					
Daily as fired coal sampling report of unit 入炉煤					
Sample Serial No: (样品序列号) 2026-01-02		Sample Delivery Date (取样时段) 1、 2026.01.01 (08:00—16:00) 1039.4tons taken from Ship 21/22. 2026.01.01 (08:00—16:00) 取自第21/22.船 1039.4 吨 2、 2026.01.01 (16:00—23:59) 1464.2 tons taken from Ship 21/22. 2026.01.01 (16:00—23:59) 取自第21/22船 1464.2 吨 3、 2026.01.02 (00:00—08:00) 810.8 tons taken from Ship 21. 2026.01.02 (00:00—08:00) 取自第21.船 810.8 吨			Total coal loaded: 3534.6 tons 合计上煤: 3534.6吨
Sample Location: (样品地点)		The 6.A. automatic sampling machine at 0 meters in the coal crusher building. 碎煤机楼0米6.A.自动采样机			
Analysis Date (分析日期)		2026.01.02			
Sampler (取样人)		Li wenyu 李文字			
Analyst Name (分析师姓名)		Li wenyu 李文字			
SL	Analysis Items (分析项目)	Basis (基础)	Units (单位)	Result (结果)	Method Name (方法名称)
Proximate Analysis工业分析					
1	Total Moisture (全水)	As Received Basis (收到基)	%	26.90	GB/T211-2017
2	Inherent moisture (内水)	Air Dried Basis (空干基)	%	15.84	
3	Ash Contant (灰分含量)	As Received Basis(收到基)	%	4.22	GB/T212-2008
4	Ash Contant (灰分含量)	Air Dried Basis (空干基)	%	4.86	
5	Volatile Matter(挥发性物质)	As Received Basis(收到基)	%	33.67	
6	Volatile Matter(挥发性物质)	Air Dried Basis (空干基)	%	38.76	
7	Total sulphur(总硫)	As Received Basis (收到基)	%	0.49	GB/T214-2007
8	Total sulphur(总硫)	Air Dried Basis (空干基)	%	0.56	
9	Fixed carbon (固定碳)	As Received Basis (收到基)	%	35.21	
10	Fixed carbon (固定碳)	Air Dried Basis (空干基)	%	40.54	
Calorific Value(发热量)					
1	Gross Calorific Value (GCV) (高位发热量)	As Received Basis (收到基)	Cal/g	5087	GB/T213-2008
2	Gross Calorific Value (GCV) (高位发热量)	Air Dried Basis (空干基)	Cal/g	5857	
3	Net Calorific Value (NCV) (低位发热量)	As Received Basis (收到基)	Cal/g	4733	
4	Net Calorific Value (NCV) (低位发热量)	Air Dried Basis (空干基)	Cal/g	5449	
Ash Fusion Analysis Report (灰熔融分析报告)					
1	Deformatio Temperature (DT) (变形温度)	Weak reducibility atmosphere (弱还原气氛)	°C	1180	GB/T219-2008
2	Softening Temperature (ST) (软化温度)	Weak reducibility atmosphere (弱还原气氛)	°C	1220	
3	Hemisphere Temperature (HT) (半球温度)	Weak reducibility atmosphere (弱还原气氛)	°C	1238	
4	Flow Temperature (FT) (流动温度)	Weak reducibility atmosphere (弱还原气氛)	°C	1267	
Auditor (审核) Chen Rendong 陈仁东					
Note: This report represent the analysis result of coal sample of as received and is only responsible for the acuracy of the analysis result of the sample received this time. 注: 本报告仅代表收到的煤样分析结果, 仅对本次收到的煤样分析结果的准确性负责。					