Eggshell–Agar Biocomposites

Development and characterisation for sustainable interior applications

Betül Ünal
Department of Interior Architecture
Cappadocia University

ICSMMEP-26 · MECCA · 3–4 NOVEMBER 2026



Background

Point of departure

Eggshell arises continuously as a food-processing by-product and is predominantly landfilled. It accounts for roughly a tenth of the mass of every egg, so the stream is neither small nor intermittent. Chemically it is almost pure calcium carbonate held in a porous, protein-bound crystalline structure, with a specific gravity below that of most mineral fillers used in construction.

Its composition and its uninterrupted supply have made it an established secondary mineral resource, and a substantial body of work has incorporated it into construction and polymer materials.

William & Owen (1995) · Torres et al. (2010) · Owuamanam & Cree (2020)

Material basis


94–97%

calcium carbonate by mass

0.85–2.66

specific gravity, below most mineral fillers

Disposal and valorisation routes



The case for eggshell as a mineral phase is settled. This paper is concerned with the phase that binds it.

Prior applications

Established uses of eggshell waste in engineered materials

Application	Binding phase	Reference
Partial cement replacement in concrete	Portland clinker	Teara et al. (2019); Bhartiya & Dubey (2018)
Compressed laterite brick	Soil – lime	Adogla et al. (2016)
Hot-mix asphalt	Bitumen	Razzaq & Yousif (2017)
Clay stabilisation	Clay mineral	Soundara & Vilasini (2015)
Eco-ceramic wall tile	Ceramic body	Vilarinho et al. (2022)
Particulate filler in PVC	Poly(vinyl chloride)	Skórczewska et al. (2020)
Filler in flexible polyurethane foam	Polyurethane	Victor et al. (2019)
Ceramic–metal composite	Metal matrix	Bilici et al. (2023); Yönetken et al. (2016)
Bone tissue scaffold	Calcium phosphate	Shafiei et al. (2019)
Wallpaper	Cellulosic furnish	Tutuş et al. (2018)

What every row above has in common

MINERAL PHASE · **recovered from waste in every study above**

BINDING PHASE · **cementitious, ceramic or petrochemical in every study above**

Agar as binder


Properties and existing characterisation

Agar is a thermoreversible polysaccharide extracted from red seaweed. It melts on heating and sets on cooling without chemical crosslinking, so no reactive hardener is required. Its behaviour with glycerol has been mapped systematically across 32 formulations and released as an open reference dataset.

Scope of that characterisation

Unfilled thin films, loaded in uniaxial tension, evaluated for packaging. Agar has not been characterised as the binding phase of a mineral-filled cast solid in bending.

Thermoreversible setting



The transition is physical, not chemical: no reactive hardener, no cure temperature, and at 66% mineral loading no coupling agent.

Form and loading case in this study

—	Film literature	This study
Form	Thin cast film	Cast solid, 20–50 mm
Mineral phase	Unfilled	66% of solids
Loading	Uniaxial tension	Compression and bending

The compositional logic transfers. The form and the loading case do not, and it is the loading case that governs use as an interior surface.

Hernández et al. (2022), Materials 15(11), 3954 — 32 agar / glycerin / water formulations, released as an open dataset.

Research gap

Three gaps follow from the preceding two slides

01

The binding phase is never biological

Across the eggshell literature the mineral is recovered from waste while the matrix remains Portland clinker, bitumen, lime, a ceramic body or a thermoplastic. No study reports an eggshell composite in which both phases are of biological origin and fully biodegradable.

02

Agar is characterised only as an unfilled film

The reference dataset covers thin films in uniaxial tension for packaging. The behaviour of agar as the binding phase of a highly mineral-filled cast solid, loaded in bending, is not reported.

03

Property sets are reported in fragments

Compressive, flexural, reaction-to-fire and hygric behaviour are reported in separate studies on separate formulations. No single study gives all four for one eggshell–biopolymer formulation family.

The contribution is therefore a documented protocol and a single coherent property set, not a novel constituent.

Aim

To document a reproducible production protocol for a fully bio-based eggshell–agar composite, and to characterise its mechanical, reaction-to-fire and hygric behaviour against published test standards.

Objectives

01	**Document the protocol in full**	Every parameter, in a form another laboratory can repeat.
02	**Characterise against published standards**	ASTM D790-17 · ISO 11925-2:2020 · ASTM D570-98.
03	**Position the results**	Against conventional interior materials and against bio-based composites.
04	**Derive an evaluation criterion**	Which measured quantity governs service behaviour for this class.

Scope

Within scope

Dimension	This study
Formulations	Five — three compressive, two flexural
Specimens	Three per formulation for mechanical testing
Properties	Compression, flexure, ignitability, water absorption, bulk density
Standards	ASTM D790-17 · ISO 11925-2:2020 · ASTM D570-98(2018)
Conditions	Ambient cure, single laboratory, single operator
Application	Non-loadbearing interior surfaces

Outside scope

No durability, classification or life-cycle data were generated. The results reported here are characterisation data, not a performance specification.

Each exclusion is revisited as a defined next experiment in the closing section.

Property coverage

Compression | **Flexure** | **Ignitability** | **Water absorption** | **Bulk density** | Durability | Fire classification | Life-cycle | Structural use

Filled: determined in this study. Outlined: not determined, and therefore outside every claim made in this presentation.

Method

A material-driven sequence in four stages

1 → 2 → 3 → 4

Produce

Develop the composite and record every production parameter.

Iterative formulation over twelve months

Measure

Characterise the cured material against published test standards.

Compression · flexure · ignitability · absorption

Position

Benchmark the results against two material families.

Conventional interior materials · bio-based composites

Propose

Derive an evaluation criterion from the observed behaviour.

Deformation capacity reported alongside strength

The order is material-driven: properties are measured first and the application envelope is derived from them, rather than the material being selected to satisfy a predetermined form. The design proposal presented later follows from the measurements and not the reverse.

Material-driven design after Karana et al. (2015)

Research questions

01	**Which formulation variable governs compressive strength?**	Formulation
02	**How does plasticiser content affect flexural behaviour?**	Formulation
03	**How does the composite compare with conventional interior materials?**	Benchmark
04	**How does it compare with other bio-based composites?**	Benchmark
05	**Is compressive strength an adequate evaluation criterion for this class?**	Criterion

Questions one to four are answered by measurement. Question five is answered by argument from those measurements.

Hypothesis

A fully bio-based eggshell–agar composite can be produced repeatably under ambient conditions, and its performance as an interior surface material is governed by deformation capacity rather than by compressive strength.

Two clauses, tested separately

Clause 1	**Producible repeatably under ambient conditions**	Tested by the protocol and the formulation series.	➡ Slides 12–15
Clause 2	**Governed by deformation capacity rather than strength**	Tested by the mechanical results and the two benchmarks.	➡ Slides 17–24

Provenance. The dissertation from which this work derives states a broader hypothesis framed on spatial resilience in interior design. The formulation above is the materials-engineering component of it, restated within the scope of the tests reported here.



Four constituents, each biodegradable

Waste eggshell powder · agar · glycerol · water, with a shellac finish. Colour and texture vary with natural pigment and mould geometry at constant composition.

Stage 1 · Mineral phase

Progressive size reduction of the shell to a sieved powder



Whole shell	Cleaned	Heat-treated	Milled	Sieved
collected from a single bakery	membrane and residue removed manually	decontamination and drying	laboratory mechanical grinder	passing fraction retained
—	—	**120 °C, 20 min**	**to homogeneous powder**	**150 µm mesh**


Particle size rationale

The 150 µm fraction was selected to match the particle size used in the eggshell polymer-composite literature, so that the mineral phase in this study is comparable with that body of work.

The 120 °C step is reported as decontamination and drying, not sterilisation: dry-heat sterilisation requires higher temperatures for longer, and sterility was not verified.

Stage 2 · Binder preparation

Temperature–time profile of the 55-minute preparation




Agar is taken into solution before viscosity develops; incremental addition prevents agglomeration, and the shell fraction is introduced late to prevent sedimentation.

Schematic. The two set points and the total heating time are recorded; intermediate ramp rates are not, and are drawn indicatively. Stirring was manual, so shear rate is not a controlled quantity.

Stage 3 · Casting and cure

Eleven days from casting to finished specimen, without thermal input



Thermal input

None after the 55-minute preparation. The entire cure proceeds at room temperature.

Silicone moulds release without a parting agent and without damaging a partially consolidated specimen. 50 mm cube moulds for compression, flat moulds otherwise.


Limitation the composite shrinks appreciably as water evaporates. Cross-sections were measured at test time, but post-drying dimensions were not logged, so every dimension quoted in this presentation is a mould dimension.

Formulations

Five mixes, with the derived ratios that govern the results

ID	Test	Water g	Shell g	Agar g	Glycerol g	Shell : binder	Solids : water
C1	Compression	325	80	35	5	**2.00**	0.37
C2	Compression	310	90	40	5	**2.00**	0.44
C3	Compression	280	110	45	10	**2.00**	0.59
F1	Flexure	450	190	70	60	1.46	0.71
F2	Flexure	480	190	70	30	1.90	0.60

Batch composition by mass



Three specimens per formulation. Values reported later are means; individual values were not retained, so standard deviations cannot be given.

Compressive series


Shell-to-binder is held at exactly 2.00 across all three mixes, so solids concentration is the only variable — the water band shortens from C1 to C3.

Flexural series

Glycerol was halved at fixed batch mass, so water rose with it. The plasticiser effect is not isolated.

Test programme


Four specimen geometries



Cube compression

50 mm cube, platen-loaded


n = 3 per mix



Three-point flexure

180 × 60 × 20 mm, 120 mm span


ASTM D790-17 · n = 3 per mix



Edge ignition

40 × 50 mm at 45°, 15 s flame

ISO 11925-2:2020 · n = 2



Immersion

40 × 50 mm, shellac-coated, 24 h

ASTM D570-98 · n = 1

Reporting convention

Mechanical values are means of three specimens; individual values were not retained, so standard deviations cannot be reported. Ignitability, absorption and density rest on single determinations.

All testing: Advanced Construction Materials Research Laboratory, Hacettepe University. · Schematic, not to scale.


Compression

Measured values

ID	Solids : water	F_{max} kN	σc MPa
C1	0.37	3.89	2.55
C2	0.44	4.30	3.12
C3	0.59	**6.80**	**4.10**

Compressive strength rises with solids concentration, not with mineral content.


Shell-to-binder is fixed at 2.00 across the series, so packing density is the only variable. The relation is linear over the range tested, R^2 = 0.99 — three formulations, and therefore a hypothesis rather than a law.




Fitted relation: σc = 6.93 (solids : water) + 0.04

Solids : water ratio shown beneath each formulation identifier.

Compressive failure



Compressive stress (MPa) – strain, C3



Observed response

- Linear to approximately 1 MPa, then progressive loss of stiffness
- Peak stress near 10% strain, with no abrupt load drop
- Continued deformation beyond peak with retained integrity

Interpretation

The agar network yields and the mineral redistributes rather than the section parting. Energy is absorbed rather than released, and the specimen remains a single body after test.

Failure proceeds by progressive crushing rather than by fracture.


Strain derived from an assumed 10% maximum deformation based on observation, not instrumented measurement. · Bulk density 1.38 g/cm^3, mould-volume basis.

Flexure

Measured values — ASTM D790-17, three-point

ID	Glycerol % solids	F_{max} N	σF MPa	EF MPa	ε peak
F1	18.8	—	*not measurable*	—	—
F2	10.3	310	2.325	192	0.0121

Flexural stress (MPa) – strain, F2



Flexural strength computed as $\sigma_F = 3FL / 2bd^2$ on the full rectangular section.

At 18.8% glycerol the instrument registered no usable resistance. Halving the plasticiser gave a section that resists while still deforming substantially.


The transition lies between these two values.

Limitation

The specimen is kerfed on its tension face. The standard assumes a solid rectangular section and the calculation uses the full section, so part of the measured compliance is geometric and the reported modulus is a lower bound.

Flexural resistance is governed by plasticiser content.

Confounded with solids concentration: batch mass was held constant, so water rose as glycerol fell.







Flexural deformation


The beam is deflected well beyond the failure point of a comparable ceramic without parting. Transverse kerfs on the tension face permit the panel to be arched by hand.

The kerfs are also why the measured compliance is partly geometric, and why the reported modulus is a lower bound rather than a material constant.

Substantial deformation with retained integrity, in both test programmes.

Three-point rig at high deflection · close-up of the kerfed tension face · panel arched by hand

Fire, water, density



Ignitability

≈ 10 s

to ignition under direct flame

4 s

to self-extinguish after flame removal

- Charring remains local
- No lateral flame spread
- No melting and no dripping

The probable mechanism is endothermic decomposition of the carbonate fraction, diluting the flame front. This was not verified calorimetrically.

ISO 11925-2:2020. Ignitability only: no Euroclass classification, cone calorimetry, smoke or toxicity data.

Water absorption, 24 h immersion

0.7%

mass gain, shellac-coated. Coating integrity rather than the composite is the limiting factor for humid service.


Bulk density

Material	g/cm³	Reference
This study (C3)	1.38	—
Mycelium, cellulose	0.3 – 0.8	Jones et al. (2020)
Fired clay brick	1.6 – 2.0	William & Owen (1995)

Denser than the fungal and cellulosic family, lighter than fired clay. Mould-volume basis, therefore a lower bound.

Conventional materials

Compressive and flexural strength against interior surface materials



Velasco & Gaona (2011) · Klyosov (2007) · Nemli & Aydın (2007) · Altun (2006)

Position

One sixth the compressive strength of MDF and one twentieth that of travertine, a stone the material visually resembles. Three times the compressive strength of compressed mushroom panel, the only other fully bio-based board in the set.


On strength alone the composite is not competitive with engineered wood or stone.

Bio-based composites

Compressive strength

Material	σc MPa	Reference
This study (C3)	**4.1**	—
Mycelium composite	0.145 – 0.452	Jones et al. (2020)
Hempcrete	0.3 – 0.6	Arnaud & Gourlay (2012)
Eggshell-filled PLA	2 – 5	Kim & Pal (2010)
Mineral-filled biocomposite	2.1 – 39.6	Shah et al. (2016)

Elastic modulus, MPa, logarithmic



Unlabelled points: soy-based bioplastic 124, flax-fibre PLA 198, pine 11 000.


Water-cast and ambient-dried, the composite attains the stiffness range of melt-processed bio-polymers.

An order of magnitude above the fungal and lime-binder family in compression, and inside the LDPE band in stiffness — without an oven, an autoclave or an extruder. Wood remains two orders of magnitude above.

Values are reported as published; specimen geometry and test method differ between sources.

Modulus of resilience

Elastic energy absorbed per unit volume



The shaded area is the energy absorbed per unit volume before permanent damage: ½ σ ε, and with ε = σ / E it reduces to the expression at right.

$$Ur = \sigma^2 / 2E$$

$$14.1\ kJ/m^3$$

computed from this study's own σ_F = 2.325 MPa and E_F = 192 MPa

Elastic modulus appears in the denominator.

The low modulus that counted against the material on the preceding slide is the same property that raises this quantity. Strength records the load at which performance ceases; it does not record whether failure is graceful or catastrophic.

Limitation

A comparative table cannot yet be assembled: the literature reports strength and modulus in separate studies on separate formulations.

This is a data point and a proposed reporting convention, not a ranking, and the value inherits the lower-bound modulus.

Resilience as a property of systems that absorb disturbance and retain function, after Holling (1973).

Application envelope

Modular proposal derived from the measurements



Demountable modules on a reversible fixing, replaceable one unit at a time.

No life-cycle assessment was carried out. These are qualitative potentials grounded in the protocol, not quantified claims.

Conditions of use, each traced to a measured result

Non-loadbearing surfaces

self-weight and handling loads only; σc = 4.1 MPa

Dry interiors

not wet rooms, not façades; absorption depends on coating integrity

Away from ignition sources

self-extinguishing, but unclassified for reaction to fire

Modular rather than sheet

damage is replaced one unit at a time

End of life

Every constituent, the shellac included, is biodegradable, and reversible fixing recovers the module intact. What is displaced is quarried limestone.

Limitations and further work

Each limitation, and the experiment that resolves it

Limitation	Resolved by
No dispersion data — individual specimen values not retained	**Repeat the series with individual values retained**
Compressive strain assumed from observation	**Instrument the strain; measure the curve**
Shrinkage unquantified, so density is a lower bound	**Record post-drying geometry**
Kerfed section calculated as a solid rectangle	**Test an un-kerfed section**
Flexural series confounded — glycerol and solids moved together	**Vary glycerol at constant solids concentration**
Durability, fire classification and life-cycle assessment untested	Outside this paper; named as further work

Every value reported today is a lower bound. None of these limitations is unknown, and each one has a defined next experiment.

Beyond the table: humidity and thermal cycling, microbial resistance, and a life-cycle assessment to support the environmental argument quantitatively.

Conclusions

01	**A protocol that can be repeated**	every production parameter reported
02	**Packing density governs compressive strength**	not mineral content
03	**Plasticiser content sets brittle or ductile response**	the transition is sharp
04	**Bio-polymer stiffness without thermal processing**	water-cast, ambient-dried
05	**Strength alone is an insufficient criterion**	report σ and E together

Betül Ünal · **b.unal91@gmail.com**

Testing: Advanced Construction Materials Research Laboratory, Hacettepe University, with thanks to Dr Hüseyin İlcan. Derived from the author's doctoral dissertation, Hacettepe University, 2025.

References

Adogla, F., Yalley, P.P.K. & Arkoh, M. (2016) Improving compressed laterite bricks using powdered eggshells. The International Journal of Engineering and Science, 5(4), 65–70.

Altun, İ.A. (2006) Mechanical properties of travertine. Afyon Kocatepe University.

Arnaud, L. & Gourlay, E. (2012) Experimental study of parameters influencing mechanical properties of hemp concretes. Construction and Building Materials, 28(1), 50–56.

Ashby, M.F. (2011) Materials selection in mechanical design. 4th edn. Oxford: Butterworth-Heinemann.

ASTM International (2017) ASTM D790-17: Flexural properties of unreinforced and reinforced plastics. West Conshohocken, PA.

ASTM International (2018) ASTM D570-98: Water absorption of plastics. West Conshohocken, PA.

Bhartiya, A. & Dubey, M. (2018) Replacement of cement with coconut shell ash and egg shell powder. IRJET, 5(6).

Bilici, V.O., Peşmen, G., Yönetken, A. & Erol, A. (2023) Effect of egg-shell particulate reinforcement in ceramic-metal composites. Thermal Science, 27(4B), 3179–3188.

Faruk, O., Bledzki, A.K., Fink, H.-P. & Sain, M. (2012) Biocomposites reinforced with natural fibers. Progress in Polymer Science, 37(11), 1552–1596.

Hernández, V. et al. (2022) Agar biopolymer films for biodegradable packaging: a reference dataset. Materials, 15(11), 3954.

Hirschler, M.M. (2013) Flammability and fire testing. In: Handbook of environmental degradation of materials. Oxford: William Andrew, 197–230.

Holling, C.S. (1973) Resilience and stability of ecological systems. Annual Review of Ecology and Systematics, 4, 1–23.

International Organization for Standardization (2020) ISO 11925-2: Ignitability of products subjected to direct impingement of flame — single-flame source test. Geneva.

Islam, M.R., Tudryn, G., Bucinell, R., Schadler, L. & Picu, R.C. (2018) Mechanical behavior of mycelium-based particulate composites. Journal of Materials Science, 53, 16371–16382.

Jones, M., Mautner, A., Luenco, S., Bismarck, A. & John, S. (2020) Engineered mycelium composite construction materials. Journal of Bionanoscience, 14(1), 1–10.

Karana, E., Barati, B., Rognoli, V. & Zeeuw van der Laan, A. (2015) Material driven design (MDD). International Journal of Design, 9(2), 35–54.

Kim, H.-S. & Pal, K. (2010) Mechanical properties of eggshell-filled poly(lactic acid) composites. Macromolecular Research.

Klyosov, A.A. (2007) Wood-plastic composites. Hoboken, NJ: Wiley-Interscience.

Mansour, G., Zoumaki, M., Tsongas, K. & Tzetzis, D. (2021) Microstructural and finite element analysis of soy protein isolate bioplastics. Materials, 14(19), 5479.

Nemli, G. & Aydın, A. (2007) Evaluation of the physical and mechanical properties of particleboard. Building and Environment, 42(3), 1210–1214.

Owuamanam, S. & Cree, D. (2020) Progress of bio-calcium carbonate waste eggshell and seashell fillers in polymer composites: a review. Journal of Composites Science, 4(2), 70.

Pope, D.G. & Hudson, R.G. (1989) Mechanical properties of timber. Structural Engineer.

Razzaq, A.K. & Yousif, R.A. (2017) Sustainability of HMA by using of egg shell powder. International Conference on Sustainable Futures, Bahrain.

Shafiei, S. et al. (2019) Egg shell-derived calcium phosphate/carbon dot nanofibrous scaffolds. Materials Science and Engineering: C, 100, 564–575.

Shah, D.U., Vollrath, F., Stires, J. & Deheyn, D.D. (2016) Housing fly larvae in silk: mechanical properties of mineral-filled biocomposites. Materials & Design, 109, 723–731.

Skórczewska, K., Kwiatkowski, W. & Kwiatkowski, M. (2020) Poly(vinyl chloride) composites with waste eggshell as a natural filler. Polymer Composites, 41(9), 3580–3589.

Soundara, B. & Vilasini, P.P. (2015) Effect of egg shell powder on the properties of clay. 50th Indian Geotechnical Conference, Pune.

Teara, A. et al. (2019) Durability of fly ash and eggshell powder to replace cement in concrete. IOP Conf. Series: Earth and Environmental Science, 244, 012025.

Torres, F.G., Troncoso, O.P., Piaggio, F. & Hijar, A. (2010) Structure–property relationships of a biopolymer network: the eggshell membrane. Acta Biomaterialia, 6(9), 3687–3693.

Tutuş, A. et al. (2018) Evaluation of egg shells in wallpaper production. 1st International Technological Sciences and Design Symposium, Giresun.

Velasco, P.M. & Gaona, J.L. (2011) Mechanical characterisation of compressed agricultural-waste panels. Construction and Building Materials.

Victor, E.I., Louis, I.C., Alfred, N.O. & Ozioma, U.N. (2019) Use of chicken eggshells as fillers in flexible polyurethane foam. International Journal of Industrial Engineering, 3(1), 1–6.

Vilarinho, I.S., Filippi, E. & Seabra, M.P. (2022) Development of eco-ceramic wall tiles with bio$CaCO_3$ from eggshells waste. Open Ceramics, 9, 100220.

William, J.S. & Owen, J.C. (1995) Egg science and technology. 4th edn. Boca Raton, FL: CRC Press.

Yönetken, A., Erol, A., Yakar, A. & Peşmen, G. (2016) Ceramic-metal composites produced by electroless Ni plating of AlN-Astaloy Cr-M. IJCMNMME, 10(3).

Zhao, X. et al. (2022) Mechanical recycling of low-density polyethylene: property evolution. Resources, Conservation and Recycling.

Standards applied: ASTM D790-17 · ISO 11925-2:2020 · ASTM D570-98(2018).