

Induprint S 1039 D

Provisional Data Sheet

- ◆ Aqueous resin solution, solubilised with DMEA

Fields of Application: Printing Inks and Overprint Varnishes

- ◆ Vehicle for pigment grinding
- ◆ Vehicle for water-based overprint varnishes and flexographic and gravure-printing inks

Performance and Characteristics:

- ◆ excellent pigment wetting
- ◆ very good hold-out
- ◆ high gloss
- ◆ very good transfer
- ◆ excellent resolubility

Appearance	:	transparent yellowish solution
Solid Contents* (oven, 1h, 130°C)	:	38 - 40 %
Viscosity * at 25°C (DIN 53019-1) (Haake Rotovisco RV 20; MS: MV-DIN)	:	2000 - 3000 mPa·s
pH Value * (DIN ISO 976)	:	8.0 – 9.0
Ionicity	:	anionic
Freeze/Thaw Stability	:	stable

2005-03-02

* Specification values listed in our certificate of analysis

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.