



TEST REPORT

DATE : 31-Mar-2020

APPLICANT : KOCO MASK

Sample Description As Declared : Antimicrobial Fabric Face Mask
Color : -
No. of Sample : 16
Order No./PO No. : -
Buyer Name : -
Style No. : -
Fiber Content :
End Uses : -
Exported To : EU
Article No. : -
Manufacture Name : KOCO Mask

Applicant Provided Care Instructions :

Machine Wash At 80°F

Gentle Cycle

Tumble Dry Low

Date Received/Date Test Started : 20 Mar 2020

Date Confirmation Received : 27 Mar 2020

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

AUTHORIZED BY
FOR INTERTEK VIETNAM LTD. [HO CHI MINH]



PHUONG LE
SOFTLINES GENERAL MANAGER

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Intertek Vietnam Ltd.

Page 1 of 3

Hochiminh office: 5th,6th,7th floor, Lobby D, S.O.H.O Biz Office Building, No. 38 Huynh Lan Khanh St., Ward 2, Tan Binh District, Ho Chi Minh City, Vietnam. Tel: (84-28) 62971099
62971098 Email: consumergoods.vietnam@intertek.com

Fax: (84-28)

Hanoi office: 3rd floor, Au Viet Building, No.01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi, Vietnam. Tel: (84-24) 37337094 Fax: (84-24) 37337093 Website: www.intertek.com

TEST REPORT

DATE : 31-Mar-2020

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Antibacterial Activity

AATCC TM100-2019 Test Organism : (Subcontracted To Can Tho Lab)

Klebsiella Pneumoniae (ATCC 4352) & Staphylococcus aureus (ATCC6538). As Receive & After 30 Washes. Washing Condition: Hand Wash At 30°C, Followed By Line Dry.

Sterilization Of Sample Before Test : Autoclave At 121°C, 15 Minutes

Neutralizing Solution : 0.85% Sodium Chloride Solution

Contact Time : 24 Hours

Incubation Temperature : 37°C

Incubation Period : 48 Hours

Agar Medium : Nutrient Agar

Tested Specimen : Submitted Sample (1g Of Square Swatches 3.8 x 3.8 cm)

As Received

Result :

	<u>Staphylococcus Aureus (ATCC 6538)(*)</u>	<u>Klebsiella pneumoniae (ATCC 4352)(*)</u>
Initial Count (CFU/ml)	2.2x10 ⁵	2.8x10 ⁵
The number of bacterial recovered from the inoculated tested sample swatches immediately after inoculation ("0" contact time)(b)(CFU/Sample)	2.5x10 ⁵	2.9x10 ⁵
The number of bacterial recovered from the inoculated tested sample swatches incubated over 24 hours contact period (a)(CFU/Sample)	<1.0x10 ²	<1.0x10 ²
Percent reduction of Bacterial (%)	>99.96	>99.97

After 30 Washes

Result :

TEST REPORT

DATE : 31-Mar-2020

	Staphylococcus Aureus (ATCC 6538)(*)	Klebsiella pneumoniae (ATCC 4352)(*)
Initial Count (CFU/ml)	2.2x10 ⁵	2.8x10 ⁵
The number of bacterial recovered from the inoculated tested sample swatches immediately after inoculation ("0" contact time)(b)(CFU/Sample)	2.7x10 ⁵	2.8x10 ⁵
The number of bacterial recovered from the inoculated tested sample swatches incubated over 24 hours contact period (a)(CFU/Sample)	<1.0x10 ²	<1.0x10 ²
Percent reduction of Bacterial (%)	>99.96	>99.96

(*) Parameters Are Not Accredited ISO 17025

Calculation : Percent Reduction Of Bacteria = (b-a)/b x 100%

CFU = Colony Forming Unit

Remark:

The report data is valid for the corresponding sample only, this is not a certificate and unrecommended for advertising purpose.

END OF THE TEST REPORT

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>.

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Intertek Vietnam Ltd.

Page 3 of 3

Hochiminh office: 5th,6th,7th floor, Lobby D, S.O.H.O Biz Office Building, No. 38 Huynh Lan Khanh St., Ward 2, Tan Binh District, Ho Chi Minh City, Vietnam. Tel: (84-28) 62971099
62971098 Email: consumergoods.vietnam@intertek.com

Fax: (84-28)

Hanoi office:3rd floor, Au Viet Building, No.01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi, Vietnam. Tel:(84-24)37337094 Fax:(84-24)37337093 Website:www.intertek.com