Average Mechanical Properties of Typical Engineering Materials[a]

(SI Units)

Materials	Density ρ (Mg/m^3)	Moduls of Elasticity E (GPa)	Modulus of Rigidity G (GPa)	Yield Strength (MPa) σ_Y Tens.	Comp.[b]	Shear	Ultimate Strength (MPa) σ_u Tens.	Comp.[b]	Shear	%Elongation in 50 mm specimen	Poisson's Ratio ν	Coef. of Therm. Expansion α (10^{-6})/°C
Metallic												
Aluminum Wrought Alloys — 2014-T6	2.79	73.1	27	414	414	172	469	469	290	10	0.35	23
Aluminum Wrought Alloys — 6061-T6	2.71	68.9	26	255	255	131	290	290	186	12	0.35	24
Cast Iron Alloys — Gray ASTM 20	7.19	67.0	27	–	–	–	179	669	–	0.6	0.28	12
Cast Iron Alloys — Malleable ASTM A-197	7.28	172	68	–	–	–	276	572	–	5	0.28	12
Copper Alloys — Red Brass C83400	8.74	101	37	70.0	70.0	–	241	241	–	35	0.35	18
Copper Alloys — Bronze C86100	8.83	103	38	345	345	–	655	655	–	20	0.34	17
Magnesium Alloy [Am 1004-T61]	1.83	44.7	18	152	152	–	276	276	152	1	0.30	26
Steel Alloys — Structural A-36	7.85	200	75	250	250	–	400	400	–	30	0.32	12
Steel Alloys — Structural A992	7.85	200	75	345	345	–	450	450	–	30	0.32	12
Steel Alloys — Stainless 304	7.86	193	75	207	207	–	517	517	–	40	0.27	17
Steel Alloys — Tool L2	8.16	200	75	703	703	–	800	800	–	22	0.32	12
Titanium Alloy [Ti-6Al-4V]	4.43	120	44	924	924	–	1,000	1,000	–	16	0.36	9.4
Nonmetallic												
Concrete — Low Strength	2.38	22.1	–	–	–	12	–	–	–	–	0.15	11
Concrete — High Strength	2.37	29.0	–	–	–	38	–	–	–	–	0.15	11
Plastic Reinforced — Kevlar 49	1.45	131	–	–	–	–	717	483	20.3	2.8	0.34	–
Plastic Reinforced — 30% Glass	1.45	72.4	–	–	–	–	90	131	–	–	0.34	–
Wood Select Structural Grade — Douglas Fir	0.47	13.1	–	–	–	–	2.1[c]	26[d]	6.2[d]	–	0.29[e]	–
Wood Select Structural Grade — White Spruce	3.60	9.65	–	–	–	–	2.5[c]	36[d]	6.7[d]	–	0.31[e]	–

[a] Specific values may vary for a particular material due to alloy or mineral composition,mechanical working of the specimen,or heat treatment. For a more exact value reference books for the material should be consulted.

[b] The yield and ultimate strengths for ductile materials can be assumed equal for both tension and compression.

[c] Measured perpendicular to the grain.

[d] Measured parallel to the grain.

[e] Deformation measured perpendicular to the grain when the load is applied along the grain.

Average Mechanical Properties of Typical Engineering Materials[a]

(U.S. Customary Units)

Materials	Specific Weight (lb/in³)	Moduls of Elasticity E (10^3) ksi	Modulus of Rigidity G (10^3) ksi	Yield Strength (ksi) σ_Y Tens.	Yield Strength (ksi) σ_Y Comp.[b]	Yield Strength (ksi) σ_Y Shear	Ultimate Strength (ksi) σ_u Tens.	Ultimate Strength (ksi) σ_u Comp.[b]	Ultimate Strength (ksi) σ_u Shear	%Elongation in 2 in. specimen	Poisson's Ratio ν	Coef. of Therm. Expansion α (10^{-6})/°F
Metallic												
Aluminum Wrought Alloys — 2014-T6	0.101	10.6	3.9	60	60	25	68	68	42	10	0.35	12.8
Aluminum Wrought Alloys — 6061-T6	0.098	10.0	3.7	37	37	19	42	42	27	12	0.35	13.1
Cast Iron Alloys — Gray ASTM 20	0.260	10.0	3.9	–	–	–	26	96	–	0.6	0.28	6.70
Cast Iron Alloys — Malleable ASTM A-19	0.263	25.0	9.8	–	–	–	40	83	–	5	0.28	6.60
Copper Alloys — Red Brass C83400	0.316	14.6	5.4	11.4	11.4	–	35	35	–	35	0.35	9.80
Copper Alloys — Bronze C86100	0.319	15.0	5.6	50	50	–	35	35	–	20	0.34	9.60
Magnesium Alloy [Am 1004-T61]	0.066	6.48	2.5	22	22	–	40	40	22	1	0.30	14.3
Steel Alloys — Structural A-36	0.284	29.0	11.0	36	36	–	58	58	–	30	0.32	6.60
Steel Alloys — Structural A992	0.284	29.0	11.0	50	50	–	65	65	–	30	0.32	6.60
Steel Alloys — Stainless 304	0.284	28.0	11.0	30	30	–	75	75	–	40	0.27	9.60
Steel Alloys — Tool L2	0.295	29.0	11.0	102	102	–	116	116	–	22	0.32	6.50
Titanium Alloy [Ti-6Al-4V]	0.160	17.4	6.4	134	134	–	145	145	–	16	0.36	5.20
Nonmetallic												
Concrete — Low Strength	0.086	3.20	–	–	–	1.8	–	–	–	–	0.15	6.0
Concrete — High Strength	0.086	4.20	–	–	–	5.5	–	–	–	–	0.15	6.0
Plastic Reinforced — Kevlar 49	0.0524	19.0	–	–	–	–	104	70	10.2	2.8	0.34	–
Plastic Reinforced — 30% Glass	0.0524	10.5	–	–	–	–	13	19	–	–	0.34	–
Wood Select Structural Grade — Douglas Fir	0.017	1.90	–	–	–	–	0.30[c]	3.78[d]	0.90[d]	–	0.29[e]	–
Wood Select Structural Grade — White Spruce	0.130	1.40	–	–	–	–	0.36[c]	5.18[d]	0.97[d]	–	0.31[e]	–

[a] Specific values may vary for a particular material due to alloy or mineral composition,mechanical working of the specimen,or heat treatment. For a more exact value reference books for the material should be consulted.

[b] The yield and ultimate strengths for ductile materials can be assumed equal for both tension and compression.

[c] Measured perpendicular to the grain.

[d] Measured parallel to the grain.

[e] Deformation measured perpendicular to the grain when the load is applied along the grain.