

BLUE STAR® XH 9650/460-1.5

Rolling Mill Water Resistant Calcium Sulfonate Complex

PRODUCT DESCRIPTION

BLUE STAR® XH 9650/460-1.5 is a unique calcium sulfonate complex thickened grease designed specifically to protect work roll bearings, spindles and other grease lubricated parts from wear and corrosion. The thickener system of BLUE STAR® XH 9650/460-1.5 resists consistency breakdown after water or steam contamination and virtually eliminates grease run out. BLUE STAR® XH 9650/460-1.5 incorporates a polymer system that imparts additional cohesive and adhesive properties not found with other calcium sulfonate complex thickened products.

	Features	Benefits
Performance	• Water Resistant	Resists the sluicing action of high pressure spray from cooling and process waters. Does not readily soften after water contamination, which means the grease will continue to lubricate in conditions where other greases would fail.
	• Superior Corrosion Protection	Provides protection from corrosion on ferrous and non-ferrous metals even in the presence of caustic or acidic process waters found in most heavy industries.
	• Excellent Lubricity	Increases the longevity of work roll bearings, highly loaded spindles and reduces machine maintenance due to the inherent anti-wear and extreme pressure properties of this grease.
	• Mechanical Shear Stability	The mechanically shear stable thickener system will not breakdown and soften under shearing and rolling operation.
	• Oxidation and Thermal Stability	The heat and oxidation resistance of both the base oils and high dropping point calcium sulfonate complex thickener ensures extended service in elevated temperature applications.
Work Environment	• Heavy Metal and Chlorine Free	The excellent anti-wear / extreme pressure and corrosion preventive capabilities are achieved without the use of chlorinated paraffin's, zinc, antimony, molybdenum or barium.

ASTM Method	Property Description	XH 9650/460-1.5
	Appearance	Brown, smooth
D 217	Cone Penetration, 0.1 mm Worked 60 Strokes	300
D 2265	Dropping Point, °F	625 +
D 445	Base Oil Kinematic Viscosity, centistokes @ 40°C	460
	Lincoln Ventmeter, psi @ 20°F @ 25°F	600 400
D 2266	Four Ball Wear, scar diameter, mm	0.56
D 2596	Four Ball Extreme Pressure, kg Load Wear Index Weld Load	75 800
D 1831	Roll Stability, % change in penetration Uncontaminated 15% water contamination	6.2 < 2
D 1743	Rust Prevention	Pass
D 1264	Water Wash Out @ 79°C, % mass loss	3.3
D 4049	Water Sprayoff @ 100°F, % mass loss	48

STORAGE AND HANDLING

BLUE STAR® XH 9650/460-1.5 greases should be stored indoors. If outdoor storage is used every effort to keep environmental contaminants from accumulating on containers should be attempted. Product is not for internal consumption. BLUE STAR® XH 9650/460-1.5 is non-irritating and non-toxic when used properly.

DISPOSABILITY

Disposal of BLUE STAR® XH 9650/460-1.5 greases should be disposed of in accordance with local, state and federal regulations.

ADDITIONAL INFORMATION

An MSDS for this product is available upon request. Purchasers of this product are urged to review and retain this information. For additional information, evaluation samples or price quotations please contact:

Blue Star Lubrication Technology® , LLC
915 N. Plum Grove Road
Suite C
Schaumburg, IL 60173
Office: (847) 285-1888
Fax: (847) 285-1894