Technical Data Sheet
ARYAFILM - A413

ARYAFILM A413 is one side corona treated & other side co-polymer coated polyester film , this film is suitable for better metallising, ink adhesion, improved bond strength in flexible packaging applications.



Sr. No.	Properties		Unit	Test Method	Target	Minimum	Maximum
General							
1	Thickness		Micron	JBF Method	23	22.54	23.46
			Gauge		92	90.16	93.84
2	Yield		M^2/Kg	JBF Method	31.06	30.45	31.69
3	Density		gm/cc	ASTM D 1505	1.395		
4	Service Temp		°C	JBF Method	-70 to 150		
Mechanical							
1	Tensile Strength at break	MD/TD	Kg/cm^2	ASTM D 882	2000	1800	2200
			(Kpsi)		28.4	25.6	31.3
2	Elongation at break	MD	%	ASTM D 882	130	90	170
		TD			120	80	160
3	Co-efficient of friction (One side to Other side)	Static	--	ASTM D 1894	0.50	0.40	0.60
		Dynamic			0.45	0.35	0.55
Thermal							
1	Shrinkage @ 150^0 C/30′	MD	%	ASTM D 1204	1.8	1.2	2.4
		TD			0.4	0.0	0.8
2	Melting Point		^0C	DSC	252	250	255
Optical							
1	Haze		%	ASTM D 1003	4.0	3.0	5.0
2	Transmittance		%	ASTM D 1003	88	85	91
Surface treatment level							
1	Co-Polymer coated side		Dynes/cm	ASTM D 2578	54	52	56
2	Corona Treated side		Dynes/cm	ASTM D 2578	52	50	54
Barrier							
1	W.V.T.R. (38°C & 90% RH)		$gm/m^2/day$	ASTM F 1249	22	17	27
			$gm/100in^2/day$		1.42	1.10	1.74
2	O.T.R. (23°C & 0%RH)		$cc/m^2/day$	ASTM D 3985	70	60	80
			$cc/100in^2/day$		4.52	3.87	5.16

MD = Machine Direction, TD = Transverse Direction

Storage & Handling: ARYA FILM need to be stocked in a closed warehouse & should not be exposed to direct sun light or light sources. Avoid extreme of humidity and heat. It is recommended to store below 40°C in dry places in original packing

Food Contact: ARYA FILM complies with EU10/2011 and US FDA regulations, Specific document and MSDS are available on request.

Disclaimer: The information given above is to the best of our knowledge and experience. Some of the properties can be changed as a result of suppliers' efforts to improve upon the quality or production efficiency of the subject. The information is believed to be true and accurate and is not intended to violate any statutory condition or right of a third party. JBF makes no warranty, express or implied, as to the fitness of the product for any specific use or purpose. The above data is purely for readers' consideration, investigation and verification and should be read in conjunction with the conditions for sale or contract

Website: www.jbfrak.com
Email: filminfo@jbfrak.ae

T.D.S No. JBF/TDS/621
Revision 05 10-July-2017