Technical Data Sheet

RBT

TRANSPARENT, BOTH SIDES HEAT SEALABLE, ONE SIDE TREATED BOPP FILM

PROPERTIES

- Both sides heat sealable
- Excellent mechanical properties
- High transparency
- Good slip & anti-static property
- Suitable for food contact

APPLICATIONS

- Printing (Rotogravure and Flexographic) & Lamination

Technical Properties	Units		Typical Values								Method
Nominal Thickness	Micron		15	18	20	22	25	30	35	40	ROWAD
Unit Weight	gm/m²		13.65	16.38	18.20	20.02	22.75	27.30	31.85	36.40	ROWAD
Yield	m²/kg		73.26	61.05	54.95	49.95	43.95	36.63	31.40	27.47	ROWAD
Wetting Tension	dynes/cm		38 min								ASTM D2578
Haze	%		2.8								ASTM D1003
Gloss @45˚	%		85								ASTM D2457
C.O.F (Film~Film)			≤0.30								ASTM D1894
Tensile Strength at Break	MD	N/mm²	140								ASTM D882
	TD	N/mm²	260								
Elongation at Break	MD	%	180								ASTM D882
	TD	%	60								
Heat Seal Strength	**UT/UT**	N/15mm	>2.2				>3.0		>3.5		ROWAD 130°C 1 Bar, 1 Sec
Dimensional Stability	MD	%	4.0								ROWAD 120°C, 5 Min/Air
	TD	%	2.0								
Heat Seal Range (Un-Treated Side)	°C		105-140								ROWAD 1 Bar, 1 Sec
Oxygen Permeability	cc/m²/24hrs		2600	2550	2200	2100	1600	1500	1300	1100	ASTM D3985 23°C, 0% RH
Water Vapor Transmission Rate	gm/m²/24hrs		4-8								ASTM F1249 38 °C,90% RH

MD: Machine Direction, TD: Transverse Direction, FxF: UTR/UTR

STORAGE AND HANDLING

In order to minimize deterioration of the level of surface treatment, storage temperature of below 30 °C is recommended for Heat sealable both side treated films. The film should be conditioned at room temperature for at least 24 hours before use. RBT film is suitable for use up to 6 months from the date of production.

TREATMENT INDICATION

The film is normally supplied with outside corona treatment. Inside corona treated or both sides treated film can also be supplied if requested.

FOOD CONTACT

Raw Material used for production of the film is approved by EU and FDA. Specific document and safety data sheet are available on request.

For more information, please contact:
Rowad Global Packaging Company, P.O. Box 14164, Dammam 31424, Kingdom of Saudi Arabia | T: +966 3 8122204 | F: +966 3 8121360