MAXOPP - PTOWL
BOPP Films

Max Speciality Films Ltd

Cavitated Non Heat Sealable 38µ Corona Treated Inside Sides for Wrap Around Labels

PRODUCT SPECIFICATION SHEET (QA)

Properties	Position	P38TIWL	P47TIWL	Tolerance Limit	Unit	Method
		Nominal Values **				
• G E N E R A L						
Nominal Thickness	-	38	47	±5%	µ	MAX (Using Flat Tip Probe with Millitron)
Grammage	-	26.22	31.50	±5%	g/m^2	MAX
• O P T I C A L						
Transmittance	-	26	22	±4	%	ASTM D 1003
Gloss	-	60		≥55	GU	ASTM D 2457
• S U R F A C E						
C O F	Film/Film	0.2		< 0.30	-	ASTM D 1894
Wetting Tension	-	38*		≥38	dy/cm	ASTM D 2578
Static Charge	-	0.4		≤0.5	Kv	MAX
• M E C H A N I C A L						
Tensile Strength (at break)	- MD	650		≥600	kg/cm^2	ASTM D 882
	- TD	1500		≥1400		
Elongation (at break)	- MD	140		≤160	%	ASTM D 882
	- TD	40		≤60		
Elastic Modulus	- MD	10000		≥8000	kg/cm^2	ASTM D 882
	- TD	20000		≥18000		
• T H E R M A L						
Linear Shrinkage	- MD	4		≤5	%	ASTM D 1204
	- TD	2		≤3		
• Remarks						
Width Tolerence		- 0 & + 2mm				

Joints	Single Joint	Percentage	Order Qty (in Tons)	Double Joint	Percentage	Order Qty (in Tons)	Remarks
		20%	≤ 1.0		5%	≤ 1.0	TYPE OF JOINT - LAP JOINT
		15%	1.0-5.0		5%	≤ 5.0	
		10%	≥ 5.0		5%	≥ 5.0	

Test ceritificate		Test ceritificate Shall Be Provided with Each Consignment
Treatment side		Shall be indicated in each Roll With Sticker
Manufacturing Date		Shall be indicated in each roll Slip

Shelf Life : Film characteristics are maintained for six months from the invoice date.

* 38 dyne/cm guaranteed for 6 months from the invoice date in controlled ambient condition (i.e. Temperature < 30 deg & Humidity 55% (Maximum) in original packed condition) .

** The figures and above properties refer to average values of laboratory test on samples of our standard production with specified lab equipements as per ASTM/MAX/AIMCAL test methods only. Customers should verify the suitability of the film for its specific end use.

Approved By

Dated

Issue :01 ,Rev :03
Date : 30.07.2021
Doc. No. QAS /Pearl-18

Max and Max Flame logo, registered trademarks of Max India Limited, are being used by Max Speciality Films Limited under license Agreements.

For Complaints technical assistance write to : **customerhelpline@maxmsp.com**
For Product development queries write to : **development@maxmsp.com**