Max Speciality Films Ltd

MAXOPP - PWL1 BOPP
Films

Cavitated Non Heat Sealable 38µ Corona Treated Both Sides High Treatment Inside for Wrap Around Labels

PRODUCT SPECIFICATION SHEET (QA)

Properties	Position	P38TTIWL1	Tolerance Limit	Unit	Method
		Nominal Values**			
• GENERAL					
Nominal Thickness	-	38	±5%	µ	MAX (Using Flat Tip Probe with Millitron)
Grammage	-	24.7	±5%	g/m^2	MAX
• OPTICAL					
Transmittance	-	26.0	±3	%	ASTM D 1003
Gloss	-	55	45-60	GU	ASTM D 2457
• SURFACE					
C O F	Film/Film	0.2	0.15-0.30	-	ASTM D 1894
Wetting Tension	-	38*	38-42	dy/cm	ASTM D 2578
• MECHANICAL					
Tensile Strength (at break)	- MD	650	600-800	kg/cm^2	ASTM D 882
	- TD	1400	1300-1600		
Elongation (at break)	- MD	150	130-170	%	ASTM D 882
	- TD	40	20-60		
Elastic Modulus	- MD	10000	8000-12000	kg/cm^2	ASTM D 882
	- TD	20000	16000-20000		
• THERMAL					
Linear Shrinkage	- MD	4	2.0-5.0	%	ASTM D 1204
	- TD	1	0.0-3.0		
• Remarks					
Width Tolerence		- 0 & + 2mm			

Joints	Single Joint	Percentage	Order Qty (in Tons)	Double Joint	Percentage	Order Qty (in Tons)	Remarks
		20%	≤ 1.0		5%	≤ 1.0	TYPE OF JOINT - LAP JOINT
		15%	1.0-5.0		5%	≤ 5.0	
		10%	≥ 5.0		5%	≥ 5.0	

Test ceritificate		Test ceritificate Shall Be Provided with Each Consignment
Treatment side		Shall be indicated in each Roll With Sticker
Manufacturing Date		Shall be indicated in each roll Slip

Shelf Life : Film characteristics are maintained for six months from the invoice date.

* 38 dyne/cm guaranteed for 3 months from the invoice date in controlled ambient condition (i.e. Temperature < 30 deg & Humidity 55% (Maximum) in original packed condition) .

** The figures and above properties refer to average values of laboratory test on samples of our standard production with specified lab equipements as per ASTM/MAX/AIMCAL test methods only. Customers should verify the suitability of the film for its specific end use.

Approved By

Dated

Issue :01 ,Rev :02
Date : 30.07.2021
Doc. No. QAS /Pearl-12

Max and Max Flame logo, registered trademarks of Max India Limited, are being used by Max Speciality Films Limited under license Agreements.

For Complaints technical assistance write to : **customerhelpline@maxmsp.com**
For Product development queries write to : **development@maxmsp.com**