MAXOPP - PWL2
BOPP Films

Max Speciality Films Ltd

Cavitated Non Heat Sealable 38µ Corona Treated Both Sides High Treatment Outside for Wrap Around Labels O.55 Density

PRODUCT SPECIFICATION SHEET (QA)

Properties	Position	P38TTOWL2	Tolerance Limit	Unit	Method
		Nominal Values **			
• G E N E R A L					
Nominal Thickness	-	38	±5%	µ	MAX (Using Flat Tip Probe with Millitron)
Grammage	-	20.9	±5%	g/m^2	MAX
• O P T I C A L					
Transmittance	-	27.0	±4	%	ASTM D 1003
Gloss	-	50	45-60	^ 45°	ASTM D 2457
• S U R F A C E					
C O F	Film/Film	0.25	0.20-0.40	-	ASTM D 1894
Wetting Tension	-	38*	38-42	dy/cm	ASTM D 2578
• M E C H A N I C A L					
Tensile Strength (at break)	- MD	600	500-700	kg/cm^2	ASTM D 882
	- TD	1200	1100-1300		
Elongation (at break)	- MD	140	120-150	%	ASTM D 882
	- TD	40	20-50		
Elastic Modulus	- MD	8500	7000-10000	kg/cm^2	ASTM D 882
	- TD	15000	14000-18000		
• T H E R M A L					
Linear Shrinkage	- MD	4	2.0-5.0	%	ASTM D 1204
	- TD	1	0.0-3.0		
• Remarks					
Width Tolerence		- 0 & + 2mm			

Joints		Percentage	Order Qty (in Tons)		Percentage	Order Qty (in Tons)	Remarks
	Single Joint	20%	≤ 1.0	**Double Joint**	5%	≤ 1.0	TYPE OF JOINT - LAP JOINT
		15%	1.0-5.0		5%	≤ 5.0	
		10%	≥ 5.0		5%	≥ 5.0	
Test ceritificate		Test ceritificate Shall Be Provided with Each Consignment					
Treatment side		Shall be indicated in each Roll With Sticker					
Manufacturing Date		Shall be indicated in each roll Slip					

Shelf Life : Film characteristics are maintained for six months from the invoice date.

* 38 dyne/cm guaranteed for 3 months from the invoice date in controlled ambient condition (i.e. Temperature < 30 deg & Humidity 55% (Maximum) in original packed condition) .

** The figures and above properties refer to average values of laboratory test on samples of our standard production with specified lab equipements as per ASTM/MAX/AIMCAL test methods only. Customers should verify the suitability of the film for its specific end use.

Approved By

Dated

Issue :01 ,Rev :03
Date : 23.08.2021
Doc. No. QAS /Pearl-06

Max and Max Flame logo, registered trademarks of Max India Limited, are being used by Max Speciality Films Limited under license Agreements.

For Complaints technical assistance write to : customerhelpline@maxmsp.com
For Product development queries write to : development@maxmsp.com