Max Speciality Films Ltd

MAXOPP - PS
BOPP Films

Pearlised Heat Sealable BOPP Film Corona treated One Side for Conversion

PRODUCT SPECIFICATION SHEET (QA)

Properties	Position	PS25TI	PS30TI	PS35TI	PS40TI	Tolerance Limit	Unit	Method
		Nominal Values**						
• G E N E R A L								
Nominal Thickness	-	25	30	35	40	±5%	μ	MAX (Using Flat Tip Probe with Millitron)
Grammage	-	17.25	20.7	24.15	27.6	±5%	g/m^2	MAX
• O P T I C A L								
Transmittance	-	36	35	32	30	±3	%	ASTM D 1003
Gloss	-	60				≥50	GU	ASTM D 2457
• S U R F A C E								
C O F	Film/Film	0.4				<0.60	-	ASTM D 1894
Wetting Tension	-	38*				≥36	dy/cm	ASTM D 2578
• M E C H A N I C A L								
Tensile Strength (at break)	- MD	700				≥600	kg/cm^2	ASTM D 882
	- TD	1500				≥1400		
Elongation (at break)	- MD	140				≤150	%	ASTM D 882
	- TD	40				≤50		
Elastic Modulus	- MD	10000				≥8000	kg/cm^2	ASTM D 882
	- TD	20000				≥18000		
• T H E R M A L								
Linear Shrinkage	- MD	4				≤5	%	ASTM D 1204
	- TD	2				≤3		
Seal initiation temperature	-	105				110	° C	MAX
Seal Strength	-	300	300	350	350	≥250	g/25mm	MAX
• Remarks								
Width Tolerence		- 0 & + 2mm						
Joints	**Single Joint**	**Percentage**	**Order Qty (in Tons)**	**Double Joint**	**Percentage**	**Order Qty (in Tons)**	**Remarks**	
		20%	≤ 1.0		5%	≤ 1.0	TYPE OF JOINT - LAP JOINT	
		15%	1.0-5.0		5%	≤ 5.0		
		10%	≥ 5.0		5%	≥ 5.0		
Test ceritificate		Test ceritificate Shall Be Provided with Each Consignment						
Treatment side		Shall be indicated in each Roll With Sticker						
Manufacturing Date		Shall be indicated in each roll Slip						

Shelf Life : Film characteristics are maintained for six months from the invoice date.

* 38 dyne/cm guaranteed for 3 months from the invoice date in controlled ambient condition (i.e. Temperature < 30 deg & Humidity 55% (Maximum) in original packed condition) .

** The figures and above properties refer to average values of laboratory test on samples of our standard production with specified lab equipements as per ASTM/MAX/AIMCAL test methods only. Customers should verify the suitability of the film for its specific end use.

Approved By

Dated

Issue :01 ,Rev :04
Date : 26.07.2021
Doc. No. QAS /Pearl-02

Max and Max Flame logo, registered trademarks of Max India Limited, are being used by Max Speciality Films Limited under license Agreements.

For Complaints technical assistance write to : **customerhelpline@maxmsp.com**
For Product development queries write to : **development@maxmsp.com**