Technical Data Sheet

RMH

HIGH BARRIER, METALLIZED ONE SIDE, HEAT SEALABLE ONE SIDE, BOPP FILM

PROPERTIES

- Good metal appearance
- Excellent moisture and gas barrier property
- High light barrier property

APPLICATIONS

- Suitable to protect light, gas and moisture sensitive products
- Thinner gauges used in lamination
- Thicker gauges used in mono web applications

Technical Properties	Units		Typical Values				Method
Nominal Thickness	Micron		15	18	20	30	ROWAD
Unit Weight	gm/m²		13.65	16.38	18.20	27.3	ROWAD
Yield	m²/kg		73.26	61.05	54.95	36.63	ROWAD
Optical Density			2.4 ± 0.2				X-RITE
C.O.F (FxF)			<0.3				ASTMD-1894
Tensile Strength at Break	MD	N/mm²	140				ASTM D-882
	TD	N/mm²	260				
Elongation at Break	MD	%	180				ASTM D-882
	TD	%	60				
Dimensional Stability	MD	%	4.0				ROWAD 120°C, 5min/Air
	TD	%	2.0				
Heat Seal Strength	**UT/UT**	N/15mm	>2.0	>2.2	>2.4	>2.4	ROWAD 130°C 1 Bar, 1 Sec
Heat Seal Range (Un-Treated)	°C		105 – 140				ROWAD 1Bar, 1 Sec
Water Vapor Transmission Rate	gm/m²/24hrs		≤0.30				ASTM F1249 38 °C, 90% RH
Oxygen Permeability	cc/m²/24hrs		≤30				ASTM D3985 23°C, 0% RH

MD: Machine Direction, TD: Transverse Direction, FxF: UTR/UTR

STORAGE AND HANDLING

In order to minimize deterioration of the level of surface tension, storage temperature of below 30 °C is recommended for Heat sealable one side metalized films.

PRINTIBILITY/LAMINATION

It is strongly recommended for in line refreshment of metallized surface before processing the material.

FOOD CONTACT

Raw Material used for production of the film is approved by EU and FDA. Specific document and safety data sheet are available on request.

For more information, please contact:
Rowad Global Packaging Company, P.O. Box 14164, Dammam 31424, Kingdom of Saudi Arabia | T: +966 3 8122204 | F: +966 3 8121360