RTL

Technical Data Sheet

ONE SIDE TREATED, TRANSPARENT LABEL BOPP FILM

PROPERTIES

- Excellent transparency
- High gloss surface
- High mechanical properties
- High surface treatment

APPLICATIONS

- Single-folded film application
- Wrapping around label
- Hot melt adhesive
- Rotogravure and flexographic printing
- Any other application for non-heart seal film

Technical Properties	Units		Typical Values				Method
Nominal Thickness	Micron		30	35	40	50	ROWAD
Unit Weight	gm/m²		27.30	31.85	36.40	45.5	ROWAD
Yield	m²/kg		36.63	31.40	27.47	21.98	ROWAD
Wetting Tension	dynes/cm		≥38				ASTM D2578
Haze	%		1.3				ASTM D1003
Gloss @ 45°	%		90				ASTM D2457
C.O.F (FxF)			<0.4				ASTM D1894
Tensile Strength at Break	MD	N/mm²	140				ASTM D882
	TD	N/mm²	240				
Elongation at Break	MD	%	180				ASTM D882
	TD	%	70				
Dimensional Stability	MD	%	4.0				ROWAD 120°C, 5 Min/Air
	TD	%	2.0				

MD: Machine Direction, TD: Transverse Direction, FxF: UTR/UTR

STORAGE AND HANDLING

In order to minimize deterioration of the level of surface treatment, storage temperature of below 30 °C is recommended for Non-Heat sealable both sides, treated films. The film should be conditioned at room temperature for at least 24 hours before use. RTL film is suitable for use up to 6 months from the date of production

TREATMENT INDICATION

The film is normally supplied with outside treatment. Inside treated or both sides treated film can also be supplied if requested.

FOOD CONTACT

Raw Material used for the film is approved by EU and FDA. Specific document and safety data sheet are available on request.

For more information, please contact:
Rowad Global Packaging Company, P.O. Box 14164, Dammam 31424, Kingdom of Saudi Arabia | T: +966 3 8122204 | F: +966 3 8121360