MAXOPP - TIHR BOPP
Films

Max Speciality Films Ltd

TRANSPARENT HEAT RESISTANT BOPP FILM FOR CONVERSION,PRINTABLE/LAMINATE

PRODUCT SPECIFICATION SHEET (QA)

Properties	Position	T15TIHR	T18TIHR	T20TIHR	T25TIHR	Tolerance Limit	Unit	Method
		Nominal Value**						
• GENERAL								
Nominal Thickness	-	15	18	20	25	±5 %	μ	MAX
Grammage	-	13.65	16.38	18.2	22.75	±5 %	g/m^2	MAX
• OPTICAL								
Haze	-	2				< 2.5	%	ASTM D 1003
Gloss	-	100				≥ 90	GU	ASTM D 2457
• SURFACE								
C O F (Heat resistance side)	Film/Film	0.18				0.10-0.25	-	ASTM D 1894
	Film/Metal	0.15				0.10-0.25	-	ASTM D 1894
Wetting Tension	-	38				≥36	dy/cm	ASTM D 2578
• MECHANICAL								
Tensile Strength (at break)	- MD	1400				≥1200	kg/cm^2	ASTM D 882
	- TD	2900				≥2600		
Elongation (at break)	- MD	170				≤190	%	ASTM D 882
	- TD	50				≤60		
Elastic Modulus	- MD	18000				≥16000	kg/cm^2	ASTM D 882
	- TD	38000				≥32000		
• THERMAL								
Linear Shrinkage	- MD	4				≤ 5	%	ASTM D 1204
	- TD	2				≤ 3		
• Defects								
Spots ®		170				≤ 255	No's per Sq.m	MAX
• Remarks								
Width Tolerence		- 0 & + 2mm						
Joints		**Single Joint**	**Percentage**	**Order Qty (in Tons)**	**Double Joint**	**Percentage**	**Order Qty (in Tons)**	**Remarks**
			20%	≤ 1.0		5%	≤ 1.0	TYPE OF JOINT - LAP JOINT
			15%	1.0-5.0		5%	≤ 5.0	
			10%	≥ 5.0		5%	≥ 5.0	
Test ceritificate		Test ceritificate Shall Be Provided with Each Consignment						
Treatment side		Shall be indicated in each Roll With Sticker						
Manufacturing Date		Shall be indicated in each roll Slip						

Shelf Life : Film characteristics are maintained for six months from the invoice date.

* 38 dyne/cm guaranteed for 3 months & 36 dynes/cm guaranteed for 6 months from the invoice date in controlled ambient condition (i.e. Temperature < 30 deg & Humidity 55% (Maximum) in original packed condition) .

** The figures and above properties refer to average values of laboratory test on samples of our standard production with specified lab equipements as per ASTM/MAX/AIMCAL test methods only. Customers should verify the suitability of the film for its specific end use..
® Spot Sizes :
≤ 0.30 mm : 204
0.30-0.80 mm : 34
0.80-1.5 mm : 17
≥ 1.5 mm : 00
Max and Max Flame logo, registered trademarks of Max India Limited, are being used by Max Speciality Films Limited under license Agreements.

Approved By

Dated

Issue :01 ,Rev :01
Date : 26.07.2021
Doc. No. QAS /Plain-13

Max and Max Flame logo, registered trademarks of Max India Limited, are being used by Max Speciality Films Limited under license Agreements.

For Complaints technical assistance write to : **customerhelpline@maxmsp.com**
For Product development queries write to : **development@maxmsp.com**