MAXOPP -TIWL

BOPP Films

Max Speciality Films Ltd

Transparent Non Heat Sealable, One Side Corona Treated for Wrap Around Labels

PRODUCT SPECIFICATION SHEET (QA)

Properties	Position	T25TIWL	T30TIWL	T38TIWL	T40TIWL	Tolerance Limit	Unit	Method
		Nominal Value**						
• G E N E R A L								
Nominal Thickness	-	25	30	38	40	±5 %	µ	MAX
Grammage	-	22.8	27.3	34.6	36.4	±5 %	g/m^2	MAX
• O P T I C A L								
Haze	-	2.5				< 3.0	%	ASTM D 1003
Gloss	-	95				≥ 90	GU	ASTM D 2457
• S U R F A C E								
C O F	Film/Film	0.3				< 0.50	-	ASTM D 1894
Wetting Tension	-	40*				≥ 38	dy/cm	ASTM D 2578
Static Charge		0.5				< 1.0	Kv	MAX
• M E C H A N I C A L								
Tensile Strength (at break)	- MD	1300				≥ 1200	kg/cm^2	ASTM D 882
	- TD	2700				≥ 2500		
Elongation (at break)	- MD	190				≤ 220	%	ASTM D 882
	- TD	60				≤ 70		
Elastic Modulus	- MD	18000				≥ 16000	kg/cm^2	ASTM D 882
	- TD	32000				≥ 28000		
• T H E R M A L								
Linear Shrinkage	- MD	4				< 5.0	%	ASTM D 1204
	- TD	2				< 3.0		
• Defects								
Gels Counts		> 4 mm-0 counts 2.0-4.0 mm -2 counts 0.5-2.0 mm-8 counts				> 4 mm- < 1 2.0-4.0 mm -4 0.5-2.0 mm-10	No's per Sq.m	MAX
Sagging		Level-01				Leve-02	Rating	MAX
•Remarks								
Width Tolerence		- 0 & + 2mm						

Joints		Single Joint	Exports	Order Qty (in Tons)	Double Joint	Exports	Order Qty (in Tons)	Remarks
			20% 15% 10%	≤ 1.0 1.0-5.0 ≥ 5.0		5% 5% 5%	≤ 1.0 ≤ 5.0 ≥ 5.0	TYPE OF JOINT - LAP JOINT

Test ceritificate		Test ceritificate Shall Be Provided with Each Consignment
Treatment side		Shall be indicated in each Roll With Sticker
Manufacturing Date		Shall be indicated in each roll Slip

Shelf Life : Film characteristics are maintained for six months from the invoice date.

* 38 dyne/cm guaranteed for 6 months from the invoice date in controlled ambient condition (i.e. Temperature < 30 deg & Humidity 55% (Maximum) in original packed condition) .

** The figures and above properties refer to average values of laboratory test on samples of our standard production with specified lab equipements as per ASTM/MAX/AIMCAL test methods only. Customers should verify the suitability of the film for its specific end use.

Approved By

Dated

Issue :01 ,Rev :04
Date : 28.07.2021
Doc. No. QAS /Plain-06

Max and Max Flame logo, registered trademarks of Max India Limited, are being used by Max Speciality Films Limited under license Agreements.

For Complaints technical assistance write to : **customerhelpline@maxmsp.com**
For Product development queries write to : **development@maxmsp.com**