
Three-Fault Slip Along Rupture, All Lengths

-2.2 -2.0 -1.8 -1.6 -1.4 -1.2 -1.0 -0.8 -0.6 -0.4 -0.2 0.0 Log10(Density)



Normalized Distance Along Strike