

Selective HER Activation of Monolayer CrCl_3 by Transition-Metal Functionalization

Juan Rafael Gomez Quispe,[†] Carlos Raul Primo Sapillado,[‡] Caique C. Oliveira,[†]
Chachi Rojas-Ayala,[‡] and Pedro Alves da Silva Autreto^{*,†}

[†]*Center of Natural and Human Sciences, Federal University of ABC, Santo Andre, Sao
Paulo, Brazil*

[‡]*Facultad de Ciencias Físicas, Universidad Nacional Mayor de San Marcos, 15081 Lima,
Peru*

E-mail: pedro.autreto@ufabc.edu.br

Phone: +55 (19) 98279-4988

Abstract

Spin-polarized density functional theory calculations were performed to investigate the effect of Co, Fe, and Ni incorporation on the hydrogen evolution reaction (HER) activity of monolayer CrCl_3 , considering both adsorbed and embedded motifs at the hollow site. Pristine CrCl_3 is intrinsically unfavorable for HER, as only one H adsorption geometry is locally stable and its adsorption free energy remains strongly positive. Co, Fe, and Ni bind strongly to the CrCl_3 surface and induce substantial structural and electronic reconstruction, including the appearance of transition-metal-derived states near the Fermi level. Among the three metals, Ni exhibits the strongest interaction with the substrate and the most pronounced perturbation of the host electronic structure, together with a tendency toward deeper incorporation during *ab initio* molecular dynamics simulations. However, the strongest metal-substrate coupling does not yield

the best HER response. The Co-adsorbed configuration gives the lowest H adsorption free energy, whereas Fe provides only moderate improvement and Ni remains less favorable. All embedded configurations are thermodynamically unfavorable for HER. These results identify adsorbed Co on monolayer CrCl_3 as the most promising motif for HER and show that catalytic activity is governed by the interplay between local coordination, electronic activation, and H-binding thermodynamics.

Introduction

The development of efficient, stable, and low-cost electrocatalysts for the hydrogen evolution reaction (HER) remains a central challenge for sustainable hydrogen production. In this context, two-dimensional (2D) materials have attracted considerable attention because their reduced dimensionality, high surface to volume ratio, and chemically accessible active sites make them promising platforms for catalytic applications. Beyond conventional nonmagnetic 2D systems, intrinsic 2D magnetic materials provide an additional degree of freedom for catalyst design, since their spin-polarized electronic structure can strongly influence charge transfer, orbital hybridization, adsorption energetics, and surface reactivity. Among these materials, chromium trihalides (CrX_3 , where $\text{X}=\text{I}, \text{Br}, \text{Cl}$) have emerged as a particularly versatile family owing to their rich interplay between electronic structure, magnetism, anisotropy, and external tunability.¹⁻⁴

Within this family, monolayer CrCl_3 is an especially appealing platform. It is an intrinsic 2D magnetic semiconductor whose magnetic properties are highly sensitive to spin orbit coupling, strain, defects, and interfacial perturbations.⁵⁻⁸ Importantly, CrCl_3 is not only a compelling theoretical platform but also an experimentally accessible material. Bulk CrCl_3 crystals have been successfully synthesized by chemical vapor transport⁹ and self-transport methods,¹⁰ and atomically thin layers can be readily isolated from these crystals by mechanical exfoliation.¹¹ Experimental studies have further shown that exfoliated CrCl_3 exhibits comparatively good environmental stability, avoiding the rapid degradation

commonly observed in more reactive chromium trihalides such as CrI_3 .[?] In addition, the fabrication of CrCl_3 thin layers by epitaxial and vapor-phase growth routes has also been demonstrated.^{??} These advances establish monolayer CrCl_3 as a realistic host material for exploring chemically functionalized two-dimensional magnetic catalysts.

Previous theoretical and computational studies have shown that CrCl_3 exhibits a comparatively weak magnetic anisotropy among chromium trihalides, which makes its magnetic state highly tunable under external stimuli such as strain, electric field, adsorption, and chemical modification.^{????} In addition, its magnetism and low-dimensional character have motivated extensive investigations on exchange interactions, magnetic excitations, spin textures, and defect-driven phenomena, confirming that CrCl_3 is a flexible host material whose electronic and magnetic properties can be significantly reshaped by local structural or chemical changes.^{?????}

From the catalytic point of view, however, pristine CrCl_3 is not an ideal HER catalyst. Recent first-principles calculations have shown that monolayer CrCl_3 possesses semiconducting character and only moderate HER activity, with a hydrogen adsorption free energy that is not fully optimized for thermo-neutral hydrogen binding.[?] This result suggests that, although the pristine material is catalytically active to some extent, its intrinsic surface still requires further tuning in order to approach the performance expected for an efficient HER electrocatalyst. Therefore, chemical functionalization emerges as a natural strategy to improve its catalytic response while simultaneously exploiting its magnetic 2D nature.

Beyond its experimental accessibility, CrCl_3 has also been shown to be highly responsive to chemical and structural perturbations. Experimental studies have demonstrated that foreign species, defects, and related chemical modifications can substantially alter its magnetic and electronic behavior, highlighting the sensitivity of the CrCl_3 surface to local bonding and charge redistribution.^{????} Complementary studies on transition-metal incorporation and related modifications, such as Ni doping and Fe-doped CrCl_3 under pressure, further indicate that chemical modification can strongly affect the band structure, magnetic ordering, and

overall stability of the system.^{???} Taken together, these results support transition-metal functionalization of CrCl_3 as a physically motivated and experimentally plausible route to tailor its surface chemistry and catalytic response, even though the specific Co-, Fe-, and Ni-decorated hollow-site motifs considered here remain to be directly realized and characterized.

Nevertheless, despite the growing body of work on CrCl_3 magnetism, strain effects, defects, and selected dopants, a systematic study of Co, Fe, and Ni adsorption at the hollow sites of monolayer CrCl_3 in the context of HER remains lacking. This is an important open question because Fe, Co, and Ni are prototypical $3d$ transition metals with partially filled electronic shells that can substantially modify the local density of states near the Fermi level, alter charge redistribution around the adsorption center, and potentially create more favorable active sites for hydrogen adsorption. At the same time, such adatoms may affect the structural stability of the host monolayer and may either improve or deteriorate the catalytic performance, depending on the balance between binding strength, electronic re-hybridization, and surface reactivity.

In this work, spin-polarized density functional theory (DFT) is used to examine Co, Fe, and Ni functionalization of monolayer CrCl_3 at the hollow site, considering both adsorbed and embedded motifs. We determine their relative stability, analyze the associated structural and electronic reconstruction of the CrCl_3 host, and evaluate the impact of these modifications on hydrogen adsorption. The results show that pristine CrCl_3 is intrinsically unsuitable for HER, whereas transition-metal incorporation activates the surface in a highly selective manner. In particular, although Ni couples most strongly to the substrate, the Co-adsorbed configuration provides the most favorable H-binding thermodynamics, while embedded configurations remain unfavorable for HER. These findings establish that the catalytic response of functionalized CrCl_3 is governed not simply by the strength of dopant anchoring, but by the interplay between local coordination, electronic activation, and adsorption thermodynamics.

Computational Methods

All calculations were performed within the framework of spin-polarized density functional theory (DFT) using the Vienna *ab initio* Simulation Package (VASP)^{??} together with the projector augmented-wave (PAW) method.^{??} Exchange-correlation effects were described using the Perdew-Burke-Ernzerhof (PBE) functional within the generalized gradient approximation (GGA).[?] A plane-wave kinetic-energy cutoff of 400 eV was employed throughout.

The CrCl₃ (2 × 2 × 1) supercell was modeled using periodic boundary conditions, and a vacuum region of 15 Å was introduced along the out-of-plane direction to avoid spurious interactions between periodic images. Brillouin-zone integrations were carried out using a Monkhorst-Pack[?] *k*-point mesh of 5 × 5 × 1 for structural relaxations, whereas a denser 10 × 10 × 1 mesh was adopted for the calculations of the electronic band structures and projected density of states (PDOS). The band structures were evaluated along the high-symmetry path Γ -M-K- Γ of the hexagonal Brillouin zone.

All atomic positions were fully relaxed for pristine CrCl₃, as well as for the Co-, Fe-, and Ni-functionalized systems in both adsorbed and embedded configurations. Hydrogen adsorption was subsequently examined on the pristine and transition-metal-functionalized CrCl₃ surfaces using the fully relaxed geometries of the corresponding H/surface systems. Structural relaxations were continued until the residual Hellmann–Feynman forces on each atom were smaller than 0.025 eV/Å, while the electronic self-consistency criterion was set to 10^{−6} eV.

The hydrogen adsorption energy was calculated as:^{??}

$$E_{\text{ads}} = E_{\text{surf+H}} - E_{\text{surf}} - \frac{1}{2}E_{\text{H}_2}, \quad (1)$$

where $E_{\text{surf+H}}$ is the total energy of the surface with an adsorbed H atom, E_{surf} is the total energy of the corresponding clean surface, and E_{H_2} is the total energy of an isolated H₂

molecule. The adsorption free energy was then estimated as:^{?, ?}

$$G_{\text{ads}} = E_{\text{ads}} + \Delta E_{\text{ZPE}} - T\Delta S, \quad (2)$$

where ΔE_{ZPE} is the zero-point energy correction and $T\Delta S$ is the entropic contribution. At $T = 298.15$ K, their combined contribution was approximated as 0.24 eV,[?] yielding:

$$G_{\text{ads}} \approx E_{\text{ads}} + 0.24 \text{ eV}. \quad (3)$$

To further analyze the adsorption process, the adsorption energy was decomposed into interaction and deformation contributions according to:

$$E_{\text{ads}} = E_{\text{int}} + E_{\text{def}}, \quad (4)$$

where E_{int} represents the interaction energy between the adsorbate and the substrate, and E_{def} denotes the structural deformation energy associated with adsorption.

To assess the thermal stability of the adsorbed species, *ab initio* molecular dynamics (AIMD) simulations were performed within the canonical ensemble using a Nose-Hoover thermostat^{?, ?} at 300 K. The total simulation time was 5 ps. These calculations were used to monitor the vertical position of the adatoms relative to the Cr plane and to evaluate the stability of the hollow-site adsorption configurations at room temperature.

Results and Discussion

Pristine monolayer CrCl_3 was first examined as the reference system for evaluating the effect of transition-metal functionalization on HER activity. As shown in Fig. ??(a), the optimized structure preserves the characteristic Cl-Cr-Cl trilayer arrangement of chromium trihalides, in which Cr atoms form a honeycomb network and each Cr center is octahedrally coordinated by six Cl atoms. This result is consistent with previous reports describing monolayer CrCl_3 as

a stable two-dimensional magnetic semiconductor with a structurally accessible hollow site at the center of the Cr hexagon.^{???} The presence of this hollow region is particularly relevant here because it provides a natural site for transition-metal adsorption or embedding.^{??}

arxiv/figures/CrCl3_perspective.png

Figure 1: (a) Top and side views of the optimized pristine CrCl_3 monolayer, illustrating the atomic configuration, the hollow adsorption site, and the vacuum spacing ($\sim 15 \text{ \AA}$) introduced along the perpendicular direction to avoid spurious interactions between periodic images. (b) Electronic band structure of pristine monolayer CrCl_3 calculated along the high-symmetry path $\Gamma\text{-M-K-}\Gamma$, with the Fermi level aligned at 0 eV. (c) Projected density of states (PDOS), showing the orbital contributions of Cr-3d and Cl-3p states. (d) Schematic representation of the first Brillouin zone of the hexagonal lattice and the selected high-symmetry path used in the electronic-structure calculations.

The band structure in Fig. ??(b) shows that pristine CrCl_3 is semiconducting, with

a calculated band gap of 1.50 eV, in reasonable agreement with previous first-principles studies.^{???} The PDOS in Fig. ??(c) further indicates that the states near the band edges are dominated by Cr-3*d* orbitals, with an important contribution from Cl-3*p* states, evidencing noticeable Cr-3*d*/Cl-3*p* hybridization. This orbital character agrees with earlier studies on CrCl₃ and shows that the hollow region is embedded in an electronically active Cr-Cl environment rather than an inert surface.^{???} Accordingly, pristine CrCl₃ provides a suitable platform for analyzing how Co, Fe, and Ni incorporation modifies the local electronic structure and, consequently, the H-adsorption thermodynamics.

Hydrogen adsorption on pristine monolayer CrCl₃ was evaluated by considering three representative initial sites, labeled S₁, S₂, and S₃, as shown in Fig. ??(a). After structural relaxation, the H atom is repelled from the surface for the S₁ and S₂ configurations [Fig. ??(b,c)], indicating that these sites are not favorable for adsorption. In contrast, only the S₃ configuration relaxes to a bound state [Fig. ??(d)], with a final H-surface distance of 1.55 Å.

Figure 2: (a) Top view of the pristine CrCl₃ monolayer, showing the three nonequivalent initial adsorption sites considered for a single H atom, labeled as S₁, S₂, and S₃. (b-d) Side views of the relaxed adsorption geometries obtained after placing H at the S₁, S₂, and S₃ sites, respectively. These panels illustrate the distinct adsorption behaviors after structural relaxation and the corresponding equilibrium distances between the H atom and the CrCl₃ monolayer.

Despite this local stabilization at S₃, the calculated adsorption free energy remains strongly positive, with $G_{\text{ads}} = 1.82$ eV, indicating that H adsorption on pristine CrCl₃ is thermodynamically unfavorable. This result confirms the poor intrinsic HER activity of the pristine monolayer and is consistent with previous theoretical studies identifying CrCl₃ as a suboptimal HER platform in the absence of chemical functionalization.^{???} Therefore, transition-metal incorporation is explored below as a strategy to activate the CrCl₃ surface toward more favorable H binding.

Figure ??(a-f) summarizes the optimized adsorbed and embedded configurations of Co,

Fe, and Ni in the hollow region of monolayer CrCl_3 . In the adsorbed structures, all three metals remain bound above the surface, confirming that the hollow site is a favorable anchoring region for transition-metal adsorption on CrCl_3 , consistent with previous reports on adsorbates and foreign-atom incorporation in this system.^{???} The equilibrium adatom-surface distances are 1.92, 1.76, and 1.44 Å for Co, Fe, and Ni, respectively, while the corresponding adsorption energies are -2.82 , -2.60 , and -3.38 eV. These results indicate strong chemisorption in all cases, with Ni displaying the strongest interaction with the CrCl_3 host.


Charge-density-difference and Bader analyses (Fig. S1) further support this picture by showing pronounced local charge redistribution around the adsorbed atoms. The calculated charge transfers are $0.77|e|$, $0.94|e|$, and $0.59|e|$ for Co, Fe, and Ni, respectively, indicating that adsorption strength is not determined solely by the net amount of transferred charge. Instead, the stronger Ni binding is more consistent with enhanced local hybridization between the Ni-3*d* states and the Cr-Cl electronic environment. The embedded structures in Fig. ??(d-f) reveal a more intimate coupling with the host lattice while preserving the overall CrCl_3 framework, highlighting the structural flexibility of this monolayer under local chemical perturbation.^{???} The corresponding embedding energies, -3.55 , -3.36 , and -4.95 eV for Co, Fe, and Ni, respectively, show that insertion into the hollow region is also energetically favorable, again with Ni as the most strongly stabilized case.

The AIMD results in Fig. ??(g-i) show that Co and Fe remain adsorbed above the CrCl_3 surface during the 5 ps simulation at 300 K, confirming their room-temperature stability. In contrast, Ni exhibits a clear downward displacement toward the Cr plane, indicating a tendency toward deeper incorporation into the lattice rather than a purely surface-bound state. This dynamical behavior is fully consistent with its shorter equilibrium height and more negative adsorption energy. Together, these results identify two distinct incorporation motifs in CrCl_3 : a stable adsorbed state for Co and Fe, and a stronger embedding tendency for Ni—which are expected to play a central role in the subsequent HER analysis.

arxiv/figures/CrCl3_Ads_Abs_AIMD.png

Figure 3: Structural and dynamical characterization of Co-, Fe-, and Ni-functionalized CrCl_3 monolayers. (a-c) Side views of the optimized Co-, Fe-, and Ni-adsorbed configurations at the hollow site of pristine CrCl_3 , respectively, with the corresponding equilibrium adatom-surface distances. (d-f) Top views of the relaxed embedded configurations, in which Co, Fe, and Ni are incorporated into the hollow site of the CrCl_3 monolayer, respectively. (g-i) Time evolution of the vertical position (z coordinate) of the adsorbed Co, Fe, and Ni atoms, respectively, obtained from *ab initio* molecular dynamics (AIMD) simulations at 300 K. In each AIMD panel, the black curve denotes the instantaneous z position of the adatom, whereas the red curve represents the average z position of the Cr atoms in the CrCl_3 sheet. The figure compares the relaxed adsorption and embedding geometries and evaluates the thermal stability of the adsorbed transition-metal atoms relative to the Cr plane of the CrCl_3 monolayer.

Figure ?? shows that both adsorption and embedding of Co, Fe, and Ni strongly perturb the semiconducting electronic structure of pristine CrCl_3 . In all cases, impurity-derived states appear within or near the original band gap, and the PDOS indicates that these features arise mainly from the transition-metal $3d$ orbitals hybridized with Cr- $3d$ and Cl- $3p$ states. This behavior is consistent with the mixed Cr- $3d$ /Cl- $3p$ character of the low-energy electronic structure of CrCl_3 reported previously. ? ? ?



arxiv/figures/CrCl3_bands.png

Figure 4: Electronic band structures and projected density of states (PDOS) of CrCl_3 functionalized with transition-metal atoms. (a), (c), and (e) show the band structures of the Co-, Fe-, and Ni-adsorbed CrCl_3 systems, respectively, while (b), (d), and (f) display the corresponding PDOS. Likewise, (g), (i), and (k) present the band structures of the Co-, Fe-, and Ni-embedded CrCl_3 configurations, respectively, whereas (h), (j), and (l) show their corresponding PDOS. The Fermi level is set to 0 eV in all panels. The PDOS highlights the contributions from Cr-3*d*, Cl-3*p*, and transition-metal *d* orbitals, allowing a direct comparison between the adsorbed and embedded cases.

For the adsorbed configurations [Fig. ??(a-f)], Co and Fe introduce relatively localized

states near the Fermi level while preserving the overall band profile of the host. In contrast, Ni adsorption produces a more pronounced reconstruction, with several Ni-3*d*-derived states appearing close to the Fermi level, consistent with its shorter equilibrium distance and stronger binding to the CrCl₃ surface. The embedded configurations [Fig. ??(g-l)] lead to an even larger spectral reconstruction, with impurity states more clearly pinned inside the pristine gap, particularly for embedded Ni. These results indicate that transition-metal functionalization drives CrCl₃ toward a more electronically active state, which is expected to favor stronger interaction with adsorbed H. However, as discussed below, a stronger perturbation of the host electronic structure does not necessarily translate into the most favorable HER thermodynamics.

Figure ?? shows that H adsorption is strongly dependent on the transition metal and on whether the metal is adsorbed or embedded in the CrCl₃ monolayer. For the adsorbed systems [Fig. ??(a-c)], the H atom remains bound near the transition-metal center, with TM-H distances of 1.44, 1.57, and 1.46 Å for Co, Fe, and Ni, respectively. The corresponding adsorption free energies are $G_{\text{ads}} = 0.20, 0.51, \text{ and } 0.88$ eV, showing that Co adsorption provides the most favorable H-binding thermodynamics, whereas Fe yields only a moderate improvement and Ni remains relatively unfavorable. In contrast, the embedded configurations [Fig. ??(e-g)] exhibit much larger adsorption free energies of 1.75, 1.36, and 3.62 eV for Co, Fe, and Ni, respectively, indicating that these structures are not suitable for HER.

The energetic decomposition in Fig. ??(d,h) clarifies the origin of this trend. For the adsorbed systems, Co shows the best balance between interaction and deformation terms, leading to an almost thermo-neutral adsorption energy, whereas Fe is penalized by a larger deformation cost and Ni by an unfavorable interaction term. The embedded cases are uniformly less favorable because all of them exhibit positive interaction energies and, in the case of Ni, a particularly large deformation penalty. These results indicate that stronger metal-substrate coupling does not necessarily lead to better HER performance. Although Ni interacts most strongly with pristine CrCl₃, the most favorable catalytic response is

obtained for adsorbed Co, where the local environment provides the best compromise between surface activation and H-binding thermodynamics. This behavior is consistent with the known sensitivity of CrCl_3 to chemical functionalization and further supports adsorbed Co/ CrCl_3 as the most promising configuration among the systems considered here.^{???}

arxiv/figures/CrCl3_ads_abs_rlx_Gads.png

Figure 5: Final relaxed geometries and energetic analysis of H adsorption on transition-metal-functionalized CrCl_3 monolayers. (a-c) Top and side views of the fully relaxed Co-, Fe-, and Ni-adsorbed CrCl_3 systems, respectively, after adsorption of a single H atom. (e-g) Top and side views of the optimized Co-, Fe-, and Ni-embedded CrCl_3 configurations, respectively, also in the presence of an adsorbed H atom. The indicated bond lengths highlight the local interaction between H, the transition-metal atom, and the local atomic environment of the CrCl_3 monolayer. (d) Interaction energy (E_{int}), deformation energy (E_{def}), adsorption energy (E_{ads}), and adsorption free energy (G_{ads}) for Co, Fe, and Ni adatoms adsorbed at the hollow site of CrCl_3 . (h) The corresponding energetic contributions for Co, Fe, and Ni atoms embedded in the hollow site of the CrCl_3 monolayer.

Conclusions

In summary, spin-polarized DFT calculations were used to investigate the effect of Co, Fe, and Ni incorporation on the structural, electronic, and catalytic properties of monolayer CrCl_3 , considering both adsorbed and embedded configurations at the hollow site. Pristine CrCl_3 was found to be intrinsically unfavorable for HER because H adsorption is thermodynamically costly. Transition-metal functionalization strongly modifies the CrCl_3 host, but the catalytic response is highly selective and depends on the local coordination of the metal center.

Among the systems examined, the Co-adsorbed configuration exhibits the most favorable HER behavior, providing the lowest H adsorption free energy and the best balance between surface activation and structural distortion. Fe adsorption yields only a moderate improvement, whereas Ni, despite its stronger interaction with the substrate, does not deliver the most favorable H-binding thermodynamics. In contrast, all embedded configurations are unfavorable for HER because of their large energetic penalties. These results identify adsorbed Co/ CrCl_3 as the most promising motif for HER and show that optimal catalytic activity in functionalized CrCl_3 is governed by the interplay between metal-substrate coupling, local structure, and H adsorption thermodynamics.

TOC Graphic

