


Graphical Abstract

Selective HER Activation of Monolayer CrCl_3 by Transition-Metal Functionalization

Juan Rafael Gomez Quispe, Carlos Raul Primo Sapillado, Caique C. Oliveira, Chachi Rojas-Ayala, Pedro Alves da Silva Autreto



Selective HER Activation of Monolayer CrCl₃ by Transition-Metal Functionalization

Juan Rafael Gomez Quispe^a, Carlos Raul Primo Sapillado^b, Caique C. Oliveira^a, Chachi Rojas-Ayala^b and Pedro Alves da Silva Autreto^{a,*}

^aCenter of Natural and Human Sciences, Federal University of ABC, Santo Andre, Sao Paulo, Brazil

^bFacultad de Ciencias Físicas, Universidad Nacional Mayor de San Marcos, 15081, Lima, Peru

ARTICLE INFO

Keywords:

doped-CrCl₃

Hydrogen Evolution Reaction

Density Functional Theory

Ab-initio Molecular Dynamics

ABSTRACT

Spin-polarized density functional theory calculations were performed to investigate the effect of Co, Fe, and Ni incorporation on the hydrogen evolution reaction (HER) activity of monolayer CrCl₃, considering both adsorbed and embedded motifs at the hollow site. Pristine CrCl₃ is intrinsically unfavorable for HER, as only one H adsorption geometry is locally stable and its adsorption free energy remains strongly positive. Co, Fe, and Ni bind strongly to the CrCl₃ surface and induce substantial structural and electronic reconstruction, including the appearance of **localized** transition-metal-derived states near the Fermi level. Among the three adsorbed metals, Ni exhibits the strongest interaction with the substrate and the most pronounced perturbation of the host electronic structure, together with a tendency toward deeper incorporation during *ab initio* molecular dynamics simulations. However, the strongest metal-substrate coupling does not yield the best HER response. The Co-adsorbed configuration gives the lowest H adsorption free energy $\Delta G_{ads} = 0.20$ eV, whereas Fe provides only moderate improvement and Ni remains less active, $\Delta G_{ads} = 0.51$ and 0.88 eV, respectively. In contrast, the embedded configurations exhibit less active H-binding thermodynamics, suggesting that surface-exposed transition-metal sites are crucial for enhancing the HER activity. These results identify adsorbed Co on monolayer CrCl₃ as the most promising motif for HER and show that catalytic activity is governed by the interplay between local coordination, electronic activation, and H-binding thermodynamics.

1. Introduction

The development of efficient, stable, and low-cost electrocatalysts for the hydrogen evolution reaction (HER) remains a central challenge for sustainable hydrogen production [1, 2, 3]. In this context, two-dimensional (2D) materials have attracted considerable attention because their reduced dimensionality, high surface to volume ratio, and chemically accessible active sites make them promising platforms for catalytic applications. Beyond conventional nonmagnetic 2D systems, intrinsic 2D magnetic materials provide an additional degree of freedom for catalyst design, since their spin-polarized electronic structure can strongly influence charge transfer, orbital hybridization, adsorption energetics, and surface reactivity [2, 3]. Among these materials, chromium trihalides (CrX₃, where X=I, Br, Cl) have emerged as a particularly versatile family owing to their rich interplay between electronic structure, magnetism, anisotropy, and external tunability [4, 5, 6, 7, 8].

Within this family, monolayer CrCl₃ is an especially appealing platform. It is an intrinsic 2D magnetic semiconductor whose magnetic properties are highly sensitive to **spin-orbit** coupling, strain, defects, and interfacial perturbations [9, 10, 11, 6, 12]. Importantly, CrCl₃ is not only a compelling theoretical platform but also an experimentally accessible material. Bulk CrCl₃ crystals have been successfully synthesized by chemical vapor transport [13] and self-transport

methods [14], and atomically thin layers can be readily isolated from these crystals by mechanical exfoliation [15]. Experimental studies have further shown that exfoliated CrCl₃ exhibits comparatively good environmental stability, avoiding the rapid degradation commonly observed in more reactive chromium trihalides such as CrI₃ [14]. In addition, the fabrication of CrCl₃ thin layers by epitaxial and vapor-phase growth routes has also been demonstrated [16, 17]. These advances establish monolayer CrCl₃ as a realistic host material for exploring chemically functionalized two-dimensional magnetic catalysts.

Previous theoretical and computational studies have shown that CrCl₃ exhibits a comparatively weak magnetic anisotropy among chromium trihalides, which makes its magnetic state highly tunable under external stimuli such as strain, electric field, adsorption, and chemical modification [10, 18, 19]. In addition, its magnetism and low-dimensional character have motivated extensive investigations on exchange interactions, magnetic excitations, spin textures, and defect-driven phenomena, confirming that CrCl₃ is a flexible host material whose electronic and magnetic properties can be significantly reshaped by local structural or chemical changes [20, 21, 22, 23, 14].

From the catalytic point of view, pristine CrCl₃ typically exhibits moderate HER activity, with a hydrogen adsorption free energy that requires further refinement to reach thermoneutral binding [24]. This suggests that, while the pristine material is catalytically active, its surface can be further tuned to optimize its performance for HER electrocatalysis. Therefore, chemical functionalization emerges as a

*Corresponding author

✉ pedro.autreto@ufabc.edu.br (P.A.d.S. Autreto)

ORCID(s):

promising strategy to improve its catalytic response while simultaneously exploiting its magnetic 2D nature.

Beyond its experimental accessibility, CrCl₃ has also been shown to be highly responsive to chemical and structural perturbations. Experimental studies have demonstrated that foreign species, defects, and related chemical modifications can substantially alter its magnetic and electronic behavior, highlighting the sensitivity of the CrCl₃ surface to local bonding and charge redistribution [25, 26, 14, 27]. Complementary studies on transition-metal incorporation and related modifications, such as Ni doping and Fe-doped CrCl₃ under pressure, further indicate that chemical modification can strongly affect the band structure, magnetic ordering, and overall stability of the system [28, 13, 29]. Taken together, these results support transition-metal functionalization of CrCl₃ as a physically motivated and experimentally plausible route to tailor its surface chemistry and catalytic response, even though the specific Co-, Fe-, and Ni-decorated hollow-site motifs considered here remain to be directly realized and characterized.

Nevertheless, despite the growing body of work on the magnetism of CrCl₃, strain effects, defects, and selected dopants, a systematic study of Co, Fe, and Ni adsorption at the hollow sites of monolayer CrCl₃ in the context of HER remains lacking. This is an important open question because Fe, Co, and Ni are prototypical 3d transition metals with partially filled electronic shells that can substantially modify the local density of states near the Fermi level, alter charge redistribution around the adsorption center, and potentially create more favorable active sites for hydrogen adsorption. At the same time, such adatoms may affect the structural stability of the host monolayer and may either improve or deteriorate the catalytic performance, depending on the balance between binding strength, electronic re-hybridization, and surface reactivity.

In this work, spin-polarized density functional theory (DFT) is used to examine Co, Fe, and Ni functionalization of monolayer CrCl₃ at the hollow site, considering both adsorbed and embedded motifs. We determine their relative stability, analyze the associated structural and electronic reconstruction of the CrCl₃ host, and evaluate the impact of these modifications on hydrogen adsorption. The results show that pristine CrCl₃ is intrinsically unsuitable for HER, whereas transition-metal incorporation activates the surface in a highly selective manner. In particular, although Ni couples most strongly to the substrate, the Co-adsorbed configuration provides the most favorable H-binding thermodynamics, while embedded configurations remain unfavorable for HER. These findings establish that the catalytic response of functionalized CrCl₃ is governed not simply by the strength of dopant anchoring, but by the interplay between local coordination, electronic activation, and adsorption thermodynamics.

2. Computational Methods

All calculations were performed within the framework of spin-polarized density functional theory (DFT) using the Vienna *ab initio* Simulation Package (VASP) [30, 31] together with the projector augmented-wave (PAW) method [32, 33]. Exchange-correlation effects were described using the Perdew-Burke-Ernzerhof (PBE) functional within the generalized gradient approximation (GGA) [34]. A plane-wave kinetic-energy cutoff of 400 eV was employed throughout.

The CrCl₃ ($2 \times 2 \times 1$) supercell was modeled using periodic boundary conditions, and a vacuum region of 15 Å was introduced along the out-of-plane direction to avoid spurious interactions between periodic images. Brillouin-zone integrations were carried out using a Monkhorst-Pack [35] *k*-point mesh of $5 \times 5 \times 1$ for structural relaxations, whereas a denser $10 \times 10 \times 1$ mesh was adopted for the calculations of the electronic band structures and projected density of states (PDOS). The band structures were evaluated along the high-symmetry path Γ -M-K- Γ of the hexagonal Brillouin zone.

All atomic positions were fully relaxed for pristine CrCl₃, as well as for the Co-, Fe-, and Ni-functionalized systems in both adsorbed and embedded configurations. Hydrogen adsorption was subsequently examined on the pristine and transition-metal-functionalized CrCl₃ surfaces using the fully relaxed geometries of the corresponding H/surface systems. Structural relaxations were continued until the residual Hellmann-Feynman forces on each atom were smaller than 0.025 eV/Å, while the electronic self-consistency criterion was set to 10^{-6} eV.

The hydrogen adsorption energy was calculated as [1, 3]:

$$E_{\text{ads}} = E_{\text{surf+H}} - E_{\text{surf}} - \frac{1}{2}E_{\text{H}_2}, \quad (1)$$

where $E_{\text{surf+H}}$ is the total energy of the surface with an adsorbed H atom, E_{surf} is the total energy of the corresponding clean surface, and E_{H_2} is the total energy of an isolated H₂ molecule. The adsorption free energy was then estimated as [1, 3]:

$$G_{\text{ads}} = E_{\text{ads}} + \Delta E_{\text{ZPE}} - T\Delta S, \quad (2)$$

where ΔE_{ZPE} is the zero-point energy correction and $T\Delta S$ is the entropic contribution. At $T = 298.15$ K, their combined contribution was approximated as 0.24 eV [36], yielding:

$$G_{\text{ads}} \approx E_{\text{ads}} + 0.24 \text{ eV}. \quad (3)$$

To further analyze the adsorption process, the adsorption energy was decomposed into interaction and deformation contributions according to:

$$E_{\text{ads}} = E_{\text{int}} + E_{\text{def}}, \quad (4)$$

where E_{int} represents the interaction energy between the adsorbate and the substrate, and E_{def} denotes the structural deformation energy associated with adsorption.

To assess the thermal stability of the adsorbed species, *ab initio* molecular dynamics (AIMD) simulations were performed within the canonical ensemble using a Nose-Hoover thermostat [37, 38] at 300 K. The total simulation time was 5 ps. These calculations were used to monitor the vertical position of the adatoms relative to the Cr plane and to evaluate the stability of the hollow-site adsorption configurations at room temperature.

3. Results and Discussion

Pristine monolayer CrCl_3 was first examined as the reference system for evaluating the effect of transition-metal functionalization on HER activity. As shown in Fig. 1(a), the optimized structure preserves the characteristic Cl-Cr-Cl trilayer arrangement of chromium trihalides, in which Cr atoms form a honeycomb network and each Cr center is octahedrally coordinated by six Cl atoms. This result is consistent with previous reports describing monolayer CrCl_3 as a stable two-dimensional magnetic semiconductor with a structurally accessible hollow site at the center of the Cr hexagon [4, 39, 14, 12]. The presence of this hollow region is particularly relevant here because it provides a natural site for transition-metal adsorption or embedding [39, 27].

The band structure in Fig. 1(b) shows that pristine CrCl_3 is semiconducting, with a calculated band gap of 1.50 eV, in reasonable agreement with previous first-principles studies [39, 12, 14, 24]. The PDOS in Fig. 1(c) further indicates that the states near the band edges are dominated by Cr-3d orbitals, with an important contribution from Cl-3p states, evidencing noticeable Cr-3d/Cl-3p hybridization. This orbital character agrees with earlier studies on CrCl_3 and shows that the hollow region is embedded in an electronically active Cr-Cl environment rather than an inert surface [40, 5, 4]. Accordingly, pristine CrCl_3 provides a suitable platform for analyzing how Co, Fe, and Ni incorporation modifies the local electronic structure and, consequently, the H-adsorption thermodynamics.




Figure 1: (a) Side view of the optimized pristine CrCl_3 monolayer, illustrating the atomic configuration and the vacuum spacing ($\sim 15 \text{ \AA}$) introduced along the perpendicular direction to avoid spurious interactions between periodic images. (b) Top view highlighting the Cr-Cl bond lengths and the hollow adsorption site where the transition metals will be incorporated. (c) Electronic band structure of pristine monolayer CrCl_3 calculated along the high-symmetry path Γ -M-K- Γ , with the Fermi level aligned at 0 eV. (d) Projected density of states (PDOS), showing the orbital contributions of Cr-3d and Cl-3p states. (e) Schematic representation of the first Brillouin zone of the hexagonal lattice and the selected high-symmetry path used in the electronic-structure calculations.

Hydrogen adsorption on pristine monolayer CrCl_3 was evaluated by considering three representative initial sites, labeled S_1 , S_2 , and S_3 , as shown in Fig. 2(a). After structural relaxation, the H atom is repelled from the surface for the S_1 and S_2 configurations [Fig. 2(b,c)], indicating that these sites are not favorable for adsorption. In contrast, only the S_3 configuration relaxes to a bound state [Fig. 2(d)], with a final H-surface distance of 1.55 Å.




Figure 2: (a) Top view of the pristine CrCl₃ monolayer, showing the three nonequivalent initial adsorption sites considered for a single H atom, labeled as S₁, S₂, and S₃. (b-d) Side views of the relaxed adsorption geometries obtained after placing H at the S₁, S₂, and S₃ sites, respectively. These panels illustrate the distinct adsorption behaviors after structural relaxation and the corresponding equilibrium distances between the H atom and the CrCl₃ monolayer.

Despite this local stabilization at S₃, the calculated adsorption free energy remains strongly positive, with $G_{\text{ads}} = 1.82$ eV, indicating that H adsorption on pristine CrCl₃ is thermodynamically costly. This result confirms the low baseline HER activity of the pristine monolayer and is consistent with previous theoretical studies identifying CrCl₃ as a suboptimal HER platform in the absence of chemical functionalization [5, 4, 24]. Therefore, transition-metal incorporation is explored below as a strategy to activate the CrCl₃ surface by introducing accessible transition-metal active centers with tunable H-binding thermodynamics. Importantly, the magnetic degree of freedom inherent to the open 3d-shell transition metals (Co, Fe, Ni) plays a central role in modulating this catalytic response. Before hydrogen adsorption, the TM adatoms possess distinct local magnetic moments of $1.78 \mu_B$ for Co, $2.72 \mu_B$ for Fe, and $-0.76 \mu_B$ for Ni (which exhibits antiparallel spin coupling relative to the host Cr matrix). Upon H chemisorption, the local spin arrangement reconfigures to accommodate the bonding electron, shifting the overall cell magnetization by $\Delta M = -3.00 \mu_B$, $-0.70 \mu_B$, and $+1.00 \mu_B$ for Co, Fe, and Ni, respectively. This spin-state flexibility in the Co-functionalized system allows the local complex to absorb

the incoming hydrogen electron with minimal spin-exchange penalties, directly facilitating near-thermoneutral H adsorption thermodynamics ($\Delta G_H = 0.20$ eV). In contrast, the antiparallel spin polarization of Ni imposes a higher spin-reorganization cost upon H binding, contributing to its less favorable HER performance.

Figure 3(a-f) summarizes the optimized adsorbed and embedded configurations of Co, Fe, and Ni in the hollow region of monolayer CrCl₃. In the adsorbed structures, all three metals remain bound above the surface, confirming that the hollow site is a favorable anchoring region for transition-metal adsorption on CrCl₃, consistent with previous reports on adsorbates and foreign-atom incorporation in this system [25, 39, 14, 27]. The equilibrium adatom-surface distances are 1.92, 1.76, and 1.44 Å for Co, Fe, and Ni, respectively, while the corresponding adsorption energies are -2.82 , -2.60 , and -3.38 eV. These results indicate strong chemisorption in all cases, with Ni displaying the strongest interaction with the CrCl₃ host.

Charge-density-difference and Bader analyses (Fig. S1) further support this picture by showing pronounced local charge redistribution around the adsorbed atoms. The calculated charge transfers are $0.77|e|$, $0.94|e|$, and $0.59|e|$ for Co, Fe, and Ni, respectively, indicating that adsorption strength is not determined solely by the net amount of transferred charge. Instead, the stronger Ni binding is more consistent with enhanced local hybridization between the Ni-3d states and the Cr-Cl electronic environment. Furthermore, the local magnetic moments of the transition-metal adatoms in their adsorbed configurations are found to be $1.99 \mu_B$, $3.34 \mu_B$, and $-0.76 \mu_B$ for Co, Fe, and Ni, respectively. The embedded structures in Fig. 3(d-f) reveal a more intimate coupling with the host lattice while preserving the overall CrCl₃ framework, highlighting the structural flexibility of this monolayer under local chemical perturbation [28, 26, 14, 27]. The corresponding embedding energies, -3.55 , -3.36 , and -4.95 eV for Co, Fe, and Ni, respectively, show that insertion into the hollow region is also energetically favorable, again with Ni as the most strongly stabilized case, which exhibits a local magnetic moment of $-1.02 \mu_B$ (with corresponding values of $2.09 \mu_B$ and $3.34 \mu_B$ for embedded Co and Fe, respectively).

The AIMD results in Fig. 3(g-i) show that Co and Fe remain adsorbed above the CrCl₃ surface during the 5 ps simulation at 300 K, confirming their room-temperature stability. In contrast, Ni exhibits a clear downward displacement toward the Cr plane, indicating a tendency toward deeper incorporation into the lattice rather than a purely surface-bound state. This dynamical behavior is fully consistent with its shorter equilibrium height and more negative adsorption energy. Together, these results identify two distinct incorporation motifs in CrCl₃: a stable adsorbed state for Co and Fe, and a stronger embedding tendency for Ni—which are expected to play a central role in the subsequent HER analysis.




Figure 3: Structural and dynamical characterization of Co-, Fe-, and Ni-functionalized CrCl_3 monolayers. (a-c) Side views of the optimized Co-, Fe-, and Ni-adsorbed configurations at the hollow site of pristine CrCl_3 , respectively, with the corresponding equilibrium adatom-surface distances. (d-f) Top views of the relaxed embedded configurations, in which Co, Fe, and Ni are incorporated into the hollow site of the CrCl_3 monolayer, respectively. (g-i) Time evolution of the vertical position (z coordinate) of the adsorbed Co, Fe, and Ni atoms, respectively, obtained from *ab initio* molecular dynamics (AIMD) simulations at 300 K. In each AIMD panel, the black curve denotes the instantaneous z position of the adatom, whereas the red curve represents the average z position of the Cr atoms in the CrCl_3 sheet. The figure compares the relaxed adsorption and embedding geometries and evaluates the thermal stability of the adsorbed transition-metal atoms relative to the Cr plane of the CrCl_3 monolayer.

Figure 4 shows that both adsorption and embedding of Co, Fe, and Ni strongly perturb the semiconducting electronic structure of pristine CrCl_3 . In all cases, impurity-derived states appear within or near the original band gap, and the PDOS indicates that these features arise mainly from the transition-metal $3d$ orbitals hybridized with Cr- $3d$ and Cl- $3p$ states. This behavior is consistent with the mixed Cr- $3d$ /Cl- $3p$ character of the low-energy electronic structure of CrCl_3 reported previously [5, 4, 40].




Figure 4: Electronic band structures and projected density of states (PDOS) of CrCl_3 functionalized with transition-metal atoms. (a), (c), and (e) show the band structures of the Co-, Fe-, and Ni-adsorbed CrCl_3 systems, respectively, while (b), (d), and (f) display the corresponding PDOS. Likewise, (g), (i), and (k) present the band structures of the Co-, Fe-, and Ni-embedded CrCl_3 configurations, respectively, whereas (h), (j), and (l) show their corresponding PDOS. The Fermi level is set to 0 eV in all panels. The PDOS highlights the contributions from Cr- $3d$, Cl- $3p$, and transition-metal d orbitals, allowing a direct comparison between the adsorbed and embedded cases.

For the adsorbed configurations [Fig. 4(a-f)], Co and Fe introduce relatively localized states near the Fermi level while preserving the overall band profile of the host. In contrast, Ni adsorption produces a more pronounced reconstruction, with several Ni- $3d$ -derived states appearing close to the Fermi level, consistent with its shorter equilibrium




Figure 5: Final relaxed geometries and energetic analysis of H adsorption on transition-metal-functionalized CrCl_3 monolayers. (a-c) Top and side views of the fully relaxed Co-, Fe-, and Ni-adsorbed CrCl_3 systems, respectively, after adsorption of a single H atom. (e-g) Top and side views of the optimized Co-, Fe-, and Ni-embedded CrCl_3 configurations, respectively, also in the presence of an adsorbed H atom. The indicated bond lengths highlight the local interaction between H, the transition-metal atom, and the local atomic environment of the CrCl_3 monolayer. (d) Interaction energy (E_{int}), deformation energy (E_{def}), adsorption energy (E_{ads}), and adsorption free energy (G_{ads}) for Co, Fe, and Ni adatoms adsorbed at the hollow site of CrCl_3 . (h) The corresponding energetic contributions for Co, Fe, and Ni atoms embedded in the hollow site of the CrCl_3 monolayer.

distance and stronger binding to the CrCl_3 surface. The embedded configurations [Fig. 4(g-l)] lead to an even larger spectral reconstruction, with impurity states more clearly pinned inside the pristine gap, particularly for embedded Ni. These results indicate that transition-metal functionalization drives CrCl_3 toward a more electronically active state, which is expected to favor stronger interaction with adsorbed H [1, 36, 41]. However, as discussed below, a stronger perturbation of the host electronic structure does not necessarily translate into the most favorable HER thermodynamics.

Figure 5 shows that H adsorption is strongly dependent on the transition metal and on whether the metal is adsorbed or embedded in the CrCl_3 monolayer. For the adsorbed systems [Fig. 5(a-c)], the H atom remains bound near the transition-metal center, with TM-H distances of 1.44, 1.57, and 1.46 Å for Co, Fe, and Ni, respectively. The corresponding adsorption free energies are $G_{\text{ads}} = 0.20$, 0.51, and 0.88 eV, showing that Co adsorption provides the most favorable H-binding thermodynamics, whereas Fe




Figure 6: LOBSTER Integrated Crystal Orbital Hamilton Population (ICOHP) chemical bonding analysis and relative stability of embedded versus adsorbed configurations for Co-, Fe-, and Ni-functionalized CrCl_3 monolayers. (a–c) Individual TM–Cl ICOHP bond energy values (eV) for 3-fold coordinated adsorbed and 6-fold octahedrally coordinated embedded Co, Fe, and Ni systems, respectively. (d) Average bond strength per TM–Cl bond. (e) Total cumulative bonding interaction energy summed over all TM–Cl bonds. (f) Relative energy stability ($\Delta E = E_{\text{embedded}} - E_{\text{adsorbed}}$) for embedded versus adsorbed transition-metal configurations.

yields only a moderate improvement and Ni remains relatively unfavorable. In contrast, the embedded configurations [Fig. 5(e–g)] exhibit much larger adsorption free energies of 1.75, 1.36, and 3.62 eV for Co, Fe, and Ni, respectively, indicating that embedding the transition metals suppresses their activity for HER.

To further elucidate the strong coupling between the transition metals and the host lattice, we performed a chemical bonding analysis using the crystal orbital Hamilton population (COHP) method, as summarized in Fig. 6. The integrated COHP (ICOHP) values quantify the covalent bond strength of individual TM–Cl interactions [Fig. 6(a–c)]. For all three metals, the embedded configurations establish six TM–Cl bonds, leading to a significantly larger total cumulative bonding interaction energy [Fig. 6(e)] compared to the three-fold coordinated adsorbed states. The enhanced bonding network in the embedded state provides a strong thermodynamic driving force for lattice incorporation, particularly for Fe and Ni, which is reflected in their relative energy stabilities [Fig. 6(f)]. However, while embedding

maximizes the thermodynamic stability of the functionalized lattice, the resulting over-coordination and deep d -band localization fundamentally suppress their ability to bind hydrogen efficiently, as corroborated by the poor HER thermodynamics for the embedded cases discussed earlier.

Figure 7 illustrates the relationship between the d -band center (ϵ_d , referenced to the Fermi level $E - E_F$) of the transition metals and the corresponding hydrogen adsorption free energy (ΔG_H) for both adsorbed and embedded configurations on the CrCl_3 monolayer. For the adsorbed configurations (blue circles), the d -band centers lie closer to the Fermi level, with Co exhibiting a d -band center ($\epsilon_d \approx -1.67$ eV) that places its adsorption free energy ($\Delta G_H = 0.20$ eV) directly within the ideal HER active window (shaded light green region). In contrast, the embedded configurations (orange squares) show deeper d -band centers associated with significantly higher, unfavorable ΔG_H values (1.36–3.62 eV). The linear trends ($R^2 = 0.362$ for adsorbed and $R^2 = 0.770$ for embedded) demonstrate that the d -band center serves as an effective electronic descriptor for rationalizing and tuning the HER catalytic activity of




Figure 7: Correlation between the d -band center (ϵ_d , $E - E_F$) and the hydrogen adsorption free energy (ΔG_{H}) for adsorbed (blue circles) and embedded (orange squares) transition-metal atoms (Co, Fe, Ni) on CrCl_3 monolayers. Dashed-dotted lines represent linear regression fits ($R^2 = 0.362$ for adsorbed, $R^2 = 0.770$ for embedded), and the light green shaded band highlights the ideal HER active window ($\Delta G_{\text{H}} \approx 0.0 \pm 0.2$ eV).

functionalized CrCl_3 [36, 42, 43]. In addition, the correlation between the local magnetic moment (μ_{B}) of the functionalizing transition-metal atom and ΔG_{H} is detailed in Fig. S6 of the Supporting Information.

The energetic decomposition in Fig. 5(d,h) clarifies the origin of this trend. For the adsorbed systems, Co shows the best balance between interaction and deformation terms, leading to an almost thermo-neutral adsorption energy, whereas Fe is penalized by a larger deformation cost and Ni by a weaker interaction term. The embedded cases exhibit a weaker response because all of them exhibit positive interaction energies and, in the case of Ni, a particularly large deformation penalty. These results indicate that stronger metal–substrate coupling does not necessarily lead to better HER performance. Although Ni interacts most strongly with pristine CrCl_3 , the most favorable catalytic response is obtained for adsorbed Co, where the local environment provides the best compromise between surface activation and H-binding thermodynamics. This behavior is consistent with the known sensitivity of CrCl_3 to chemical functionalization and further supports adsorbed Co/ CrCl_3 as the most promising configuration among the systems considered here [25, 28, 26, 14, 27, 24].

4. Conclusions

In summary, spin-polarized DFT calculations were used to investigate the effect of Co, Fe, and Ni incorporation on

the structural, electronic, and catalytic properties of monolayer CrCl_3 , considering both adsorbed and embedded configurations at the hollow site. The HER activity of pristine CrCl_3 was established as a baseline reference, showing that its stable 2D framework requires chemical activation to improve the H-binding thermodynamics. Transition-metal functionalization strongly modifies the CrCl_3 host, but the catalytic response is highly selective and depends on the local coordination of the metal center.

Among the systems examined, the Co-adsorbed configuration exhibits the most favorable HER behavior, providing the lowest H adsorption free energy and the best balance between surface activation and structural distortion. Fe adsorption yields only a moderate improvement, whereas Ni, despite its stronger interaction with the substrate, does not deliver the most favorable H-binding thermodynamics. In contrast, the embedded configurations show higher free energy barriers, highlighting that surface exposure of the active transition-metal sites is essential for achieving a favorable HER response. These results identify adsorbed Co/ CrCl_3 as the most promising motif for HER and show that optimal catalytic activity in functionalized CrCl_3 is governed by the interplay between metal-substrate coupling, local structure, and H adsorption thermodynamics.

CRedit authorship contribution statement

Juan Rafael Gomez Quispe: Conceptualization, Methodology, Software, Investigation, Writing - original draft. **Carlos Raul Primo Sapillado:** Investigation,

Software, Validation. **Caïque C. Oliveira**: Investigation, Software, Writing - review. **Chachi Rojas-Ayala**: Validation, Writing - review & editing. **Pedro Alves da Silva Autreto**: Supervision, Project administration, Funding acquisition, Writing - review & editing.

Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgment

C. C. O. acknowledges the Sao Paulo Research Foundation (FAPESP process number 2024/11376-6). P. A. S. A. acknowledges Coordenacao de Aperfeicoamento de Pessoal de Nivel Superior (CAPES finance code 001), CNPq (grant 308428/2022-6) and National Institute of Science and Technology on Materials Informatics (grant no. 371610/2023-0). C. C. O., J. G. Q. and P. A. S. A. also acknowledge the UFABC Computation Multiuser Center (CCM) for the computational resources provided.

Data availability

Data will be made available on request.

References

- [1] X. Liao, R. Lu, L. Xia, Q. Liu, H. Wang, K. Zhao, Z. Wang, Y. Zhao, Density functional theory for electrocatalysis, *ENERGY & ENVIRONMENTAL MATERIALS* 5 (1) (2022) 157–185. arXiv:https://onlinelibrary.wiley.com/doi/pdf/10.1002/eem2.12204, doi:https://doi.org/10.1002/eem2.12204. URL https://onlinelibrary.wiley.com/doi/abs/10.1002/eem2.12204
- [2] B. Ipaves, J. F. Justo, J. M. de Almeida, L. V. C. Assali, P. A. d. S. Autreto, Metal-free doping strategies in two-dimensional carbon nitride c4n2 for enhanced hydrogen evolution catalysis, *ACS Omega* 10 (38) (2025) 44248–44259. doi:10.1021/acsomega.5c05773. URL https://doi.org/10.1021/acsomega.5c05773
- [3] J. R. Gomez Quispe, F. G. Ordinola Sanchez, R. M. Guzmán-Arellano, C. Rojas-Ayala, P. A. d. S. Autreto, Chirality-driven electronic, mechanical, and hydrogen adsorption properties of dodecanophene nanotubes, *ACS Omega* 11 (4) (2026) 5211–5226. arXiv:https://doi.org/10.1021/acsomega.5c07529, doi:10.1021/acsomega.5c07529. URL https://doi.org/10.1021/acsomega.5c07529
- [4] D. Soriano, M. I. Katsnelson, J. Fernández-Rossier, Magnetic Two-Dimensional Chromium Trihalides: A Theoretical Perspective, *Nano Letters* 20 (9) (2020) 6225–6234. arXiv:2008.08855, doi:10.1021/acs.nanolett.0c02381.
- [5] O. Besbes, S. Nikolaev, N. Meskini, I. Solovyev, Microscopic origin of ferromagnetism in the trihalides CrCl₃ and CrI₃, *Physical Review B* 99 (10) (2019) 1–14. arXiv:1901.09525, doi:10.1103/PhysRevB.99.104432.
- [6] I. Lee, J. Cen, O. Molchanov, S. Feng, W. L. Huey, J. van Tol, J. E. Goldberger, N. Trivedi, H.-Y. Kee, P. C. Hammel, Spin-orbit coupling controlled two-dimensional magnetism in chromium trihalides, *Physical Review B* 113 (1) (2026) 14401. arXiv:2405.16709, doi:10.1103/qg64-ztxj. URL https://doi.org/10.1103/qg64-ztxj
- [7] Y. O. Kvashnin, A. Bergman, A. I. Lichtenstein, M. I. Katsnelson, Relativistic exchange interactions in CrX₃ (X=Cl, Br, I) monolayers, *Physical Review B* 102 (11) (2020) 1–11. arXiv:2007.07611, doi:10.1103/PhysRevB.102.115162.
- [8] J. Garrido Aldea, D. L. Esteras, S. Roche, J. H. Garcia, Challenges and strategies for first-principles simulations of two-dimensional magnetic phenomena, *Nanoscale* (2025). doi:10.1039/d4nr05503a.
- [9] F. Xue, Y. Hou, Z. Wang, R. Wu, Two-dimensional ferromagnetic van der Waals CrCl₃ monolayer with enhanced anisotropy and Curie temperature, *Physical Review B* 100 (22) (2019) 1–7. arXiv:1908.07710, doi:10.1103/PhysRevB.100.224429.
- [10] L. Webster, J. A. Yan, Strain-tunable magnetic anisotropy in monolayer CrCl₃, CrBr₃, and CrI₃, *Physical Review B* 98 (14) (2018) 144411. arXiv:1809.08725, doi:10.1103/PhysRevB.98.144411. URL https://doi.org/10.1103/PhysRevB.98.144411
- [11] M. Dupont, Y. O. Kvashnin, M. Shiranzai, J. Fransson, N. Laflorencie, A. Kantian, Monolayer as an Ideal Test Bed for the Universality Classes of 2D Magnetism, *Physical Review Letters* 127 (3) (2021) 37204. arXiv:2012.12801, doi:10.1103/PhysRevLett.127.037204. URL https://doi.org/10.1103/PhysRevLett.127.037204
- [12] L. Zhu, X. Zeng, H. Luo, H. Shang, Z. Li, Theoretical Raman Study of In-Plane Spin-Phonon Coupling in a CrCl₃ Monolayer, *Journal of Physical Chemistry C* 129 (21) (2025) 9954–9967. doi:10.1021/acs.jpcc.5c02709.
- [13] M. Abdel-Hafiez, G. Lingannan, A. Ali, L. Gries, R. Thiagarajan, M. E. H. Khan, A. Abutaha, T. A. Abdel-Baset, K. Uemura, M. Mito, V. Borisov, A. Delin, R. Klingeler, M. S. R. Rao, O. Eriksson, Pressure-tuned magnetism and band-gap modulation in layered Fe-doped CrCl₃, *Physical Review B* 112 (11) (2025) 115145. doi:10.1103/v7l7-f3wj. URL https://link.aps.org/doi/10.1103/v7l7-f3wj
- [14] D. Mastripolito, L. Ottaviano, J. Wang, J. Yang, F. Gao, M. Ali, G. D'Olimpio, A. Politano, S. Palleschi, S. Kazim, R. Gunnella, A. Di Cicco, A. Sgarlata, J. Strychalska-Nowak, T. Klimczuk, R. J. Cava, L. Lozzi, G. Profeta, Emerging oxidized and defective phases in low-dimensional CrCl₃, *Nanoscale Advances* 3 (16) (2021) 4756–4766. doi:10.1039/d1na00401h.
- [15] S. Kazim, M. Ali, S. Palleschi, G. D'Olimpio, D. Mastripolito, A. Politano, R. Gunnella, A. Di Cicco, M. Renzelli, G. Moccia, O. A. Cacioppo, R. Alfonsetti, J. Strychalska-Nowak, T. Klimczuk, R. J. Cava, L. Ottaviano, Mechanical exfoliation and layer number identification of single crystal monoclinic crcl3, *Nanotechnology* 31 (39) (2020) 395706. doi:10.1088/1361-6528/ab7de6. URL https://doi.org/10.1088/1361-6528/ab7de6
- [16] A. Bedoya-Pinto, J.-R. Ji, A. K. Pandeya, P. Gargiani, S. Valdivares, P. Sessi, J. Taylor, F. Radu, K. Chang, S. Parkin, Intrinsic 2d-xy ferromagnetism in a van der waals monolayer, *Science* 374 (2021) 616–620. doi:10.1126/science.abd5146.
- [17] J. Wang, Z. Ahmadi, D. Lujan, J. Choe, T. Taniguchi, K. Watanabe, X. Li, J. Shield, X. Hong, Physical vapor transport growth of anti-ferromagnetic crcl3 flakes down to monolayer thickness, *Advanced Science* 10 (12 2022). doi:10.1002/advs.202203548.
- [18] A. Ebrahimian, A. Dyrdał, A. Qaiumzadeh, Control of magnetic states and spin interactions in bilayer CrCl₃ with strain and electric fields: an ab initio study, *Scientific Reports* 13 (1) (2023) 1–10. arXiv:2209.04527, doi:10.1038/s41598-023-32598-1. URL https://doi.org/10.1038/s41598-023-32598-1
- [19] D. L. Esteras, J. J. Baldoví, Strain engineering of magnetic exchange and topological magnons in chromium trihalides from first-principles, *Materials Today Electronics* 6 (2023). arXiv:2104.03023, doi:10.1016/j.mtelec.2023.100072.
- [20] S. Sarkar, P. Kratzer, Magnetic exchange interactions in bilayer CrX₃ (X=Cl,Br,and I): A critical assessment of the DFT+U approach MAGNETIC EXCHANGE INTERACTIONS in BILAYER ... SOUMYAJIT SARKAR and PETER KRATZER, *Physical Review B* 103 (22) (2021) 1–12. doi:10.1103/PhysRevB.103.224421.
- [21] S. Stagraczyński, P. Baláž, M. Jafari, J. Barnaś, A. Dyrdał, Magnetic ordering and dynamics in monolayers and bilayers of chromium

- trihalides: atomistic simulations approach, *Scientific Reports* 14 (1) (2024) 1–14. doi:10.1038/s41598-024-75501-2.
- [22] A. Esquembre-Kučukalić, K. B. Le, A. García-Cristóbal, M. Bernardi, D. Sangalli, A. Molina-Sánchez, Magnons in chromium trihalides calculated with the ab initio Bethe-Salpeter equation, *Physical Review B* 112 (18) (2025) 184412. arXiv:2502.06598, doi:10.1103/gbpw-zh1v. URL <http://arxiv.org/abs/2502.06598> <https://link.aps.org/doi/10.1103/gbpw-zh1v>
- [23] X. Lu, R. Fei, L. Zhu, L. Yang, Meron-like topological spin defects in monolayer CrCl₃, *Nature Communications* 11 (1) (2020). arXiv:2002.05208, doi:10.1038/s41467-020-18573-8. URL <http://dx.doi.org/10.1038/s41467-020-18573-8>
- [24] V. B. Zala, R. S. Shukla, S. K. Gupta, P. N. Gajjar, Ferromagnetic and photocatalytic properties of CrCl₃ monolayer: a spin-polarized ab initio study, *Interactions* 245 (1) (2024) 1–8. doi:10.1007/s10751-024-01971-5.
- [25] M. Luo, Y. D. Li, K. J. Wang, Y. H. Shen, Adsorption induced magnetic anisotropy in the two-dimensional magnet CrCl₃, *Solid State Communications* 321 (July) (2020). doi:10.1016/j.ssc.2020.114048.
- [26] Y. Gao, J. Wang, Y. Li, M. Xia, Z. Li, F. Gao, Point-Defect-Induced Half Metal in CrCl₃ Monolayer, *Physica Status Solidi - Rapid Research Letters* 12 (7) (2018) 3–8. doi:10.1002/pssr.201800105.
- [27] D. Mastripiolito, J. Wang, G. Profeta, L. Ottaviano, Unconventional ferrimagnetism and enhanced magnetic ordering temperature in monolayer CrCl₃ by introducing O impurities and Cl vacancies, *JPhys Materials* 5 (1) (2022). doi:10.1088/2515-7639/ac5dcd.
- [28] J. Wang, J. Yang, Y. Sun, Q. Liu, M. Xia, Z. Li, F. Gao, Y. Li, Theoretical insights in Ni doped intrinsic magnetic CrCl₃ monolayer, *Materials Today Communications* 21 (July) (2019) 100724. doi:10.1016/j.mtcomm.2019.100724. URL <https://doi.org/10.1016/j.mtcomm.2019.100724>
- [29] A. L. Safi, S. Chakraborty, M. A. Ahmed, S. Panda, B. Chattopadhyay, Influence of Mo Doping on Electronic and Magnetic Properties of Monolayer CrX₃: A First-Principles Study, *ECS Journal of Solid State Science and Technology* 12 (4) (2023) 043001. doi:10.1149/2162-8777/acc8fe. URL <https://iopscience.iop.org/article/10.1149/2162-8777/acc8fe>
- [30] G. Kresse, J. Furthmüller, Efficiency of ab-initio total energy calculations for metals and semiconductors using a plane-wave basis set, *Computational Materials Science* 6 (1) (1996) 15–50. doi:10.1016/0927-0256(96)00008-0.
- [31] G. Kresse, J. Furthmüller, Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set, *Phys. Rev. B* 54 (1996) 11169–11186. doi:10.1103/PhysRevB.54.11169. URL <https://link.aps.org/doi/10.1103/PhysRevB.54.11169>
- [32] P. E. Blöchl, Projector augmented-wave method, *Physical Review B* 50 (24) (1994) 17953–17979. doi:10.1103/PhysRevB.50.17953.
- [33] G. Kresse, D. Joubert, From ultrasoft pseudopotentials to the projector augmented-wave method, *Physical Review B* 59 (3) (1999) 1758–1775. doi:10.1103/PhysRevB.59.1758.
- [34] J. P. Perdew, K. Burke, M. Ernzerhof, Generalized gradient approximation made simple, *Phys. Rev. Lett.* 77 (1996) 3865–3868. doi:10.1103/PhysRevLett.77.3865. URL <https://link.aps.org/doi/10.1103/PhysRevLett.77.3865>
- [35] H. J. Monkhorst, J. D. Pack, Special points for brillouin-zone integrations, *Phys. Rev. B* 13 (1976) 5188–5192. doi:10.1103/PhysRevB.13.5188.
- [36] J. K. Nørskov, T. Bligaard, A. Logadottir, J. R. Kitchin, J. G. Chen, S. Pandelov, U. Stimming, Trends in the exchange current for hydrogen evolution, *Journal of The Electrochemical Society* 152 (3) (2005) J23. doi:10.1149/1.1856988. URL <https://doi.org/10.1149/1.1856988>
- [37] S. Nosé, A molecular dynamics method for simulations in the canonical ensemble, *Molecular Physics* 52 (2) (1984) 255–268. doi:10.1080/00268978400101201.
- [38] W. G. Hoover, Canonical dynamics: Equilibrium phase-space distributions, *Physical Review A* 31 (3) (1985) 1695–1697. doi:10.1103/PhysRevA.31.1695.
- [39] M. Luo, Y. D. Li, K. J. Wang, Y. H. Shen, Adsorption induced magnetic anisotropy in the two-dimensional magnet CrCl₃, *Solid State Communications* 321 (July) (2020). doi:10.1016/j.ssc.2020.114048.
- [40] B. Nharangatt, R. Chatanathodi, Electronic properties and magnetism of CrCl₃ nanoribbons, *Journal of Magnetism and Magnetic Materials* 564 (October) (2022). doi:10.1016/j.jmmm.2022.170105.
- [41] Z. Pu, I. S. Amiinu, R. Cheng, P. Wang, C. Zhang, G. Shao, S. Sun, Single-atom catalysts for electrochemical hydrogen evolution reaction: Recent advances and future perspectives, *Nano-Micro Letters* 12 (1) (2020) 21. doi:10.1007/s40820-019-0349-y.
- [42] D. Deng, L.-M. Yang, Magnetic moment is an effective descriptor for electrocatalytic nitrogen reduction reaction on two-dimensional organometallic nanosheets, *ACS Applied Materials & Interfaces* 15 (18) (2023) 22012–22024. doi:10.1021/acsami.3c01309.
- [43] C. Groome, H. Ngo, J. Li, C. S. Wang, R. Wu, R. Ragan, Influence of magnetic moment on single atom catalytic activation energy barriers, *Catalysis Letters* 152 (2022) 3657–3666. doi:10.1007/s10562-022-03932-w.