

NORDSTROM RACK – TURNKEY PROTOTYPE

SECTION 030133 – CONCRETE SLAB PATCHING

- a. Water Reducer Normal: ASTM C 494, Type A; Master Builders Solutions "MasterPozzolith" series or "MasterPolyheed" series; Euclid Chemical Co. "Eucon WR 75".
 - b. High Range Water Reducer (Superplasticizer): ASTM C 494, Type F or G and shall be of the second or third generation type. Batch plant added to extend plasticity time and reduce water 20 to 30 percent. Master Builders Solutions "MasterRheobuild 1000," or "MasterGlenium" series; Euclid Chemical "Eucon 37".
 - c. Accelerator: ASTM C 494, Type C or E, non-corrosive, non-chloride, non-chloride; Master Builders Solutions "MasterSet AC 534" or "MasterSet FP 20" (formerly "Pozzutec 20+"); Euclid Chemical Co. "Accelguard 90".
 - d. Set Retarder: ASTM C494, Type B.
- B. Reinforcing Steel:
- 1. ASTM A615, grade 60, unless indicated otherwise.
 - 2. Dowels: Provide #4 dowels, 1/2-inch (12.7mm) diameter; in length equal to trench width.
 - 3. Doweling Epoxy: Hilti Corp. (Tulsa, OK; 866-445-8827) "RE-500 SD" epoxy adhesive anchor system.
 - 4. Chairs, Bolsters, Bar Supports, and Spacers: Sized and shaped for strength and support of reinforcement during installation and placement of concrete.
 - 5. Fabricate as indicated.
- C. Accessories:
- 1. Acrylic Bonding Agent:
 - a. Euclid Chemical Co. "Flex-con".
 - b. GCP Applied Technologies, "Daraweld C".
 - c. Sika (formally Master Builders Solutions), "MasterEmaco A660".
 - 2. Curing Materials: Waterproof sheet: ASTM C171; minimum 4-mil polyethylene sheet or reinforced waterproof kraft paper.
 - 3. Vapor Retarder: Stego Industries; Stego Wrap, 10 mils thick, Class A. Include Stego Tape at seams and penetrations.
- D. Brass Monument Markers:
- 1. Provide 1-inch diameter solid brass rod. Insert into slab not less than 2-inches deep.
 - a. Basis of Design Product: PGCKO brand from Amazon.com or equal.
 - 2. Locations: As indicated on Drawings.

2.2 CONCRETE MIX

- A. Mix concrete in accordance with ASTM C94.
- B. Admixtures:
- 1. All concrete shall contain the specified water reducing or high range water reducing admixture.
 - 2. All concrete placed in cold weather conditions as defined in ACI 306.1, and all slab concrete placed in ambient temperatures below 50 degrees F, shall contain an accelerator at the manufacturer's required dosage.
 - 3. All concrete placed in hot weather conditions as defined in ACI 305.1 and ambient temperatures of 90 degrees F or above, shall contain a set retarder at the manufacturer's required dosage.
- C. Compressive Strength (unless indicated otherwise):
- 1. Typical: 3000 psi (21 MPa) 28-day compressive strength.
 - 2. Polished Concrete Areas: 3500 psi (24 MPa), 28-day compressive strength.
- D. Concrete shall have a water cement ratio of .42 or lower.

PART 3 - EXECUTION